

FleeceBACK® KEE HP

Polyester Membrane



Overview

Carlisle's FleeceBACK KEE HP (High Performance) polyester reinforced membrane is tough, durable, and versatile, making it ideal for a wide variety of re-roofing and new construction projects. Manufactured using a hot-melt extrusion process for complete scrim encapsulation, this product is available in total sheet thicknesses of 105, 115, and 135 mils.

FleeceBACK KEE HP polyester reinforced membrane offers exceptional weatherability, flexibility, and toughness due to its polyester reinforcing scrim, polyester fleece backing, and DuPont® Elvaloy® KEE HP copolymer. The polyester reinforcing scrim provides the sheet with added breaking strength, tear strength and puncture resistance for fully adhered or mechanically attached applications; the fleece backing adds to the puncture-resistance of the membrane and provides a built-in separation layer against rough concrete decks or existing asphaltic-based roofing systems. Elvaloy KEE HP, a solid plasticizer that won't migrate out of the sheet over time, helps to ensure the membrane remains pliable and weldable as it ages and reduces the amount of smoke generated during the welding process.

Features and Benefits

- » Available in white, gray, light gray, and tan and offered in 105-, 115-, and 135-mil thicknesses.
 - 105-mil roll size = 10' x 100'
 - 115-mil roll size = 10' x 100'
 - 135-mil roll size = 10' x 75'
- » Provides superior wind uplift performance and ratings (up to FM 1-990) due to a mechanical bond between the fleece and adhesive
- » Labor-saving 10'-wide sheets result in 67% fewer seams than a modified bitumen system of comparable size, when used as a cap sheet
- » Fleece backing enhances toughness, durability, and puncture-resistance
- » Polyester reinforcing scrim provides exceptional puncture strength
- » Low-volatility KEE HP plasticizer won't migrate out of the sheet over time

- » KEE HP membrane is highly resistant to chemical types, such as acids, restaurant oils, fats, and greases
- » White and Light Gray KEE HP are California Title 24 compliant
- » Passes UL-2218 Class 4 rating
- » KEE HP contributes to a wide window of weldability and less smoke during the welding process
- » Can contribute to LEED® (Leadership in Energy and Environmental Design) credits

Installation

FleeceBACK KEE HP polyester reinforced membrane can be installed as a fully adhered or a mechanically attached system.

Mechanically Fastened Roofing System

The mechanically fastened system starts with approved insulation being fastened with a minimum of 5 fasteners per 4' x 8' board. The FleeceBACK KEE HP membrane is then mechanically fastened to the deck using HP-X™ Fasteners and Piranha™ Plates or HP-XTRA Fasteners and Piranha XTRA Plates. Adjoining sheets of FleeceBACK KEE HP membrane are overlapped over the fasteners and plates and joined together with a minimum 1½"-wide hot-air weld.

Adhered Roofing System – Low Rise Foam

Insulation is mechanically fastened or adhered with Flexible FAST™ Adhesive to the roof deck. Spray-apply, splatter, or extrude adhesive onto the substrate, and allow foam to develop string/body/gel prior to setting FleeceBACK membrane into the adhesive. Roll FleeceBACK membrane with a 30"-wide, 150-pound (68 kg) segmented weighted roller to ensure full embedment. Splices are hot-air welded.

Adhered Roofing System – Water Based

HydroBond™ can be applied to the approved substrate with a medium nap roller. Once the adhesive has been applied, roll the membrane in place. To prevent over-drying, Carlisle recommends applying the adhesive 3'–4' at a time ahead of the roll. Immediately broom the membrane starting from the center and working out to the sides of the sheet using a soft bristle push broom to work out any air bubbles. Immediately after brooming, roll the adhered membrane in two directions in a crossways pattern using a minimum 150-lb (68 kg) segmented membrane roller.

Adhered Roofing System – Multiple-Ply

Insulation is mechanically fastened or adhered with Flexible FAST Adhesive, Type III, IV, or modified asphalt to the roof deck. When adhering insulation with asphalt, the insulation boards are limited to 4' x 4'. Cover boards are required over the insulation for hot asphalt installations. If a two-ply system is specified, install the SureMB Modified Base Ply with hot asphalt or Carlisle Cold Applied Adhesive over an approved substrate. Apply FleeceBACK KEE HP cap sheet membrane over the base ply substrate with Flexible FAST Adhesive, Carlisle Cold Applied Adhesive, SBS, or SEBS Type III or IV asphalt. FleeceBACK KEE HP cap sheet membrane may be adhered directly to existing smooth BUR, mineral cap sheet, or SBS modified bitumen after priming the surface with cutback asphalt primer.

Review Carlisle specifications and details for complete installation information.

FleeceBACK KEE HP

Polyester Membrane

Supplemental Approvals, Statements, and Characteristics

- » FleeceBACK KEE HP meets or exceeds the requirements of ASTM D4434 Standard Specification for Poly (Vinyl Chloride) Sheet Roofing. FleeceBACK KEE HP is classified as a Type III or a Type IV as defined by ASTM D4434.

Precautions

- » Use proper stacking procedures to ensure sufficient stability of the materials.
- » Exercise caution when walking on wet membrane; membranes may be slippery when wet.
- » Sunglasses which filter out ultraviolet light are strongly recommended since white surfaces are highly reflective to sunlight. Roofing technicians should dress appropriately and wear sunscreen.
- » White surfaces reflect heat and may become slippery due to frost and ice accumulation.
- » Care must be exercised when working close to a roof edge, particularly when the surrounding area is snow-covered, as the roof edge may not be clearly visible.
- » FleeceBACK membrane rolls must be tarped and elevated to keep them dry prior to installation. If the fleece gets wet, use a wet vac system to help remove moisture from the fleece.
- » KEE HP membrane that has been exposed to the weather must be prepared with Carlisle's PVC & KEE HP Membrane Cleaner prior to hot-air welding.

Radiative Properties for Cool Roof Rating Council (CRRC), and LEED

| Physical Property | Test Method | White KEE HP | Tan KEE HP | Gray KEE HP | Light Gray KEE HP |
|--|------------------------|--------------|------------|-------------|-------------------|
| CRRC - Initial Solar Reflectance | ASTM C1549 | 0.87 | 0.73 | 0.58 | 0.75 |
| CRRC - Solar Reflectance after 3 years | ASTM C1549 (uncleaned) | 0.71 | 0.64 | 0.53 | 0.64 |
| CRRC - Initial Thermal Emittance | ASTM C1371 | 0.89 | 0.88 | 0.88 | 0.89 |
| CRRC - Thermal Emittance after 3 years | ASTM C1371 (uncleaned) | 0.87 | 0.89 | 0.88 | 0.89 |
| Solar Reflective Index (SRI) | ASTM E1980 | 110 | 90 | 69 | 93 |
| Solar Reflective Index (SRI) SRI after 3 years | ASTM E1980 | 88 | 78 | 61 | 77 |

Typical Properties and Characteristics

| Physical Property | ASTM D4434 Requirement | 105-mil | 115-mil | 135-mil |
|--|---|-----------------------|-----------------------|-----------------------|
| Thickness over fleece | No requirement | 50-mil | 60-mil | 80-mil |
| Membrane Thickness Over Scrim, in. (mm) ASTM D4434 optical method, average of 3 areas | 0.016 min (0.40) | 0.024 (0.61) | 0.029 (0.74) | 0.036 (0.91) |
| Weight, lbs/ft ² (kg/m ²) | No requirement | 0.38 | 0.46 | 0.59 |
| Breaking strength (MD x CD), lbf/in (kN/m) ASTM D751 grab method | 200 min (35) | 410 x 360 (72 x 63) | 450 x 410 (79 x 72) | 500 x 490 (87 x 86) |
| Elongation break of reinforcement (MD x CD), % ASTM D751 grab method | 15 x 15 min For reinforcing fabric only | 35 x 30 | 35 x 30 | 35 x 30 |
| Tearing strength (MD x CD), lbf (N) ASTM D751 proc. B, 8 in. x 8 in. | 45 min (200) | 178 x 162 (791 x 720) | 147 x 174 (653 x 774) | 152 x 183 (676 x 814) |
| Air Permeance (membrane only) ASTM E2178 | | Pass | Pass | Pass |
| Low temperature bend, ASTM D2136, no cracks 5x at -40°C | PASS | PASS | PASS | PASS |
| Linear dimensional change, % ASTM D1204, 6 hours at 176°F | ±0.5 max | 0.4 typ. | 0.4 typ. | 0.4 typ. |
| Water absorption resistance, mass % ASTM D570, 166 hours at 158°F water | ±3.0 max | 1.25 | 0.87 | 0.89 |
| Puncture resistance - Dynamic, J (ft-lbf) ASTM D5635 | 20 (14.7) | 32.5 | 40 | 42.5 |
| Puncture resistance - Static, lbf (N) ASTM D5602 | 33 (145) | 63.99 | 63.99 | 63.99 |
| Puncture Resistance - Federal Puncture (Max. Load in lbf) FTM 101C | No requirement | 332 | 384 | 482 |
| Xenon-Arc resistance, no cracks/crazing 10x, ASTM G155 0.35 W/m ² at 340-nm, 63°C B.P.T. 12,600 kJ/m ² total radiant exposure 10,000 hours | PASS | PASS | PASS | PASS |
| Properties after heat aging ASTM D3045, 56 days at 176°F | | | | |
| Breaking strength, % retained | 90 min | 90 min | 90 min | 90 min |
| Elongation reinf., % retained | 90 min | 90 min | 90 min | 90 min |

Typical properties and characteristics are based on samples tested and are not guaranteed for all samples of this product. This data and information is intended as a guide and does not reflect the specification range for any particular property of this product.

LEED Information

| | |
|--|--|
| Pre-consumer Recycled Content | 10% |
| Post-consumer Recycled Content | 0% |
| Manufacturing Location | Greenville, IL |
| Solar Reflectance Index (SRI), Initial | White: 110, Tan: 90, Gray 69, Light Gray: 77 |