

SureMB 90 Base Ply



Overview

Versico's SureMB 90 Base Ply is a premium SBS-modified asphalt base sheet. SureMB 90 Base Ply can be used wherever the specification calls for a membrane base ply in conjunction with a cap sheet of VersiFleece® AC TPO or KEE HP FRS. SureMB 90 Base Ply can also be used as an air barrier, vapor barrier, and temporary roof (for up to 60 days). Contact Design and Review if SureMB 90 Base Ply is to be used as a temporary roof for more than 60 days. SureMB 90 Base Ply meets or exceeds the requirements of ASTM D6163 Type 1, Grade S for SBS-modified bituminous sheet materials using glass fiber reinforcements.

Features and Benefits

- Excellent tensile strength and puncture resistance
- Lay-flat characteristics offer easy installation without wrinkles
- Excellent dimensional stability
- Covered by Versico's Total System Warranties for up to 25 years
- Can be exposed as a temporary roof for up to 60 days

Installation

1. SureMB 90 Base Ply can be installed using Versico's Cold-Applied adhesive, ASTM D312 Type III or IV asphalt, or an approved modified asphalt.
2. When fastened in place, SureMB 90 Base Ply should overlap a minimum of 3" on both the edges and end laps.

REVIEW CURRENT VERSICO SPECIFICATIONS AND DETAILS FOR SPECIFIC INSTALLATION REQUIREMENTS.

Precautions

- Review any applicable Safety Data Sheets for complete safety information prior to use.
- Use proper stacking procedures to ensure sufficient stability of the materials.
- Keep dry. Store pallets on a flat surface, away from direct exposure to the elements.
- Do not double-stack SureMB 90 Base Ply.

Specifications

- Width: 39 3/8" (1 m)
- Length: 49' 1" (15 m)
- Roll weight: 94 lbs/roll (43 Kg/m²)
- Square feet per roll: 161 sq. ft. (14.96 m²)

Ratings and Certifications

- Meets ASTM D 6163 Type I, Grade S
- FM Approved
- Listed with Florida Building Code (FBC) FL-8077 and Texas Department of Insurance (TDI) RC-123

SureMB 90 Base Ply

Typical Properties and Characteristics

Physical Property	Test Method	Value
Maximum Load @ 73°F	ASTM D5147	10 lbs min.
Tearing Strength, min.	ASTM D5147	30 lbf
Water Absorption, max.	ASTM D5147	40 lbf
Low Temperature Flex, min.	ASTM D5147	1%
High Temperature Stability, min.	ASTM D5147	-13°F (-25°C)
Salt Solutions	ASTM D5147	250°F (121°C)
Water Vapor Permeance	ASTM E96	0.012 perms

Typical properties and characteristics are based on samples tested and are not guaranteed for all samples of this product. This data and information is intended as a guide and does not reflect the specification range for any particular property of this product.

LEED® Information

Pre-consumer Recycled Content	24.4%
Manufacturing Location	Fort Worth, TX

Packaging

Product	SureMB 90 Modified Base Sheet
Size/Weight	39⅝" x 49'94 lbs
Actual Coverage	150 ft ²
Part Number	307253



A SINGLE SOURCE FOR SINGLE-PLY ROOFING

800.992.7663 • www.versico.com