

# VersiFlex™ PVC Reinforced Coverstrip



## Overview

Versico's VersiFlex PVC Reinforced Coverstrip is an 8" (20.3 cm)-wide, nominal 60-mil (1.52 mm) or 80-mil (2.03 mm)-thick PVC flashing that contains a polyester reinforcing fabric. Available in white, gray, and tan, PVC Reinforced Coverstrip is used for stripping in rows of fasteners and plates, covering the butt joints of VersiFlex PVC and VersiFleece® PVC membranes, and stripping in PVC Coated Metal roof edging. This product's smooth surface allows a total surface fusion weld over a wide temperature range, facilitating a consistent, watertight roof system.

Note: PVC Reinforced Coverstrip cannot be used to flash corners, pipes, t-joints, any angled metal flanges such as gravel stops, or other canted metal edgings.

Versico's VersiFlex PVC Reinforced Coverstrip is part of the Certified Fabricated Accessory (CFA) program. CFAs are the only factory-fabricated PVC accessories that meet the stringent quality tolerances required for inclusion in a Versico warranted roofing system.

## Features and Benefits

- Excellent chemical resistance
- Wide window of weldability
- Low-temperature flexibility
- Impact and puncture resistance
- Easy installation
- Outstanding solar, UV, ozone, and oxidation resistance
- Available in white, gray and tan



## Installation

1. Ensure the existing PVC membrane, or Coated Metal surface is clean prior to welding the Reinforced Coverstrip in place. If dirt is present, use Versico's PVC and KEE HP Membrane Cleaner to properly prepare the surface.
2. Weld Reinforced Coverstrip in place using an auto-welder or hand-welder.
3. Use the edge of a hand-held silicone roller to press the flashing into any membrane step-off for a proper seal.

**Stripping in fasteners and plates:** Cut PVC Reinforced Coverstrip to the proper length and install atop the row of fasteners and plates, maintaining a 1½" (3.8 cm) width of Coverstrip on both sides of the row. Tack weld to hold in place; then, using a handheld hot air welder or an automatic hot air welding machine, properly weld all edges of the Coverstrip to ensure a watertight seal. Maintain a 1½" (3.8 cm)-wide weld on all edges.

REVIEW CURRENT Versico SPECIFICATIONS AND DETAILS FOR SPECIFIC INSTALLATION REQUIREMENTS.

## Precautions

- Sunglasses that filter out ultraviolet light are strongly recommended, as the membrane's white surface is highly reflective to sunlight. Roofing technicians should dress appropriately and wear sunscreen.
- Smooth surfaces may be slippery due to frost and ice buildup. Exercise caution during cold conditions to prevent falls.
- Care must be exercised when working close to a roof edge, particularly when the surrounding area is snow-covered, as the roof edge may not be clearly visible.
- Use proper stacking procedures to ensure sufficient stability of the materials.
- Exercise caution when walking on wet membrane. Membranes may be slippery when wet.
- Store PVC Reinforced Coverstrip in its original container.

## Supplemental Approvals, Statements and Characteristics

1. VersiFlex PVC meets or exceeds the requirements of ASTM D4434 Standard Specification for Poly (Vinyl Chloride) Sheet Roofing. VersiFlex is classified as Type III and/or Type IV as defined by ASTM D4434.
2. VersiFlex reinforced PVC was tested for dynamic puncture resistance per ASTM D5635-04 using the most recently modified impact head. 50-mil thick membrane was watertight after an impact energy of 22.5 J (16.6 ft-lbf), which passes the ASTM D4434 requirement.
3. VersiFlex reinforced PVC was tested for static puncture resistance per ASTM D5602-98 and exceeded 33 lbf (145 N), which passes the ASTM D4434 requirement.

# VersiFlex PVC Reinforced Coverstrip

## Typical Properties and Characteristics

Physical Property	ASTM D4434 Requirement	60-mil	80-mil
Thickness over scrim, in. (mm) ASTM D4434 optical method, average of 3 areas	0.016 min (0.40)	0.027 (0.686)	0.037 (0.940)
Weight, lbs/ft <sup>2</sup> (kg/m <sup>2</sup> )	No requirement	0.40 (1.95)	0.55 (2.68)
Breaking strength (MD x CD), lbf/in (kN/m) ASTM D751 grab method	275 min (48)	330 x 300 (58 x 55)	360 x 330 (63 x 58)
Elongation break of reinforcement (MD x CD), % ASTM D751 grab method	25 min	30 x 30	30 x 30
Tearing strength (MD x CD), lbf (N) ASTM D751 proc. B, 8 in. x 8 in.	90 min (400)	100 x 130 (445 x 578)	100 x 132 (445 x 587)
Low temperature bend, no cracks 5x ASTM D2136	PASS	PASS (-40°C)	PASS (-40°C)
Linear dimensional change, % ASTM D1204, 6 hours at 176°F	± 0.5 max	0.4	0.4
Ozone resistance, no cracks 7X ASTM D1149, 100 pphm, 168 hrs	PASS	PASS	PASS
Water absorption resistance, mass % ASTM D570 166 hours at 158°F water	± 3.0 max	2.0	2.0
Field seam strength, lbf/in. (kN/m) ASTM D1876 tested in peel	No requirement	25 (4.4) min 60 (10.5) typ	25 (4.4) min 60 (10.5) typ
Water vapor permeance, Perms ASTM E96 proc. B	No requirement	0.10 max 0.05 typ	0.10 max 0.05 typ
Puncture resistance - Federal, lbf (kN) FTM 101C, method 2031	No requirement	320	380
Puncture resistance - Dynamic, J (ft-lbf) ASTM D5635	20 (14.7)	PASS	PASS
Puncture resistance - Static, lbf (N) ASTM D5602	33 (145)	PASS	PASS
Xenon-Arc resistance, no cracks/crazing 10x ASTM G155 0.35 W/m <sup>2</sup> at 340nm, 63°C B.P.T. 12,600 kJ/m <sup>2</sup> total radiant exposure 10,000 hours	PASS	PASS	PASS
Properties after heat aging ASTM D3045, 56 days at 176°F	90 min	90 min	90 min
Breaking strength, % retained	90 min	90 min	90 min
Elongation reinf., % retained			

Typical properties and characteristics are based on samples tested and are not guaranteed for all samples of this product. This data and information is intended as a guide and does not reflect the specification or specification range for any particular property of this product.

# VersiFlex PVC Reinforced Coverstrip

## Radiative Properties for Cool Roof Rating Council (CRRC) and LEED®

Physical Property	Test Method	Gray PVC	Tan PVC	White PVC
CRRC – Initial Solar Reflectance	ASTM C1549	0.59	0.72	0.86
CRRC – Solar Reflectance after 3 years	ASTM C1549 (uncleaned)	0.49*	0.60*	0.63
CRRC – Initial Thermal Emittance	ASTM C1371	0.89	0.87	0.89
CRRC – Thermal Emittance after 3 years	ASTM C1371 (uncleaned)	0.86*	0.86*	0.87
Solar Reflective Index (SRI)	ASTM E1980	69	89	111
Solar Reflective Index (SRI) after 3 years	ASTM E1980	56*	71*	75

\* Rapid Ratings

## LEED Information

Pre-consumer Recycled Content	10%
Post-consumer Recycled Content	0%
Manufacturing Location	Greenville, IL
Solar Reflectance Index (SRI)	White: 111, Tan: 89, Gray: 69



A SINGLE SOURCE FOR SINGLE-PLY ROOFING

800.992.7663 • [www.versico.com](http://www.versico.com)