



Sure-Seal®/Sure-White®/Sure-Tough™ EPDM Roofing Systems Adhered, Ballasted and Mechanically Fastened

TABLE OF CONTENTS

July 2025

Part I-General	Page
1.01 Description	
1.02 General Design Considerations	
1.03 Quality Assurance	
1.04 Submittals	6
1.05 Warranty	7
Warranty Tables	
TABLE I – Non-Reinforced EPDM Membrane Thickness for Various Warranty Options	
TABLE II – Reinforced EPDM Membrane Thickness for Various Warranty Options	9
TABLE III - Mechanically Fastened Roofing Systems Fastening Criteria Up to 20 YR Warranty 22 GA. Steel, Structural	Concrete,
Wood Plank, and 3/4" Plywood Decks	10
TABLE IV - Mechanically Fastened Roofing Systems - Up to 20 YR Warranty - Wood (Plywood or OSB) Decks	11
TABLE V – Re-Roofing Substrate Criteria – Up to 20 YR Warranty	12
TABLE VI – Adhered Roofing Systems – Underlayment Fastening Criteria – Up to 20 YR Warranty	13
TABLE VII – Adhered SAT EPDM – Underlayment/Fastening – Up to 20 YR Warranty	15
TABLE VIII – Minimum Perimeter Width for Insulation Attachment for All Warranties	
1.06 Job Conditions	17
1.07 Product Delivery, Storage and Handling	17
Part II – Product	
2.01 General	
2.02 Membrane	
2.03 Insulation/Underlayments	
2.04 Related Materials	
2.05 Fastening Components	
2.06 Insulation Securement Adhesive	
2.07 Vapor / Air Barrier	
2.08 Edgings/Terminations	34
2.09 Roof Walkways	36
2.10 Other Carlisle Accessories	36
Part III-Execution—Adhered, Ballasted and Mechanically Fastened	
3.01 General	26
3.02 Roof Deck/Substrate Criteria	
3.03 Insulation/Underlayments	
3.04 Insulation Attachment	
3.05 Membrane Placement and Securement (including Ballasting)	
3.06 Flashings	
3.07 Roof Walkways	
3.08 Daily Seal	
3.09 Optional Color Coating	
3.10 Clean Up	
0.10 Oldan Op	JZ
ATTACHMENTS	
"Attachment I" – Ballast Criteria and Walkway - Design "B" Ballasted	55
"Attachment II" - 25/30 Year Warranty Design Enhancements	59
Installation Details.	69

Note: In addition to the information listed in this section Specifiers and Authorized applicators should reference Spec Supplement and Design Reference Sections for other pertinent information.







Sure-Seal®/Sure-White®/Sure-Tough™ EPDM Roofing Systems Adhered, Ballasted and Mechanically Fastened

July 2025

The information contained in this generic specification represents a part of Carlisle's requirements for obtaining a roofing systems warranty. Construction materials and practices, building siting and operation, climatic conditions, and other site-specific factors will have an impact on the performance of the roofing system. Carlisle recommends that the building owner retain a design professional to determine appropriate design measures to be taken in order to address these factors.

This section is to serve as criteria for Specifiers and Authorized Applicators regarding the design and installation of Carlisle's Design "A" Adhered, Design "B" Ballasted and Reinforced Mechanically Fastened EPDM Membrane Roofing Systems. Additional information essential for the design and installation of the roof system mentioned herein is also included in the Design Reference Section and also listed in the form of a Specification Supplement at the end of the Technical Manual. Specifiers and Authorized Applicators are advised to reference all applicable sections.

Various Warranty Tables have been included in Paragraph 1.05 citing various requirements by which specific warranty coverage can be obtained. Appropriate Warranty Table should be referenced to ensure proper warranty coverage.

PART I - GENERAL

1.01 Description

A. The Design "A" Adhered Roofing System incorporates Sure-Seal (black) 60- or 90- mil thick non-reinforced or Sure-Seal (gray) 60-mil thick non-reinforced or Sure-White (white) 60- or 90-mil thick non-reinforced or Sure-White (white) 60-mil thick reinforced or 45-, 60- or 75-mil Sure-Tough™ reinforced EPDM membrane. An acceptable insulation is mechanically fastened to the roof deck or adhered with Carlisle supplied urethane-based insulation adhesive or hot asphalt and the EPDM membrane is fully adhered to the insulation with Carlisle EPDM Bonding Adhesive (Sure-Seal Bonding Adhesive, Low-VOC Bonding Adhesive, Water Based Bonding Adhesive and CAV-GRIP III Bonding Adhesive). Adjoining sheets of EPDM membrane are spliced together using 3" or 6" wide SecurTAPE™ and Primer OR Factory-Applied TAPE (FAT™) and Primer. There are no maximum slope restrictions for the application of this roofing system.

Note:

When non-reinforced EPDM membrane is used, Carlisle recommends a minimum of 60-mil thick material. Sure-Seal FR 45-mil non-reinforced EPDM may be utilized when specified or required by the owner or owner's representative.

Water based adhesive may be used for projects with 20 year maximum warranty and wind speed coverage up to 72 mph.

- B. The Design "B" Loose Laid Ballasted Roofing System incorporates minimum 45-mil thick Sure-Seal (black) non-reinforced or minimum 60-mil Sure-Tough reinforced EPDM membrane. Both the EPDM membrane and an acceptable membrane underlayment or insulation are loose laid over the substrate and held in place with a minimum of 10 pounds of ballast per square foot depending upon wind load requirements. Adjoining sheets of EPDM membrane are spliced together using 3" or 6" wide SecurTAPE and Primer OR Factory-Applied TAPE (FAT) and Primer. The maximum roof slope for this roofing system is 2" to one horizontal foot.
- C. The Mechanically Fastened Roofing System incorporates 45-, 60- or 75-mil Sure-Tough or 60-mil Sure-White (white-on-black) reinforced EPDM membrane. An acceptable insulation is mechanically fastened to the roof deck

and, depending on project criteria; the reinforced membrane is mechanically fastened with the appropriate Carlisle Fastener and 2" or 2-3/8" diameter Fastening Plates (Polymer Seam Plates required over steel deck) or Fastening Bars at 6" minimum to 12" maximum along the center of the membrane splice.

Adjoining sheets of EPDM membrane are spliced together using 6" Factory-Applied TAPE (FAT) and Primer OR 6" SecurTAPE and Primer. Field membrane sheets are either 5', 6.5', 8' or 10' wide depending upon wind load requirements, building height and type of roof deck. At the roof perimeter, a heavier fastening density is required utilizing 5', 6.5' wide sheets or 9" wide Pressure-Sensitive RUSS (Reinforced Universal Securement Strip). The maximum roof slope for this roofing system is 18" in one horizontal foot.

This roofing system can also be specified over an existing standing seam, flat seam or corrugated metal roof with the membrane secured to the structural purlins. Refer to the Metal Retrofit System Specification and Details.

NOTE: The selection of various components (i.e. insulation, underlayment, membrane thickness, etc.) may vary depending on desired Warranty coverage. Refer to appropriate Warranty Tables listed in Paragraph 1.05.

Assemblies with membrane fasteners 12" or longer must be submitted for Carlisle's review to ensure adequate securement due to the possibility of increased dynamic fastener movement. Such assemblies when accepted may require the use of additional insulation fasteners and the use of 1/2" SecurShieldTM HD Recover Board.

1.02 General Design Considerations

- A. Projects where wind speed coverage greater than 55 mph is specified or those with a 20-year or longer Total System Warranty will require additional enhancements beyond those outlined in this section. Prior to installation, refer to Warranty Tables in Paragraph 1.05.
- B. Petroleum based products; certain chemicals and waste products (i.e., grease, oil, animal fats, etc.) are not compatible with these roofing systems. Carlisle should be contacted for verification of compatibility and recommendations concerning an acceptable roofing assembly.
- C. It is the responsibility of the specifier to review local, state and regional codes to determine their impact on the specified Carlisle Roofing System.
- D. It is the responsibility of the building owner or his/her designated representative to verify structural load limitation. In addition, a core cut may be taken to verify the weight of existing components when the roofing system is to be specified on an existing facility.
- E. Coordination between various trades is essential to avoid unnecessary rooftop traffic over completed sections of the roof and to prevent subsequent damage to the membrane roofing system.
- F. Concentrated loads from rooftop equipment may cause deformation of insulation/underlayment and possible damage to the membrane if proper protection is not provided. A protection course or sleepers must be specified.

G. Drainage

- Drainage must be evaluated by the Specifier in accordance with all applicable codes. Slopes may be provided by tapering the structure or through the use of tapered insulation; a sufficient number of roof drains should also be specified and properly located to allow for positive drainage. Significant ponding that could remain after 48 hours should be eliminated with the addition of auxiliary drains in low areas where ponding is anticipated. Carlisle specifically disclaims responsibility for the design and selection of an adequate drainage system and drain accessories. Selection must be made by the building owner or the owner's design professional.
- 2. Small incidental areas of ponded water will not impact the performance of this roofing system; however, in accordance with industry standards, the roofing assembly should be designed to prevent ponding of water on the roof for prolonged periods (longer than 48 hours). Good roofing practice dictates proper drainage to prevent possible excessive live loads and, in the event of a roof leak, to minimize potential interior damage to the roofing assembly and to the interior of the building.
- 3. **Tapered edge strips, crickets or saddles** are recommended where periodic ponding of water may occur. When the slope of the taper exceeds 2" to one horizontal foot additional membrane securement at the base of the tapered edge strip, cricket or saddle will be required.
- 4. On **Sure-White Roofing Systems**, a slope greater than 1/8" per horizontal foot is recommended to serve the long-term aesthetics.

H. On new construction projects, especially in cold climate regions, moisture generated due to the construction process could adversely impact various components within the roofing assembly if not addressed. Refer to Design Reference DR-01 Construction Generated Moisture" included in the Carlisle Technical Manual.

I. Vapor Retarders

- Carlisle does not require a vapor retarder for the protection of the membrane; however, it should be considered
 by the specifier for the protection of the roofing assembly (i.e. primarily insulation, underlayment and adhesives).
 The following criteria should be considered by the specifier:
- 2. Use of a vapor retarder to protect insulation and reduce moisture accumulation within an insulated roofing assembly, should be investigated by the specifier.
- 3. In the generally temperate climate of the United States, during the winter months, water vapor flows upward from a heated, more humid interior toward a colder, drier exterior. Vapor retarders are more commonly required in northern climates than in southern regions, where downward vapor pressure may be expected and the roofing membrane itself becomes the vapor retarder.
- 4. All Carlisle roofing membranes are tested and pass in accordance with ASTM E 2178 and shall qualify as an air barrier when following Carlisle specifications and details for roofing applications.
- J. On structural concrete decks, when a vapor retarder is not used, gaps in the deck along the perimeter and around penetrations must be sealed along with vertical joints between tilt-up panels, if present, to prevent infiltration of hot humid air and possible moisture contamination resulting from condensation. This is specifically important when polyurethane adhesive is used to attach the roof insulation.

NOTE: If left unaddressed, collected moisture could weaken insulation boards and facers resulting in a blow-off or increase the probability of mold growth.

- K. Retrofit Recover Projects (when the existing roofing material is left in place)
 - 1. The removal of existing wet insulation and membrane must be specified. The Specifier shall select an appropriate and compatible material as filler for voids created by removal of old insulation or membrane.
 - 2. A core cut should be taken to verify the weight of existing components when the roofing system is to be specified over an existing roofing assembly.
 - 3. Entrapment of water between the old and new membrane can damage and deteriorate new insulation/underlayment between the two membranes. If a vapor retarder or air barrier is not specified, Carlisle recommends the existing membrane be perforated to avoid potential moisture accumulation and to allow the detection of moisture to enable the building owner to take corrective action. This can be accomplished by drilling approximately 3/4" diameter holes every 100 square feet in the existing built-up roof or single-ply membrane (excluding PVC membrane).
 - 4. Existing PVC membrane must be totally removed, or the existing membrane must be cut into maximum 10' by 10' sections. All PVC flashings at the perimeter, roof drains and roof penetrations must be removed.

L. Optional Color Coating

1. Sure-Seal X-Tenda Coat Coating is recommended for color coating the EPDM membrane and flashing when required by the Specifier. Available in white or gray.

X-Tenda Coat Coating can also be specified as a "Restoration System" when applied to an existing Carlisle EPDM membrane system that may qualify for a 5 or 10-year Coating System Warranty. Refer to Carlisle's published Sure-Seal X-Tenda Coat Coating Specification for specific requirements.

NOTE: Carlisle may be contacted for other optional color coatings.

1.03 Quality Assurance

Building codes are above and beyond the intended purpose of this specification. The building **owner, owner's representative** or **Specifier** should verify local codes for applicable requirements and limitations. It is the responsibility of the specifier to review local, state and regional codes to determine their impact on the specified Carlisle Roofing System.

NOTE: For code approvals achieved with the Carlisle EPDM Roofing Systems, refer to the Carlisle EPDM Code Approval Guide, DORA (Directory of Roof Assemblies), Factory Mutual (FM) Approval Guide or Underwriters Laboratories (UL) Fire Resistance or Roofing Materials and Systems Directories.

- A. When recovering or retrofitting an existing roof system, the addition of new insulation (type and thickness) may alter the fire performance characteristics of the assembly. Building owners or their designated representatives shall consult the local code enforcement agency to avoid potential code violation.
- B. Carlisle recommends the use of Carlisle supplied products for use with these Carlisle Roofing Systems. The performance or integrity of products by others, when selected by the specifier and accepted as compatible by Carlisle, is not the responsibility of Carlisle and is disclaimed by the Carlisle Warranty.
- C. The specified roofing system must be installed by a Carlisle Authorized Roofing Applicator in compliance with drawings and specifications as approved by Carlisle SynTec.
- D. Provide polyisocyanurate insulation that meets PIMA Quality Mark Certified LTTR value through third party verification meeting ASTM C 1289, Type II, Class 1, Grade 2.
- E. There must be no deviations made from Carlisle's specification or Carlisle's approved shop drawings without the **PRIOR WRITTEN APPROVAL** of Carlisle SynTec.
- F. After completion of the installation, upon request, an inspection shall be conducted by a Field Service Representative (FSR) of Carlisle SynTec to ascertain that the membrane roofing system has been installed according to Carlisle's published specifications and details applicable at the time of bid. This inspection is to determine whether a warranty shall be issued. It is not intended as a final inspection for the benefit of the owner.
- G. For ballasted, 30-year warranty projects, the applicator must submit pictures showing the use of EPDM Primer for perimeter RUSS securement or allow random test cuts to confirm the use of EPDM Primer.

1.04 Submittals

- A. To ensure compliance with Carlisle's minimum warranty requirements, the following projects should be forwarded to Carlisle for review prior to installation, preferably prior to bid.
 - Air pressurized buildings, canopies, and buildings with large openings where the total wall openings exceed 10% of the total wall area on which the openings are located (such as airport hangars, warehouses and large maintenance facilities). Refer to Attachment IV at the end of this section for perimeter considerations, when a Mechanically Fastened System is specified.
 - Cold storage buildings and freezer facilities.
 - 3. Design "A" Adhered Roofing Systems over 250' in height for projects with warranties up to 15 years.
 - 4. Design "A" Adhered Roofing Systems over 100' in height for projects with warranties greater than 15 years.
 - 5. Design "B" Ballasted Roofing System projects over 75' in height.
 - 6. Mechanically Fastened Roofing System projects over 100' in height.
 - 7. Projects where the EPDM is expected to come in direct contact with petroleum-based products, waste products (i.e., grease, oil, animal fats, etc) and other chemicals.
 - 8. Projects where hot asphalt is specified for insulation attachment.
 - 9. Mechanically Fastened projects specified with a fastener length exceeding 12 inches.
- B. Shop drawings must be submitted to Carlisle by the Carlisle Authorized Roofing Applicator along with a completely executed Notice of Award (Page 1 of Carlisle's Request for Warranty form) for approval. Approved shop drawings are required for inspection of the roof and on projects where on-site technical assistance is requested.

Shop drawings must include:

- 1. Outline of roof and size
- 2. Deck type (for multiple deck types)
- 3. Location and type of all penetrations
- 4. Perimeter and penetration details
- 5. Key plan (on multiple roof areas) with roof heights indicated
- 6. Sheet width and number of perimeter sheets for Reinforced Mechanically Fastened systems
- 7. Sure-Seal Fastener type, length and maximum spacing (for membrane securement) for Reinforced Mechanically Fastened systems.
- C. Along with the project submittals (shop drawing and Request for Warranty), the roofing contractor must include pullout test results when the results are below the requirements identified in the Table included in Design Reference DR-06 "Withdrawal Resistance Criteria".

- D. Ballasted projects incorporating a **lightweight insulating concrete** substrate, a **certification letter** is **required** from the lightweight insulating concrete manufacturer for the following conditions:
 - The membrane is specified directly over vermiculite or cellular lightweight insulating concrete with a maximum compressive strength of 140 psi.
 - 2. The membrane is specified with HP Protective Mat as the membrane underlayment over **vermiculite** or **cellular** lightweight insulating concrete with a compressive strength between 140 175 psi.

The certification letter must reference the project name and location, accompany the project submittals (shop drawing and Request for Warranty) and contain the following information pertaining to the lightweight insulating concrete mix design:

- 1. Manufacturer's brand name
- 2. Maximum compressive strength
- 3. Average wet density
- 4. Average air-dry density
- E. When field conditions necessitate modifications to the originally approved shop drawings, a copy of the shop drawing outlining all modifications must be submitted to Carlisle for revision and approval prior to inspection and warranty issuance.
- F. As-Built Projects (roofing systems installed prior to project approval by Carlisle)

The Carlisle Authorized Applicator may supply Carlisle with an As-Built drawing for a project completed prior to Carlisle's approval. The As-Built drawings:

- 1. Must conform to Carlisle's most current published specifications and details applicable at the time of bid.
- 2. Must be submitted along with a completely executed Notice of Completion.
- 3. Must include the items identified in Paragraphs B, C and D above.

Note: As-Built projects are not recommended for those projects referenced in Paragraph A in order to ensure Carlisle warranty requirements have been met.

G. Notice of Completion (Page 2 of the Carlisle Request for Warranty form)

After project completion, a Notice of Completion must be submitted to Carlisle to schedule the necessary inspection and acceptance of the project prior to issuance of the Carlisle warranty.

1.05 Warranty

- A. A Total System Warranty is available for roofing systems on commercial buildings within the United States and applies only to **products manufactured or marketed by Carlisle SynTec**. The total system is defined as membrane, flashings, adhesives, sealants and other Carlisle brand products utilized in the installation. For a complete description of these products, refer to the Part 2 "Products" Section in this Specification and Spec Supplement "Related Products" P-01.
- B. See Tables Below for information regarding Warranted Systems and Design Criteria:
 - TABLE I Non-Reinforced EPDM Membrane Thickness for Various Warranty Options Identifies
 minimum membrane thickness for non-reinforced membranes used in adhered or ballasted roofing systems.
 - TABLE II Reinforced EPDM Membrane Thickness for Various Warranty Options Identifies minimum membrane thickness required for adhered and mechanically fastened assemblies using Reinforced Membrane.
 - TABLE III Mechanically Fastened Roofing Systems Membrane Fastening Criteria Up to 20 YR Warranty - Steel/Concrete Decks Identifies fastening density, field membrane width and number perimeter sheets required for the various wind zones. The assemblies are categorized based on various building height and specific wind speed warranty coverage.
 - 4. TABLE IV Mechanically Fastened Roofing Systems Membrane Fastening Criteria Up to 20 YR Warranty Wood (Plywood & OSB) Decks Identifies fastening density, field membrane width and number perimeter sheets required for the various wind zones. The assemblies are categorized based on various building height and specific wind speed warranty coverage.
 - TABLE V Re-roofing Substrate Criteria Up to 20 YR Warranty Identifies required substrates for reroofing applications for adhered, mechanically fastened and ballasted roofing systems.
 - 6. TABLE VI Adhered Roofing Systems Underlayment Fastening Criteria Up to 20 YR Warranty Identifies required underlayment for adhered roofing systems with Warranties up to 20 year based on the

- various wind speed coverage available. The Table also identifies fastening density or adhesive bead spacing and required edge terminations.
- 7. TABLE VII Adhered Roofing Systems Underlayment Fastening Criteria 25 to 30 YR Warranty Identifies required underlayment for adhered roofing systems with Warranties from 25 to 30 year based on the various wind speed coverage available. The Table also identifies fastening density or adhesive bead spacing and required edge terminations.

Table I Non-Reinforced EPDM Membrane Thickness for Various Warranty Options

The state of the s										
	SURE-SEAL OR SURE-WHITE NON-REINFORCED MEMBRANES - ADHERED									
	Warranty Wind S	peed Coverage	Э		Hail Coverage					
Warranty Duration	55, 72 or 80 mph	55, 72 or 80 mph 90 to 100 mph 110 to 120 mph			*(Cover Board set in Adhesive)					
5,10, or 15 year	٧	V	N/A	60-mil Sure-Seal OR Sure-White 60-mil Sure-Seal SAT OR Sure- White SAT	1" for Adhered*					
20 year	V	V	N/A	60-mil Sure-Seal OR Sure-White 60-mil Sure-Seal SAT OR Sure- White SAT	1" for Adhered*					
25 year (3)	√(1)	√ (1)	N/A	60-mil Sure-Seal OR Sure-White 60-mil Sure-Seal SAT OR Sure- White SAT	1" for Adhered*					
30 year (3)	√(1)	√ (1)	N/A	90-mil Sure-Seal OR Sure-White	2" for Adhered*					
	SURE-SEAL OR SURE	-WHITE NO	N-REINFO	RCED MEMBRANES - BALL	ASTED					
	Warranty Wind S	Speed Coverage	•							
Warranty Duration	55, 72 or	80 mph		Minimum Membrane Thickness	Hail Coverage					
5,10, 15, 20 or 25 year (3)	√ (,	√ (2)		Sure-Seal 45-mil	1" for Ballasted					
5,10, 15 or 20 year				√ (2)		60-mil Sure-Seal OR Sure-White	2" for Ballasted			
25 or 30 year (3)	√ (2)		√ (2)		60-mil Sure-Seal OR Sure-White	2" for Ballasted			
30 year (3)	√ (2)			90-mil Sure-Seal OR Sure-White	3" for Ballasted					

Notes: N/A = Not Acceptable $\sqrt{}$ = Acceptable

⁽¹⁾ Standard 90-8-30A, EPDM x-23 Low-VOC, Low-VOC EPDM/TPO or CAV-GRIP III Bonding Adhesive must be utilized.

⁽²⁾ When Sure-Tough Reinforced membrane is specified, 60-mil membrane minimum is required for warranties for up to 20 year. Projects with 25 / 30 Year Warranty must incorporate 75-mil membrane.

⁽³⁾ See Attachment II '25/30 Year Warranty Design Enhancements' for enhanced design requirements.

Reinforced EPDM Membrane Thickness for Various Warranty Options

		Sure-Tough or Sure-White Reinforced Membranes										
Warranty		Warranty Wind Speed Coverage				Warranty Wind Speed Coverage					Hail Coverage	
Duration	55, 72 o	r 80 mph	90 mph		100 to 1	120 mph	Minimum Membrane Thickness	*(Cover	Puncture Coverage			
	Adhered	Mech. Fastened	Adhered	Mech. Fastened	Adhered	Mech		Board set in Adhesive)	Coverage			
5,10, or 15 year	V	√	√	√	V	N/A	45-mil Sure-Tough	N/A	8 man hours			
20 year	√	√	√	√	V	N/A	60-mil Sure-Tough, 60-mil Sure-White Reinforced, 60-mil Sure-Tough SAT OR 60-mil Sure-White SAT	1" for Adhered*	16 man hours			
25 year (2)	√ (1)	√	√ (1)	√	√ (1)	N/A	75-mil Sure-Tough OR 75-mil Sure- Tough SAT	2" for Adhered*	32 man hours			
30 year (2)	√ (1)	√	√ (1)	√	√ (1)	N/A	75-mil Sure-Tough	2" for Adhered*	32 man hours			

Notes: N/A = Not Acceptable $\sqrt{=}$ Acceptable

- (1) Standard 90-8-30A, EPDM x-23 Low-VOC, Low-VOC EPDM/TPO or CAV-GRIP III Bonding Adhesive must be utilized.
- (2) See Attachment II '25/30 Year Warranty Design Enhancements' for enhanced design requirements.
- (3) Carlisle's Accidental Puncture Warranty covers labor hours and material used during the repair. Maximum labor and material hours are dependent upon system design. Refer to the Warranty Availability Quick Reference Guide for coverage.

Mechanically Fastened Roofing Systems Fastening Criteria Up to 20 YR Warranty (1) 22 GA. Steel, Structural Concrete, Wood Plank, and 3/4" Plywood Decks

Table III

	Min. Number of Perimeter Sheets						
Peak Gust Wind Speed	Max. Building	Buildi	ing Distand Coastline		Field Membrane	Perimeter Sheet	Fastening Density* (Field & Perimeter
Warranty	Height	Greater than 7 miles	3 to 7 miles	Less than 3 miles	Width	Width	Sheets)
	Up to 60'	1	2	3	10'	6.5'	12" O.C.
55 MPH	Op 10 60	_	2	3	8'	6.5'	12" O.C.
35 WIPH	61' to	2	2	3	10'	6.5'	6" O.C.**
	100'	2	2	3	8'	6.5'	12" O.C.
	Lin to GO!	2	2	3	10'	6.5'	12" O.C.
72 MPH	Up to 60'	2	2	3	8'	6.5'	12" O.C.
/2 WIPH	61' to	3	4	4	10'	6.5'	6" O.C.**
	100'	3	4	4	8'	6.5'	12" O.C.
	Lin to COI	2	3	4	10'	5'***	12" O.C.
80 MPH	Up to 60'	3	3	4	8'	5'***	12" O.C.
80 MPH	61' to	2	4	4	10'	5'***	6" O.C.**
	100'	3	4	4	8'	5'***	12" O.C.
	Lin to CCI	2	4	4	10'	5'***	6" O.C.**
00 MDU (4)	Up to 60'	3	4	4	8'	5'***	12" O.C.
90 MPH (1)	61' to	4	5	5	10'	5'***	6" O.C. **
	100'	4	5	5	8'	5'***	12" O.C.

^{*} Using HP Fasteners on Steel Deck, Wood Plank and ¾" Plywood Decks with Polymer Seam Plates

^{**12&}quot; o.c. Spacing can be utilized by using HP-Xtra Fasteners and 2-3/8" Polymer Seam Plates.

^{***}As an option, 9" wide EPDM Pressure Sensitive RUSS can be used beneath the field sheets for perimeter securement.

^{(1) 20} year is the maximum warranty available with peak gust wind speed of 90 MPH. Projects with greater wind speed coverage **MUST** be submitted to Carlisle for review and possible considerations.

EPDM Membrane Fastening Criteria (Up to 20 Year Warranty – Up to 60' Building Height) for Mechanically Fastening Roofing Systems Wood (Plywood or OSB) Decks

TABLE IV

Wood (Plywood or OSB) Decks	Deck Type			ber of Perimo		Field Membrane	Perimeter Sheet	Fastening Density (Field &	
Peak Gust Wind Speed Warranty		Values	Greater than 7 miles	3 to 7 miles	Less than 3 miles	Width	Width	Perimeter Sheets)	
	- 4400 000	210 lbs	2	3	3	10'	5'*	9" O.C.	
	7/16" OSB	210105	2	3	3	8'	5'*	12" O.C.	
55 MPH	15/32" 3-Ply Plywood	240 lbs	2	2	3	8'	5'*	12" O.C.	
55 MPH	15/32" 5-Ply Plywood	530 lbs	1	2	3	10'	6.5'	12" O.C.	
	5/01/ 000	0.40 !!	2	3	3	10'	5'*	12" O.C.	
	5/8" OSB	310 lbs	2	3	3	8'	5'*	12" O.C.	
	15/32" 3-Ply Plywood	240 lbs	2	2	3	8'	5'*	12" O.C.	
TO MPU	15/32" 5-Ply Plywood	530 lbs	2	2	3	10'	6.5'	12" O.C.	
72 MPH	5/01/ 000	040 II.	2	3	3	10'	5'*	12" O.C.	
5/8" OSB	310 lbs	2	3	3	8'	5'*	12" O.C		
80 MPH	Contact Carlisle for Approval and Evaluation								

^{*}Maximum duration for OSB NOT to exceed 20 Years.

Table V Re-roofing Substrate Criteria - Up to 20 YR Warranty

Acceptable Roof Deck/Substrate	EPDM Membrane (See Table I and II for minimum membrane thickness)							
RETROFIT / NO TEAR-OFF	Adhered - Design "A"	Mechanically Fastened						
Existing Smooth Surface BUR or Mineral Surface Cap Sheet	Direct Application	Insulation	Direct Application					
Gravel Surfaced BUR	Insulation	Insulation	Insulation					
Coal Tar Pitch	itch Insulation Insulation		Insulation					
Modified Bitumen	Direct Application	Insulation	Direct Application					
Existing Single-Ply	Insulation	Insulation	Direct Application (1)					
Sprayed-in-place Urethane	Complete Tear-off Required	Insulation	Complete Tear-off Required					

⁽¹⁾ Direct application over existing PVC is not permitted regardless of warranty duration. Carlisle may be contacted for specific substrate

EPDM 7/2025 12

requirement.

NOTE: Projects with Warranties greater than 20 YR require total removal of existing materials. Refer to Table VI and VII for further material requirements.

NOTE: Refer to Roof Deck and Substrate Criteria Table in Part III for additional installation requirements.

Adhered Roofing Systems Underlayment Fastening Criteria Up to 20 YR Warranty

Table VI

Other Requirements are Listed in Additional Design Considerations following this Table

All Carlisle Products listed for higher wind speed coverage can also be used for Warranties for lower speed coverage. (i.e. 72 MPH underlayment may be used for 55 MPH underlayment)

			Underlayment Attachment			
Maximum Peak Gust Wind Speed Warranty	Minimum Membrane Underlayment	# of Fasteners per 4' x 8'	Adhesive Spac for 4' x 4' s	Metal Edging		
		board size	Field	Perimeter		
	1" (20 psi) Polyisocyanurate or 1" (20 psi) Polyisocyanurate Eco	16				
	1-1/2" (20 psi) Polyisocyanurate or 1-1/2" (20 psi) Polyisocyanurate Eco	10			SecurEdge Drip	
55 or 72 MPH	2" (20 psi) Polyisocyanurate Or 2" (20 psi) Polyisocyanurate Eco	8	12" (4)(5)(10)	6" (4)	Edge	
	1/2" SecurShield HD or 1/2" SecurShield HD Eco (1)	12				
	1/4" DensDeck Prime, 1/4" Securock, or 1/4" DEXcell FA VSH TM , 1/4" Securock Ultralight Coated Glass Mat (1)	12				
	1/2" SecurShield HD Plus (1)	8				
	1/2" HP Recovery Board (1)(11)	16				
	1/2" SecurShield HD and 1/2" SecurShield HD Eco (1)	16				
	2" SecurShield HD Composite	6				
80 MPH	1/2" DensDeck Prime, 1/2" Securock (1), or 1/2" DEXcell FA VSH [™] , 1/2" Securock Ultralight Coated Glass-Mat Board	8	12" (4)(5)(6)(10) 6' (4)(6)		SecurEdge Drip Edge (9)	
	1-1/2" Polyisocyanurate (25-psi) Or 1-1/2" (25 psi) Polyisocyanurate Eco	10				
	2" (25 -psi) Polyisocyanurate Or 2" (25 psi) Polyisocyanurate Eco	8				
	or 1/2" DEXcell FA VSH TM , 1/2" Securock Ultralight Coated Glass-Mat (1)	Glass-Mat (1) " SecurShield HD, 1/2" SecurShield HD Eco, or 1-1/2" (20-psi) SecurShield Polyiso or 1 1/2" (20 psi) SecurShield Fee (1)				
	1/2" SecurShield HD, 1/2" SecurShield HD Eco, or 1-1/2" (20-psi) SecurShield Polyiso or 1-1/2" (20-psi) SecurShield Eco (1)			011 (0)(7)	SecurEdge Drip Edge (2)(3) or SecurEdge EX	
90 MPH	1/2" SecurShield HD Plus or 1/2" EcoStorm VSH (1)	12	6" (8)	6" (6)(7)	Drip Edge or	
	2" (20-psi) SecurShield, 2" (20 psi) SecurShield Eco or 2" SecurShield HD Polyiso Composite (1)	8			SecurEdge Snap- On Fascia	
	1-1/2" StormBase (OSB/Polyiso Composite)	8				
	1-1/2" Insulfoam HD Composite	16				
100 MPH	2" (25-psi) SecurShield Polyiso or 2" (25 psi) SecurShield Eco	16	FS	FS	SecurEdge Drip Edge (2)(3) or SecurEdge EX Drip Edge or SecurEdge Snap- On Fascia	
110 MPH	1-1/2" StormBase (OSB/Polyiso Composite) or 1/2" EcoStorm VSH (1)	16	FS	FS	SecurEdge EX Drip Edge or	
	1/2" SecurShield HD Plus (1)				SecurEdge Snap- On Fascia	
	5/8" DensDeck Prime, 5/8" DensDeck StormX Prime, 5/8" Securock or 5/8" Securock Ultralight Coated Glass-Mat (1)	16			SecurEdge EX	
120 MPH	1-1/2" StormBase (OSB/Polyiso Composite) or 1/2" EcoStorm VSH (1)	17	FS	FS	Drip Edge or SecurEdge Snap-	
	1/2" SecurShield HD Plus (1)	24			On Fascia	
	2" SecurShield HD Composite	16				

FS = Full Spray or Ribbons @ 4" O.C.

⁽¹⁾ For Steel Decks, cover boards must be installed over a min. 1" thick approved Carlisle Insulation.

- (2) Carlisle HP or HP-X Fasteners must be used to secure SecurEdge Snap-On Canted Fascia to perimeter wood nailers.
- (3) Membrane securement is required at the base of the SecurEdge Drip Edge waterdam.
- (4) Gravel Surface BUR Field @ 6" O.C. / Perimeter @ 4" O.C.
- (5) Steel Decks Field & Perimeter @ 6" O.C.
- (6) Cementitious Wood Fiber Field @ 6" O.C. / Perimeter @ 4" O.C.
- (7) Smooth BUR Field @ 6" O.C. / Perimeter @ 4" O.C.
- (8) Gravel Surface BUR FS
- (9) May be fastened with ring shank nails staggered 4" on center. Carlisle HP or HP-X Fasteners may also be used fastened 12" on center.
- (10) Gypsum Deck must have a minimum 6" o.c. bead spacing.
- (11) HP Recovery Board cannot exceed 15 YR. warranty for Reroof and No Tear-off projects only.

Table VI - Additional Adhered Design Considerations - Up to 20 YR Warranty

- 1 For Building heights between 51-100', enhance 12'-wide perimeter with 50% more fasteners and plates.
- 2 Building height shall not exceed 100'*
- 3- Acceptable decking: 22-gauge or heavier steel, structural concrete, 1-1/2" wood plank, or 15/32" plywood.**
- 4- See DR-05 for insulation fastening patterns.
- * For projects where building height exceeds 100', please submit to Carlisle for review.
- ** 16 fasteners per 4' x 8' board are required for the following decks: OSB, gypsum, cementitious, wood fiber (Tectum), lightweight insulated concrete over steel roof deck thinner than 22-gauge and steel roof deck thinner than 22-gauge. Warranties are limited to a 20-year, 72-mph wind speed.

Table VII

Underlayment/Insulation & Required Attachment Assemblies Up to 20 YR Warranty for SAT EPDM Adhered Roofing Systems

Other Requirements are Listed in Additional Design Considerations following this Table All Carlisle Products listed for higher wind speed coverage can also be used for Warranties for a lower speed coverage. (i.e. 72 MPH underlayment may be used for 55 MPH underlayment)

Peak		Insu	Insulation Attachment			
Peak Gust Wind Speed Warranty	Minimum Membrane Underlayment	# of Fasteners per 4' x 8' board	1 Spacing for 4 x 4 Size		Metal Edging	
Transanty		size	Field	Perimeter		
	1" (20 psi) Polyisocyanurate Or 1" (20 psi) Polyisocyanurate Eco 1-1/2" (20 psi) Polyisocyanurate	16 10				
	Or 1-1/2" (20 psi) Polyisocyanurate Eco					
55 or 72 MPH	2" (20 psi) Polyisocyanurate Or 2" (20 psi) Polyisocyanurate Eco	8	12" (2)(3)	6" (2)	SecurEdge Drip	
IVIPH	1/2" SecurShield HD or 1/2" SecurShield HD Eco (1)				Edge	
	1/4" DensDeck Prime, 1/4" Securock 1/4" DEXcell FA VSH ^{TM,} 1/4" Securock Ultralight Coated Glass-Mat (1)	12				
	2" (1.25 lb/density) Insulfoam SP*					
	1/2" DensDeck Prime or 1/2" Securock, 1/2" DEXcell FA VSH, Or 1/2" Securock Ultralight Coated Glass-Mat (1)	8				
	1/2" SecurShield HD or 1/2" SecurShield HD Eco (1)	16		12" (3)(4)(10) 6" (2)(4)		
	1/2" SecurShield HD Plus (1)	8	12"			
	2" SecurShield HD Composite	6	(2)(3)(4)(10)		SecurEdge Drip Edge (9)	
80 MPH	1-1/2" (25-psi) Polyisocyanurate Or 1-1/2" (25 psi) Polyisocyanurate Eco	10				
	2" (25 -psi) Polyisocyanurate Or 2" (25 psi) Polyisocyanurate Eco	8				
	2" (1.25 lb/density) Insulfoam SP**	16	6" (2)(3)(4)	6" (2)(4)		
	1-1/2" Insulfoam HD Composite*	12	12"(6)	6"(4)(5)		
	1/2" DensDeck Prime, 1/2" Securock, 1/2" DEXcell FA VSH™ or 1/2" Securock Ultralight Coated Glass-Mat (1)	12				
	1/2" SecurShield HD or 1/2" SecurShield HD Eco (1) 1-1/2" (20-psi) SecurShield Polyiso	16			SecurEdge Drip Edge (7)(8) or	
90 MPH	or 1-1/2" (20-psi) SecurShield Polyiso Eco	40	6" (6)	6" (4)(7)	SecurEdge EX Drip Edge or SecurEdge Snap-On Fascia.	
	1/2" SecurShield HD Plus or 1/2" EcoStorm VSH (1)	12				
	1-1/2" StormBase (OSB/Polyiso Composite) 2" (20-psi) SecurShield Polyiso, 2" (20 psi) SecurShield Eco or 2"	8			опар-оп газов.	
	SecurShield HD Composite	8				
	1-1/2" Insulfoam HD Composite	16				
	5/8" DensDeck Prime, 5/8" DensDeck StormX Prime, 5/8" Securock, 5/8" DEXcell FA VSH [®] , or 5/8" Securock Ultralight Coated Glass-Mat (1)					
	1/2" SecurShield HD Plus (1)				SecurEdge Drip Edge (7)(8) or	
100 MPH	1-1/2" StormBase (OSB/Polyiso Composite) or 1/2" EcoStorm VSH	16	FS	FS	SecurEdge EX Drip Edge or SecurEdge	
	2" (25-psi) SecurShield Polyiso or 2" (25 psi) SecurShield Eco				SecurEdge Snap-On Fascia.	
	2" SecurShield HD Composite					

FS = Full Spray or Ribbons @ 4" O.C.

(1) Cover boards must be installed over a min. 1" thick approved Carlisle Insulation.

- (2) Gravel Surface BUR Field @ 6" O.C. / Perimeter @ 4" O.C.
- (3) Steel Decks Field & Perimeter @ 6" O.C.
- (4) Cementitious Wood Fiber Field @ 6" O.C. / Perimeter @ 4" O.C.
- (5) Smooth BUR Field @ 6" O.C. / Perimeter @ 4" O.C.
- (6) Gravel Surface BUR FS
- (7) Carlisle HP or HP-X Fasteners must be used to secure Carlisle Drip Edge or SecurEdge Snap-On Canted Fascia to perimeter wood nailers.
- (8)Membrane securement is required at the base of the SecurEdge Drip Edge waterdam.
- (9) May be fastened with ring shank nails staggered 4" on center. Carlisle HP or HP-X Fasteners may also be used fastened 12" on center.
- (10) Gypsum deck must have minimum 6" o.c. bead spacing.
- Maximum warranty available 20 year.
- ** Maximum warranty available 15 year

Table VII – Additional Design Considerations (Up to 20 YR Warranty)

- 1 For Building heights between 51-100', enhance 12'-wide perimeter with 50% more fasteners and plates.
- 2 Minimum membrane thickness 60-mil SAT EPDM.
- 3 Building height shall not exceed 100'*
- 4 Acceptable decking: 22-gauge or heavier steel, structural concrete, 1-1/2" wood plank or 15/32" plywood.
- 5 All "T-joints" must be overlaid with appropriate flashing material or Carlisle "T-joint" Covers.
- 6 See DR-05 for insulation fastening patterns.

Table VIII Minimum Perimeter Width for Insulation Attachment for All Warranties

Width of Perimeter	Building Height
4 feet	25 feet
8 feet	26 to 50 feet
12 feet	51 to 75 feet
16 feet	76 to 100 feet
24 feet	Greater than 100 feet

Note: This Table is for reference for Carlisle System Warranties and does not replace FM requirements for FM insured projects.

C. Access for warranty service

It shall be the owner's responsibility to expose the membrane in the event warranty service is required when access is impaired. Such impairment includes, but is not limited to:

- a. Design features, such as window washer systems, which require the installation of traffic surface units in excess of 100 pounds per unit.
- b. Any equipment, ornamentation, building service units and other top surfacing materials, which are not defined as part of this specification.
- c. Photovoltaic and Mounting Systems or other Rooftop equipment which does not provide Carlisle with reasonable access to the membrane system for purposes of warranty investigation and related repairs.
- d. Severely ponded conditions.

CAUTION:

APPLICATIONS SUCH AS WALKING DECKS, TERRACES, PATIOS OR AREAS SUBJECTED TO CONDITIONS NOT TYPICALLY FOUND ON ROOFING SYSTEMS WILL **NOT** BE ELIGIBLE FOR A MEMBRANE SYSTEM WARRANTY. CARLISLE MAY BE CONTACTED FOR OTHER AVAILABLE OPTIONS.

^{*} Projects where building height exceeds 100' or warranty wind speed exceeds 100 mph, shall be submitted to Carlisle for review.

D. The formation or presence of mold or fungi in a building is dependent upon a broad range of factors including, but not limited to, the presence of spores and nutrient sources, moisture, temperatures, climatic conditions, relative humidity, and heating/ventilating systems and their maintenance and operating capabilities. These factors are beyond the control of Carlisle and Carlisle shall not be responsible for any claims, repairs, restoration or damages relating to the presence of any irritants, contaminants, vapors, fumes, molds, fungi, bacteria, spores, mycotoxins, or the like in any building or in the air, land, or water serving the building.

1.06 Job Conditions

- A. On phased roofing, temporary closures should be provided to prevent moisture infiltration. When a temporary roof is specified, Carlisle 725TR in conjunction with CCW-702, CCW-702 LV or CAV-GRIP III Primer may be used. Refer to Product Section Part II for additional product information and Spec Supplement G-08 "Application Procedures for 725TR Air and Vapor Barrier".
- B. When possible, on multiple level roofs, begin the installation on the highest level to avoid or minimize construction traffic on completed roof sections.
- C. On projects at high altitudes (6,000' and above) rapid flash-off (drying) of Bonding Adhesive and Primers will occur due to low atmospheric pressure.

D. Vapor Retarders

- 1. Carlisle does not require a vapor retarder for the protection of the membrane; however, it should be considered by the specifier for the protection of the roofing assembly (i.e. primarily insulation, underlayment and adhesives). The following criteria should be considered by the specifier:
 - a. Use of a vapor retarder to protect insulation and reduce moisture accumulation within an insulated roofing assembly, should be investigated by the specifier. Consult latest publications by ASHRAE (American Society of Heating, Refrigerating and Air-Conditioning Engineers, Inc.) and NRCA (National Roofing Contractors Association) for specific information.
 - b. In the generally temperate climate of the United States, during the winter months, water vapor flows upward from a heated, more humid interior toward a colder, drier exterior. Vapor retarders are more commonly required in northern climates than in southern regions, where downward vapor pressure may be expected and the roofing membrane itself becomes the vapor retarder.
 - c. On cold storage/freezer facilities, the perimeter and penetration details must be selected to provide an air seal and prevent outside air from infiltrating and condensing within the roofing assembly.
- When a vapor retarder is specified, Carlisle VapAir Seal 725TR or VapAir Seal MD Air and Vapor Barrier may be used. Refer to Part II "Products" for necessary information and Spec Supplement G-08 "Application Procedures for 725TR Air and Vapor Barrier" for product Installation.
- E. Wood nailers are required for the securement of metal edgings, deck-level scuppers, and insulated pipes. Treated or non-treated wood nailer may be specified and shall be secured per specifier recommendation or in accordance with Factory Mutual's property Loss Prevention Data Sheet 1-49. Refer to Design Reference DR-08 "Wood Nailers and Securement Criteria" in Carlisle Technical Manual shall be referenced.
- F. For Adhered or Mechanically Fastened systems specified over existing standing seam, flat seam or corrugated metal roofs, refer to the Carlisle's Metal Retrofit Roofing System Specification in the Carlisle Technical Manual for specific installation requirements.
- G. When any of the EPDM Roofing Systems are specified on a portion of a roof, tie-ins to existing roofing membranes will be required. Depending on the type of the existing roofing system, the tie-in method will vary. Total isolation between two roofing systems or weep holes may be required to address moisture migration from one roofing system to the other. Prior to the selection of any tie-in detail, ensure the selected detail will not restrict drainage.

1.07 Product Delivery, Storage and Handling

- A. Deliver materials to the job site in original, unopened containers.
- B. When loading materials onto the roof, the Carlisle Authorized Roofing Applicator must comply with the requirements of the specifier/owner to prevent overloading and possible disturbance to the building structure.
- C. Job site storage temperatures in excess of 90°F (32°C) may affect shelf life of curable materials (i.e., uncured flashing, adhesives, sealants, primers, SecurTAPE and Pressure-Sensitive Flashing/Accessories).

D. When the temperature is expected to fall below 40° F (4°C), outside storage boxes should be provided on the roof for temporary storage of liquid adhesives, sealants, primers, SecurTAPE and Pressure-Sensitive Flashing/Accessories. Containers must be rotated to maintain their temperature above 40°F (4°C). Refer to Product Data Sheets for individual products for temperature restrictions.

Note: Prolonged exposure of Pressure-Sensitive Flashing and SecurTAPE to temperatures below 40° F (4°C) will cause the pre-applied adhesive tape to lose tack and in extreme cases, not bond to the substrate. Refer to Spec Supplement E-02 "EPDM Membrane Splicing and Splice Repairs" in Carlisle Technical Manual for application procedures in colder temperatures.

- E. Do not store adhesive containers with opened lids due to the loss of solvent, which will occur from flash-off.
- F. Insulation/underlayment must be stored so it is kept dry and is protected from the elements. Store insulation on a skid and completely cover with a breathable material such as tarp or canvas. If the insulation is lightweight, it should be weighted to prevent possible wind damage.

Part II- PRODUCTS

2.01 General

The components of this roofing system are to be products of Carlisle or accepted by Carlisle as compatible. The installation, performance or integrity of products by others, **when selected by the specifier and accepted by Carlisle**, is not the responsibility of Carlisle and is expressly disclaimed by the Carlisle warranty.

2.02 Membrane

A. Sure-Seal/Sure-White Non-Reinforced EPDM Membranes

1. Cured non-reinforced EPDM (Ethylene, Propylene, Diene Terpolymer) compounded elastomer.

45-mil thick (black membrane only), 60-mil thick (black, gray or white), or 90-mil thick (black or white). Non-reinforced EPDM membrane is available in **Sure-Seal (black), Sure-Seal (gray)** or **Sure-White (white)**. Sure-Seal Gray is only available in 60-mil. Sure-White membranes are installed with the white surface facing up. Sure-Seal (black) membrane with thickness up to 60-mil can be available in widths up to 50' and lengths up to 150' (200' for 45-mil membrane only). Sure-White membrane with thickness of 60-mil is available up to 20' widths and lengths up to 150' long. Sure-Seal / Sure-White 90-mil membranes and Sure-Seal Gray 60-mil membranes are available in widths up to 10' and lengths up to 100'. Membrane conforms to ASTM D4637, Type I (non-reinforced) and to ASTM E2178 as an air barrier.

- 2. **Sure-Seal KLEEN (black) EPDM Membrane** (mica dust has been removed during manufacturing) is available for sheets maximum 10' wide.
- 3. Sure-Seal Gray Non-Reinforced EPDM Membrane is available with and without FAT.
- 4. Refer to the physical properties listed on the following pages.

B. Sure-Tough Reinforced EPDM Membranes

 Cured reinforced EPDM (Ethylene, Propylene, Diene Terpolymer) compounded elastomer. Sure-Tough Reinforced EPDM Membrane is only available in black.

45, **60**, **or 75-mil thick Sure-Tough Reinforced EPDM membrane** is available in sizes referenced in Table below. Reinforced membrane with polyester fabric conforms to ASTM D4637, Type II (reinforced) and ASTM E2178 as an air barrier.

Sure-Tough Reinforced Membrane Size Availability*									
Membrane Thickness	Sheet Sizes								
45-mil	5' or 6.5' x 100'	10' x 50' or 100'							
60-mil	5' or 6.5' x 100' 5' x 200'	8' x 100'	10' x 50' or 100'						
75-mil	-	-	10' x 50' or 100'						

^{*}Contact Carlisle for other custom sizes available.

- 2. **60-mil thick Sure-White Reinforced EPDM** membrane is available in a 10' x 100' sheet size.
- 3. Refer to the physical properties listed on the following pages:

45, 60 and 90-MIL THICK NON-REINFORCED EPDM MEMBRANE STANDARD AND FIRE RETARDANT (FR)

45-mil thick Sure-Seal (standard) non-reinforced EPDM membrane is used only for Sure-Seal Design "B" Loose Laid Ballasted Roofing Systems.

60 or 90-mil thick Sure-Seal FR (black) or Sure-White (white on black) and 60-mil thick Sure-Seal (gray) non-reinforced EPDM membrane is used primarily for Adhered Roofing Systems. Membranes can also be used for ballasted and protected membrane assemblies.

Note: Although 60-mil thick Non-Reinforced EPDM is recommended for Adhered Roofing Systems, 45-mil thick FR Non-Reinforced EPDM may be utilized, if specified.

SURE-SEAL(Black and Gr	ay) / SURE-	-WHITE (WI	nite) NON-F	REINFORCE	D MEMBR	ANES
	•	-		Тур	oical	
	Test	ASTM	45-mil	60-mil	60-mil	90-mil
Physical Property	Method	SPEC. (Pass)	Standard	FR	White & Gray	Sure-Seal FR / Sure- White
Tolerance on Nominal Thickness, %	ASTM D 412	±10	±10	±10	±10	±10
Weight, lb/ft² (kg/m²)			0.26 (1.3)	0.35 (1.7)	0.39 (1.9)	0.59 (2.9)**
Tensile Strength, min, psi (MPa)	ASTM D 412	1305 (9)	1600 (11)	1600 (11)	1600 (11)	1600 (11)
Elongation, Ultimate, min, %	ASTM D 412	300	480	465	540	540
Tear Resistance, min, lbf/in (kN/m)	ASTM D 624 (Die C)	150 (26.3)	200 (35.0)	200 (35.0)	200 (35.0)	200 (35.0)
Factory Seam Strength, min.	Modified ASTM D 816	Membrane Rupture	Membrane Rupture	Membrane Rupture	Membrane Rupture	Membrane Rupture
Resistance to Heat Aging* Properties after 4 weeks @ 240°F (116°C)	ASTM D 573					
Tensile Strength, min, psi (MPa)	ASTM D 412	1205 (8.3)	1500 (10.3)	1450 (10.0)	1345 (9.3)	1450 (10.0)
Elongation, Ultimate, min, %	ASTM D 412	200	225	280	280	280
Tear Resistance, min, lbf/in (kN/m)	ASTM D 624 ASTM D	125 (21.9)	215 (37.6)	215 (37.6)	185 (32.4)	215 (37.6)
Linear Dimensional Change, max, %	1204	±1.0	-0.4	-0.5	-0.2	-0.5
Ozone Resistance* Condition after exposure to 100 pphm Ozone in air for 168 hours @ 104°F (40°C) Specimen is at 50% strain	ASTM D 1149	No Cracks	No Cracks	No Cracks	No Cracks	No Cracks
Brittleness Temp., max, deg. F (deg. C)*	ASTM D 746	-49 (-45)	-49 (-45)	-49 (-45)	-67 (-55)	-49 (-45)
Resistance to Water Absorption* After 7 days immersion @ 158°F (70°C) Change in mass, max, %	ASTM D 471	+8.0, -2.0	[+2]	[+2]	[+3.3]	[+2.0]
Water Vapor Permeance* max, perm	ASTM E 96 (Proc. B or BW)	0.1	0.05	0.03	0.02	0.03
Resistance to Outdoor (Ultraviolet) Weathering* Xenon-Arc, total radiant exposure at .70 W/m² irradiance, 176°F (80° C) black panel temp.	ASTM D 4637 Conditions	No Cracks No Crazing @ 7560 kJ/m²	No Cracks No Crazing @ 41580 kJ/m²	No Cracks No Crazing @ 41580 kJ/m²	No Cracks No Crazing @ 25200 kJ/m²	No Cracks No Crazing @ 41580 kJ/m²(black) 25200 kJ/m²(white)

^{*} Not a Quality Control Test due to the time required for the test or the complexity of the test. However, all tests are run on a statistical basis to ensure overall long-term performance of the sheeting.

^{**} Sure-White 90-mil Membrane Weight in lb/ft2(kg/m2) is equal to 0.60 (2.9)

45, 60, or 75-MIL THICK REINFORCED EPDM MEMBRANE

The membrane is used for Adhered or Mechanically Fastened Roofing Systems

Sure-Tough membranes are formulated with fire retardants to inhibit spread of flame and meets or exceeds UL Class A requirements for slopes up to 3", depending on the assembly.

SURE-TOUGH REINFORCED MEMBRANES									
		ASTM		Typical					
Physical Property	Test Method	SPEC. (Pass)	45-mil	60-mil	75-mil				
Tolerance on Nominal Thickness, %	ASTM D 751	±10	±10	±10	±10				
Weight, lb/ft² (kg/m²)			0.27 (1.3)	0.39 (1.9)	0.48 (2.3)				
Thickness Over Scrim, min. in.(mm)	ASTM D 4637 Annex	0.015 (.381)	0.016 (.406)	0.020 (.508)	0.032 (0.81)				
Breaking Strength, min, lbf (N)	ASTM D 751 Grab Method	90 (400)	140 (623)	140(623)	177(787)				
Elongation, Ultimate, min, %	ASTM D 751 Grab Method	250 **	480**	480**	500**				
Tear Strength, min, lbf (N)	ASTM D 751 B Tongue Tear	10 (45)	70 (311)	70 (311)	70 (311)				
Brittleness Temp., max. deg. F (deg. C)*	ASTM D 2137	[-49] (-45)	[-49] (-45)	[-49] (-45)	[-49] (-45)				
Resistance to Heat Aging* Properties after 4 weeks @ 240°F	ASTM D 573								
Breaking Strength, min, lbf (N)	ASTM D 751	80 (355)	182 (823)	182 (823)	182 (823)				
Elongation, Ultimate, min, %	ASTM D 751	200**	250**	250**	250**				
Linear Dimensional Change, max, %	ASTM D 1204	±1.0	-1.0	-1.0	-1.0				
Ozone Resistance* Condition after exposure to 100 pphm Ozone in air for 168 hours @ 104°F (40°C) Specimen wrapped around 3" mandrel	ASTM D 1149	No Cracks	No Cracks	No Cracks	No Cracks				
Resistance to Water Absorption* After 7 days immersion @ 158°F (70°C) Change in mass, max, %	ASTM D 471	+8.0, -2.0	[+5.5**]	[+5.5**]	[+5.5**]				
Factory Seam Strength, min.	Modified ASTM D 816	Membrane Rupture	Membrane Rupture	Membrane Rupture	Membrane Rupture				
Resistance to Outdoor (Ultraviolet) Weathering* Xenon-Arc, total radiant exposure at .70 W/m² irradiance, 176°F (80° C) black panel temp.	ASTM D 4637 Conditions	No Cracks No Crazing @ 7560 kJ/m²	No Cracks No Crazing @ 35320 kJ/m²	No Cracks No Crazing @ 35320 kJ/m²	No Cracks No Crazing @ 35320 kJ/m ²				

^{*} Not a Quality Control Test due to the time required for the test or the complexity of the test. However, all tests are run on a statistical basis to ensure overall long-term performance of the sheeting.

EPDM 7/2025 21

^{**} Specimens to be prepared from coating rubber compound, vulcanized in a similar method to the reinforced product.

60-MIL THICK REINFORCED EPDM MEMBRANE

The membrane is used for Mechanically Fastened or Adhered Roofing Systems.

Sure-Tough membranes are formulated with fire retardants to inhibit spread of flame and meets or exceeds UL Class A requirements for slopes up to 2", depending on the assembly.

SURE-WHITE REINFORCED MEMBRANE						
Physical Property	Test Method	ASTM SPEC.	Typical			
		(Pass)	60-mil			
Tolerance on Nominal Thickness, %	ASTM D 751	±10	±10			
Weight, lb/ft² (kg/m²)			0.40 (2.0)			
Thickness Over Scrim, min. in.(mm)	ASTM D 4637 Annex	0.015 (.381)	0.025 (.635)			
Breaking Strength, min, lbf (N)	ASTM D 751 Grab Method (1)	90 (400)	225(996)			
Elongation, Ultimate, min, %	ASTM D 751 Grab Method	250 **	480**			
Tear Strength, min, lbf (N)	ASTM D 751 B Tongue Tear	10 (45)	70 (311)			
Brittleness Temp., max. deg. F (deg. C)*	ASTM D 2137	[-49] (-45)	[-49] (-45)			
Resistance to Heat Aging* Properties after 4 weeks @ 240°F	ASTM D 573					
Breaking Strength, min, lbf (N)	ASTM D 751	80 (355)	250 (1,110)			
Elongation, Ultimate, min, %	ASTM D 412	200**	250**			
Linear Dimensional Change, max, %	ASTM D 1204	±1.0	-1.0			
Ozone Resistance* Condition after exposure to 100 pphm Ozone in air for 168 hours @ 104°F (40°C) Specimen wrapped around 3" mandrel	ASTM D 1149	No Cracks	No Cracks			
Resistance to Water Absorption* After 7 days immersion @ 158°F (70°C) Change in mass, max, %	ASTM D 471	+8.0, -2.0	5.2**			
Water Vapor Permeance* Max. perms	ASTM E 96 (Proc. B or BW)	0.10	0.02			
Fungi Resistance	ASTM G 21	N/A	0 (No Growth)			
Specular Gloss at 85°C	ASTM D523	N/A	3			
Resistance to Outdoor (Ultraviolet) Weathering* Xenon-Arc, total radiant exposure at .70 W/m² irradiance, 176°F (80° C) black panel temp.	ASTM G 155	No Cracks No Crazing @ 2,520 kJ/m² 1,000 hrs.	No Cracks No Crazing @ 25,200 kJ/m² 10,000 hrs.			
At 0.35 W/m² irradiance, 80°C black panel temperature		2,000 hrs.	20,000 hrs.			

^{*} Not a Quality Control Test due to the time required for the test or the complexity of the test. However, all tests are run on a statistical basis to ensure overall long-term performance of the sheeting.

^{**} Specimens to be prepared from coating rubber compound, vulcanized in a similar method to the reinforced product.

2.03 Insulations/Underlayments

A. General

- 1. Roof insulation thickness must be determined by the thermal value required for each project and may be subject to code approval limitations. On projects where a vapor retarder is used, the specifier must calculate insulation thickness to ensure the temperature at the vapor retarder will not fall below the calculated dew point.
- 2. Multiple layers of insulation are recommended with all joints staggered between layers.
- 3. For minimum recommended R-Values, previously published by American Society of Heating and Air-Conditioning Engineers (ASHRAE), consult local building code official for applicable requirements.
- For Insulation fastening pattern and densities refer to Carlisle Applicable Details and Design Reference DR-05
 "Insulation Fastening Patterns".
- 5. Carlisle Insulation/underlayment must be specified for all Total System Warranty projects or when the insulation is to be covered by the Carlisle Warranty. Any of the Carlisle Insulation/Underlayment may be specified subject to design restrictions included with each table.

B. Carlisle Polyisocyanurate

Table B1 Polyisocyanurate (See below for product descriptions)						
	Minimouna		Roofing System Acceptability			
Insulations / Underlayment	Minimum Thickness	ASTM	Adhered	Mechanically Fastened	Ballasted	
Carlisle InsulBase Polyisocyanurate, Carlisle InsulBase Eco	*1.5"	C1289, Type II, Class 1, Grade 2 or 3	√	√	√	
Carlisle InsulBase NH Polyisocyanurate	*1.5"	C1289, Type II, Class 1, Grade 2 or 3	√	√	√	
Carlisle SecurShield Polyisocyanurate, Carlisle SecurShield Eco	*1.5"	C1289, Type II, Class 2, Grade 2 or 3	√	√	√	
Carlisle SecurShield NH Polyisocyanurate	*1.5"	C1289, Type II, Class 2, Grade 2 or 3	√	√	√	
Carlisle SecurShield HD Composite Polyisocyanurate (SS HD)	2"	C1289, Type IV, Grade 2 or 3	√	V	N/A	
Carlisle StormBase Composite (OSB)	1.5"	C1289, Type V, Grade 2 or 3			N/A	
Design Restrictions						

- Extended Warranty, those with longer duration, higher wind speed, or puncture coverage, may require the use of a cover board over Polviso Insulation, refer to Warranty Tables in Paragraph 1.04 for applicable requirements.
- Maximum Flute Spanability shall be limited to 2-5/8" when 1" Minimum Polyiso Insulation is to be used.
- Minimum thickness of insulation board may be restricted by wind speed coverage and warranty duration, refer to Tables V and VI in Paragraph 1.05.
- The use of HD Polyiso Composite roof insulation is not recommended for Ballasted Applications.

Notes: N/A = Not Acceptable $\sqrt{\ }$ = Acceptable

SecurShield HD is listed in Paragraph E4 below.

^{*1.5&}quot; minimum for adhered systems. 1" minimum for mechanically fastened systems or as a base layer for adhered.

- a. Carlisle InsulBase Polyisocyanurate A foam core insulation board covered on both sides with a medium weight fiber-reinforced felt facer meeting ASTM C 1289, Type II, Class 1, Grade 2 (20 psi) or Grade 3 (25 psi). The product is available in 4' x 8' standard size with a thickness from 1 to 4 inches. 4' x 4' tapered panels are also available.
- b. **Carlisle InsulBase Eco** A rigid roof insulation panel with 5% ISCC-certified bio-attributed content composed of a closed-cell polyisocyanurate foam core bonded to glass-reinforced felt (GRF) facers, meeting ASTM C 1289, Type II, Class 1, Grade 2 (20 psi) or Grade 3 (25 psi). The product is available in 4' x 8' standard size with a thickness from 1 to 4 inches. 4' x 4' tapered panels are also available. UL and FM approved for direct application over steel decks, Polyiso provides the highest R-value per inch of any commercially available insulation product.
- c. Carlisle InsulBase NH Polyisocyanurate A foam core insulation board covered on both sides with a glass-reinforced felt meeting ASTM C 1289, Type II, Class 1, Grade 2 (20 psi) or Grade 3 (25 psi). The product is available in 4' x 4' and 4' x 8' standard size with a thickness from ½" to 4 inches. InsulBase NH contains zero halogenated flame retardants.
- d. Carlisle SecurShield Polyisocyanurate— A foam core insulation board covered on both sides with a coated glass fiber mat facer meeting ASTM C 1289, Type II, Class 2, Grade 2 (20 psi) or Grade 3 (25 psi). The product is available in 4' x 8' standard size with a thickness from 1 to 4 inches. 4' x 4' tapered panels are also available. These flat board products feature a dark-colored coated-glass facer (CGF) on one side of the insulation board and a light-colored CGF on the other, labeled Ready Flash. Ready Flash Technology allows applicators to manage adhesive flash-off times by choosing between two different-colored facers on every board.
- e. Carlisle SecurShield Eco A rigid roof insulation panel with 5% ISCC-certified bio-attributed content composed of a closed-cell polyisocyanurate foam core bonded to high performance coated glass facers (CGF). ASTM C 1289, Type II, Class 2, Grade 2 (20 psi) or Grade 3 (25 psi), available in 4' x 8' standard size with a thickness from 1 to 4 inches. 4' x 4' tapered panels are also available. Ideal for use in adhered membrane systems. Achieves a UL Class A fire rating direct to combustible deck.
- f. Carlisle SecurShield NH Polyisocyanurate A foam core insulation board covered on both sides with a coated glass fiber mat facer meeting ASTM C 1289, Type II, Class 2, Grade 2 (20 psi) or Grade 3 (25 psi). The product is available in 4' x 4' and 4' x 8' standard size with a thickness from ½ inch to 4 inches. SecurShield NH contains zero halogenated flame retardants.
- g. Carlisle SecurShield HD Composite Polyisocyanurate Composite insulation panel comprised of 1/2-inch high-density (109 psi max) Polyiso cover board laminated during the manufacturing process to SecurShield rigid Polyiso roof insulation meeting ASTM C1289 Type IV, Grade 2 (20 psi) or Grade 3 (25 psi). Available in 4' x 8' boards with thickness from 2" to 4.5". 4' x 4' panels are also available.
- h. Carlisle StormBase Polyisocyanurate Composite (OSB) Polyiso insulation bonded on the bottom side with a medium weight fiber-reinforced felt facer and laminated with a top surface of 7/16" or 5/8" thick Oriented Strand Board (OSB) meeting ASTM C1289, Type V, Grade 2 (20 psi) or Grade 3 (25 psi). Available in 4' x 8' boards with thickness from 1-1/2" to 4".

C. EPS: Expanded Polystyrene

Table C1 EPS: Expanded Polystyrene (See below for product descriptions)						
	Minimum		Roofing System Acceptability			
Insulations / Underlayment	Thickness	ASTM	Adhered	Mechanically Fastened	Ballasted	
InsulFoam I	1"	C578 Type I	N/A	N/A	V	
InsulFoam VIII	.75"	C578 Type VIII	N/A	N/A	√	
InsulFoam II	.75"	C578 Type II	N/A	N/A	$\sqrt{}$	
InsulFoam IX	.75"	C578 Type IX	N/A	N/A	√	
InsulFoam HD Composite (SecurShield HD)	1.5"	C578 Type (I, VIII, II, or IX)	√	√	N/A	
InsulLam (Various Cover Boards)	1.5"	C578 Type (I, VIII, II. or IX)	V	N/A	N/A	
InsulFoam SP	1"	C578 Type VIII	√(1)	√ ·		
Design Restrictions						

 Local Codes must be consulted regarding the acceptance of expanded insulation directly over steel decks. When specified, minimum thickness shall be designated by the manufacturer.

- Expanded polystyrene roof insulations cannot be installed directly over coal-tar pitch roof surfaces or existing PVC membranes. A separation layer of minimum 1/2" SecurShield HD, HP Recovery Board or Polyiso Insulation shall be used.

- (1) Adhered assemblies using Sure-Seal SAT or Sure-Tough SAT.

Notes: N/A = Not Acceptable $\sqrt{ = Acceptable}$

R-Tech Fanfold Recover Board is listed in Paragraph E4 below.

- 1. **InsulFoam I** A closed-cell lightweight expanded polystyrene (EPS) that meets ASTM C578, Type I. Nominal density of 1.0 lbs/cubic ft (pcf) available in 4' x 4' or 4' x 8' sizes with thickness from 1/4" to 40". Custom lengths, widths and tapered boards are available. May be specified beneath Sure-Seal HP Recovery Board, DensDeck Prime, DensDeck StormX Prime, Securock, or DEXcell[®].
- InsulFoam VIII A closed-cell lightweight expanded polystyrene (EPS) that meets ASTM C578, Type VIII.
 Nominal density of 1.25 lbs/cubic ft (pcf) available in 4' x 4' or 4' x 8' sizes with thickness from 1/4" to 40". Custom lengths, widths and tapered boards are available. May be specified beneath Sure-Seal HP Recovery Board, DensDeck Prime, DensDeck StormX Prime, Securock or DEXcell®.
- 3. **InsulFoam II –** A closed-cell lightweight expanded polystyrene (EPS) that meets ASTM C578, Type II. Nominal density of 1.5 lbs/cubic ft (pcf) available in 4' x 4' or 4' x 8' sizes with thickness from 1/4" to 40". Custom lengths, widths and tapered boards are available. May be specified beneath Sure-Seal HP Recovery Board, DensDeck Prime, DensDeck StormX Prime, Securock or DEXcell®.
- 4. **InsulFoam IX –** A closed-cell lightweight expanded polystyrene (EPS) that meets ASTM C578, Type IX. Nominal density of 2.0 lbs/cubic ft (pcf) available in 4' x 4' or 4' x 8' sizes with thickness from 1/4" to 40". Custom lengths, widths and tapered boards are available. May be specified beneath Sure-Seal HP Recovery Board, DensDeck Prime, DensDeck StormX Prime, Securock or DEXcell®.
- 5. **InsulFoam HD Composite** InsulFoam expanded polystyrene (EPS) insulation laminated with a top surface of 1/2" thick SecurShield HD. Available in 4' x 8' boards with thickness from 1-1/2" to 7".
- 6. **InsulLam –** InsulFoam expanded polystyrene (EPS) insulation laminated with a top surface of 7/16" or 5/8" thick Oriented Strand Board. Available in 4' x 8' boards with thickness from 1-1/2" to 7".
- 7. **InsulFoam SP –** A closed-cell lightweight expanded polystyrene (EPS) with a factory-laminated fiber glass facer. Nominal density of 1.25 lbs/cubic ft (pcf), and meets ASTM C578, Type VIII. Designed for low-sloped roof applications that employ mechanically fastened or ballasted membranes. Can also be used in Adhered systems using Sure-Seal or Sure-Tough SAT Membranes.
- D. **XPS: Extruded Polystyrene** Available through Carlisle is dimensionally stable with high thermal and low water absorption performance capability. XPS is available in varying compressive strengths thicknesses and sizes. Refer to specific product data sheets for physical properties and additional technical information.

Table D1 XPS: Extruded Polystyrene (See below for product descriptions)					
	Minimo	lin in the same		ng System Accep	otability
Insulations / Underlayment	Minimum Thickness	ASTM	Adhered	Mechanically Fastened	Ballasted
Thermapink 18	.75"	Refer to Product Data Sheet	N/A	N/A	$\sqrt{}$
Thermapink 25	1"	Refer to Product Data Sheet	N/A	N/A	$\sqrt{}$
Foamular 400	1"	Refer to Product Data Sheet	N/A	N/A	V
Dow Styrofoam Deckmate Plus	1"	Refer to Product Data Sheet	N/A	N/A	V

Design Restrictions

- Local Codes must be consulted regarding the acceptance of expanded insulation directly over steel decks. When specified, minimum thickness shall be designated by the manufacturer.
- Expanded polystyrene roof insulations cannot be installed directly over coal-tar pitch roof surfaces or existing PVC membranes. A
- separation layer of minimum 1/2" SecurShield HD, HP Recovery Board or Polyiso Insulation shall be used.

 Refer to related products listed in Spec Supplement P-01 "Related Products" for other products which may be suitable for use. Carlisle must be contacted for specific requirements.

 $\sqrt{}$ = Acceptable Notes: N/A = Not Acceptable

- 1. Thermapink 18 or 25 Extruded Polystyrene
- 2. Foamular 400 Extruded Polystyrene
- 3. Dow Styrofoam Deckmate Plus Extruded Polystyrene

E. Carlisle Vacuum Insulated Panel (VIP)

Table E1 Vacuum Insulated Panel (VIP) (See below for product descriptions)						
Minimum		ASTM	Roofing System Acceptability			
Insulations / Underlayment	Thickness	ASTM	Adhered	Mechanically Fastened		
Carlisle Optim-R VIP	*1.6"	C1484	√	N/A		
Design Restrictions						
*2.6" minimum for total installed system including an additional 2 layers of 1/2" SecurShield HD panels; 1 layer on top and 1 layer on bottom of Optim-R. For adhered systems only. Note: Optim-R VIP cannot be cut or punctured.						
Notes: N/A = Not Acceptable	√ = Acceptable					

1. Optim-R Vacuum Insulated Panel (VIP) - a high R-Value vacuum insulated panel (VIP) used to provide a low-profile solution when height restrictions exist, such as windows, doors, equipment curbs, etc. Provides an R-38 insulating value in a 2.6" system thickness with up to 35% infill (non-VIP material). Available in 23.6" x 23.6" and 23.6" x 47.2" board sizes.

F. Cover Boards / Slip Sheets

EPDM 7/2025 26

Table F1 Cover Boards (See below for product descriptions)						
	NA::		Roofing System Acceptability			
Insulations / Underlayment	Minimum Thickness	ASTM	Adhered	Mechanically Fastened	Ballasted	
SecurShield HD, SecurShield HD Eco	.5"	C1289-06, Type II, Class 4 (109 psi max)	√	V	N/A(2)	
SecurShield HD Plus	.5"	C1289-06, Type II, Class 4 (109 psi max)	√	V	N/A(2)	
InsulBase HD, InsulBase HD Eco	.5"	C1289-06, Type II, Class 1, Grade 3	C1289-06, Type II, Class 1,		N/A	
Securock Cover Board	.25"	Refer to Product Data Sheet	√	V	N/A	
EcoStorm VSH	.5"	Refer to Product Data Sheet	√	V	N/A	
HP Recovery Board	.5"	C208 Grade 2	√	V	V	
DensDeck StormX Prime	.625"	C1177	$\sqrt{}$	√ (1)	N/A	
DensDeck Prime	.25"	C1177	√	√ (1)	N/A	
DensDeck	.25"	C1177	N/A	√ (1)	N/A	
R-Tech Fanfold Recovery Board	.5"	C578 Type (I, VIII, II. or IX)	N/A	$\sqrt{}$	$\sqrt{}$	
HP Protection Mat	6 oz	Refer to Product Data Sheets	N/A	$\sqrt{}$	\checkmark	
DEXcell Glass Mat [®]	.5"	C1177		V	N/A	
DEXcell FA [™]	.5"	C1177		V	N/A	
DEXcell [®] Cement Roof Board	.4375"	C1325	V	V	N/A	
DEXcell FA VSH [®]	.625"	C1177	√	√ (1)	N/A	
Design Restrictions						

- HP Recovery Board and R-Tech Fanfold not recommended for direct use over Type B and F steel decks.
- Securock Cover Board, HP Recovery Board, DensDeck Prime, DensDeck StormX Prime, DensDeck or DEXcell® may not be used directly over New or Existing Lightweight Insulating Concrete Decks OR Structural Concrete.
- Due to some warranty restrictions, DensDeck Prime, DensDeck StormX PrimeDensDeck and DEXcell® are not recommended for use directly over existing roofing membrane without prior written approval from Carlisle. Contact Carlisle for specific requirements.
- R-Tech Fanfold primarily for use in existing roof re-covers applications or directly over structural or lightweight insulating concrete.
- HP Protection Mat may be used for Ballasted systems over Lightweight Insulating Concrete with a Maximum Warranty duration of up to 15 years. To be used for Mechanically fastened on new construction projects with Lightweight Insulating Concrete, Fiber Cement or Gypsum Deck a Maximum Warranty duration of up to 15 years.
- (1) Permitted with roofs with slopes greater than 2" per foot for compliance with external fire codes, refer to UL listings or contact Carlisle.
- (2) Acceptable for some roof system designs, Contact Carlisle for recommendations.

Notes: N/A = Not Acceptable $\sqrt{\ }$ = Acceptable

1. **SecurShield HD** - a rigid insulation panel composed of a high-density (109 psi max), closed-cell polyisocyanurate foam core laminated to coated-glass fiber-mat facer meeting ASTM C1289, Type II, Class 4, Grade 1, for use as a cover board or recover board. Available 1/2" thick 4' x 4' (5.5 lbs) and 4' x 8' (11 lbs) panels with an R-value of 2.5.

Features Ready Flash, a dark-colored coated-glass facer (CGF) on one side of the insulation board and a light-colored CGF on the other. Ready Flash Technology allows applicators to manage adhesive flash-off times by choosing between two different colored facers on every board.

- 2. **SecurShield HD Eco** A rigid roof insulation panel with 5% ISCC-certified bio-attributed content composed of ½" high-density, closed-cell polyisocyanurate foam core bonded to a premium performance coated glass facer (CGF) specifically designed for use as a cover board, meeting ASTM C1289, Type II, Class 4, Grade 1. Provides 5 times the R-value at one-fifth the weight of traditional gypsum cover boards. Achieves a UL Class A fire rating direct to combustible deck. Available in 1/2" thick, 4' x 4' (5.5 lbs) and 4' x 8' (11 lbs) panels with an R-value of 2.5.
- 3. **SecurShield HD Plus** a rigid insulation panel composed of a high-density (109 psi max), closed-cell polyisocyanurate foam core laminated to premium-performance coated-glass fiber-mat facer, meeting ASTM C1289, Type II, Class 4, Grade 1. Specifically designed for use as a cover board or recover board. Available 1/2" thick 4' x 4' (6.5 lbs) and 4' x 8' panel (13 lbs) with an R-value of 2.5. Meets an FM 1-90 using only 8 fasteners per 4' x 8' board.
- 4. **InsulBase HD** a closed-cell polyisocyanurate foam core insulation board covered on both sides with glass-reinforced felt (GRF) facer meeting ASTM C 1289, Type II, Class 1, Grade 3. The product is available in 4' x 4' and 4' x 8' standard sizes with a thickness of one-half inch with an R-value of 2.5. ASTM C1289, Type II, Class 1, Grade 3.
- 5. **InsulBase HD Eco** A rigid-roof insulation cover board with 5% ISCC-certified bio-attributed content composed of a high-density closed-cell polyisocyanurate foam core bonded on each side to glass-reinforced felt (GRF), meeting ASTM C1289, Type II, Class 1, Grade 3. UL and FM approved for direct application over steel decks. Available in 1/2" thick, 4' x 4' and 4' x 8' panels with an R-value of 2.5. Suitable for both re-roofing and new construction applications, InsulBase HD is specifically designed for use as a cover board in mechanically attached single-ply systems only. InsulBase HD

delivers an R-value of 2.5.

- 6. **Securock Cover Board** A uniform composition of fiber-reinforced gypsum, without a facer, for use as a cover board or a thermal barrier. Available in 1/4" to 5/8" thick and 4' x 4' or 4' x 8' size boards. Long uninterrupted runs (>200') may require slight gapping due to thermal expansion.
- 7. **EcoStorm VSH Cover Board** an engineered composite building material made from a proprietary blend of plastic and cellulose fiber sourced from post-industrial and post-consumer waste streams. EcoStorm VSH is a durable, extremely moisture and mold resistant building material with a core that does not disintegrate or delaminate in the presence of water. Available in 1/2" thick and 4' x 8' size board.
- 8. **Sure-Seal HP Recovery Board** A 1/2" or 1" thick high-density wood fiberboard with an asphalt coated facer for use as a cover board or recover board. Available 1/2" or 1" thick and 4' x 4' or 4' x 8' size boards. When used in reroof / no tear-off projects, warranty is limited to 15-year projects.
- 9. **DensDeck StormX Prime** a reinforced gypsum cover board with an enhanced, moisture-resistant core and coated glass mat facers on the top and bottom side. The top surface is pre-primed and provides excellent bond strength for adhered membrane for use as a cover board. DensDeck StormX Prime is extremely durable and is approved for use in assemblies meeting FM's Very Severe Hail (VSH) Classification. Available in 5/8" thickness and 4' x 4' or 4' x 8' size boards.
- 10. **DensDeck Prime** gypsum core that incorporates glass-mat facings on the top and bottom side. The top surface is pre-primed and provides excellent bond strength for adhered membrane for use as a cover board. Available in 1/4" to 5/8" and 4' x 4' or 4' x 8' size boards.
- 11. **DensDeck Cover Board** gypsum core that incorporates glass-mat facings on the top and bottom side for use as a cover board. Available in 1/4" to 5/8" and 4' x 4' or 4' x 8' size boards.
- 12. **R-Tech FanFold Recover Board** Closed-cell lightweight expanded polystyrene (EPS) with polymeric laminated faces which meets ASTM C 578, while metallic side used with EPDM. Available in thicknesses of 3/8" to 3/4" with coverage 4' x 50' (2 squares). 4' x 8' units are also available.
- 13. **HP Protection Mat –** A nominal 6-oz per square yard UV resistant polypropylene needle punched fabric used either above the membrane as a slip-sheet for ballast or as an underlayment to the membrane. Available 15' x 300' roll (4500 square foot) weighing 0.06 lbs per square foot.
- 14. **DEXcell Glass Mat**® A mold & mildew resistant, gypsum substrate board with coated fiberglass facers, used for thermal protection and acoustical enhancement of roof systems. May be used as a substrate for a vapor retarder and /or the continuous substrate for the application of commercial roofing applications. Available in 1/4", 1/2" and 5/8" thicknesses in 4' x 8' boards.
- 15. **DEXcell FA**TM– A mold & mildew resistant, gypsum substrate board with heavy duty, coated fiberglass facers, used for thermal protection and acoustical enhancement of roof systems. May be used as a substrate for a vapor retarder and /or the continuous substrate for the application of commercial roofing applications. The precoated, fiberglass facers are designed to increase adhesive coverage and enhance performance of the bond strength of the system. Available in 1/4", 1/2" and 5/8" thicknesses in 4' x 4' and 4' x 8' boards.
- 16. **DEXcell® Cement Roof Board** A mold & mildew resistant, Portland Cement, lightweight aggregate roof board with heavy-duty fiberglass mesh facers used as a substrate board, thermal barrier and cover board for commercial roofing applications. Available in 7/16" and 5/8" thicknesses in 4' x 4' and 4' x 8' boards.
- 17. **DEXcell FA VSH**[®] A reinforced gypsum panel with enhanced moisture resistant gypsum core and heavy duty coated glass facers used as a substrate board, thermal barrier and cover board for commercial roofing applications, approved for use in single-ply and multi-ply assemblies meeting FM Very Severe Hail rating. Available in 5/8" thickness in 4' x 4' and 4' x 8' boards.

2.04 Related Materials

A. Flashing

- 1. Sure-Seal/Sure-White or Sure-Seal Gray Pressure-Sensitive Cured Cover Strip: A 6" or 9" wide and 100' long and 12" wide by 50' long Sure-Seal, Sure-White or Sure-Seal Gray 60-mil cured EPDM membrane laminated to a nominal 30-mil cured Pressure-Sensitive TAPE. The Cured Cover Strip is ideal for flashing gravel stops, metal edging, Carlisle Seam Fastening Plates and for EPDM repairs.
- Sure-Seal Pressure-Sensitive Overlayment Strip: A nominal 40-mil black, semi-cured EPDM membrane laminated to a nominal 30-mil cured, Pressure-Sensitive TAPE. Available in 6" and 9" widths and 100' long rolls used to overlay seams, flash gravel stops, metal edgings and Seam Fastening Plates used for additional membrane securement.
- 3. Sure-Seal / Sure-White or Sure-Seal Gray Pressure-Sensitive Elastoform[®] Flashing: A 6" x 100' and 9" or 12" wide by 50' long, 60-mil thick Sure-Seal (black), Sure-White (white) or Sure-Seal Gray (gray) uncured EPDM Flashing laminated to a 30-mil Pressure-Sensitive TAPE used in conjunction with EPDM Primer.
 - Sure-Seal/Sure-White or Sure-Seal Gray uncured Pressure-Sensitive Elastoform Flashing is used to flash inside and outside corners, pipes, scuppers and field fabricated pourable sealer pockets when the use of Carlisle prefabricated flashing accessories is not feasible.
- 4. Sure-Seal/Sure-White or Sure-Seal Gray Pressure-Sensitive Curb Flashing A 20" wide by 50' long Sure-Seal (cured 60-mil thick EPDM membrane with 6" wide Pressure-Sensitive TAPE along one edge to be used to flash curbs/skylights, etc.
- 5. Sure-Seal / Sure-White or Sure-Seal Gray 20" Pressure-Sensitive Cured Flashing A 20" wide by 50' long Sure-Seal (black), Sure-White (white) or Sure-Seal (gray) cured 60-mil thick EPDM membrane, with Pressure-Sensitive TAPE the full width already applied, used to flash curbs/skylights, etc.
- 6. **Sure-Seal / Sure-White or Sure-Seal Gray Pressure-Sensitive "T" Joint Covers:** A factory cut uncured 60-mil thick EPDM flashing laminated to a nominal 30-mil Pressure-Sensitive TAPE, used to overlay field splice intersections and to cover field splices at angle changes; available in 6" x 6" and 12" x 12" sizes for Sure-Seal (black) and 6" x 6" sizes for Sure-White and Sure-Seal (gray).
- 7. **Sure-Seal / Sure-White or Sure-Seal Gray Inside/Outside Corner:** A 7" x 9" precut 60-mil thick (black, gray or white) Elastoform Flashing with a 30-mil Pressure-Sensitive TAPE; used for inside and outside corners, to overlay field splice intersections, and to cover field splices at angle changes.
- 8. **Sure-Seal / Sure-White or Sure-Seal Gray Pressure-Sensitive Pipe Seals** with Pressure-Sensitive TAPE on the deck flange are available for use with Sure-Seal / Sure-White or Sure-Seal Gray Roofing Systems:
 - a. Sure-Seal (black) Pressure-Sensitive Pipe Seals are available in sizes: 1/2" to 3" and 1" to 6".
 - b. Sure-White (white) and Sure-Seal (gray) Pressure-Sensitive Pipe Seals are available in one size: 1" to 6".
- 9. Sure-Seal / Sure-White or Sure-Seal Gray Pressure-Sensitive Pourable Sealer Pocket: A pre-fabricated Pourable Sealer Pocket which consists of a 2" wide plastic support strip with Pressure-Sensitive, adhesive backed uncured Elastoform Flashing; available in 4", 6" and 8" diameters for Sure-Seal (black), 6" diameter for Sure-Seal (gray) and 6" and 8" diameter for Sure-White (white).

B. Splice Tapes, Primers, Adhesives and Sealants/Cleaners

Refer to Product Data Sheets for material coverage rates and proper usage. Prior to the use of any of the products listed below, consult the Material Safety Data Sheets for applicable cautions and warnings.

- 1. Sure-Seal or Sure-White Pressure-Sensitive SecurTAPE: A 3" or 6" wide by 100' long splice tape used for splicing adjoining sections of EPDM membrane. 6" wide splice tape is used for Mechanically Fastened Roofing Systems and 20-year Warranty Systems. Complies with the South Coast Air Quality Management District Rule 1168.
- 2. **HP-250 EPDM Primer:** A solvent-based primer used to prepare the surface of EPDM membrane for application of SecurTAPE or Pressure-Sensitive products. Available in 1- or 3-gallon pails and as CAV-PRIME Pressurized Cylinders.
- 3. Low-VOC EPDM and TPO Primer A Low-VOC (volatile organic compound) primer (less than 250 grams/liter) for

- priming of EPDM or TPO surfaces prior to application of FAT, Cover strip, SecurTAPE and all other pressure-sensitive products. Available in 1- or 3-gallon pails and as CAV-PRIME Pressurized Cylinders.
- 4. **Sure-Seal or Sure-White Lap Sealant:** A heavy-bodied material used at splice intersections beneath "T"-joint covers, at cut edges of reinforced EPDM membrane and around uncured pressure-sensitive accessories.
- Carlisle Weathered Membrane Cleaner: A clear, solvent-based cleaner used to loosen and remove dirt and other
 contaminants from the surface of exposed EPDM membrane prior to applying Carlisle EPDM Primer. Available in 1
 and 5-gallon pails.
- Low-VOC Membrane Cleaner: A Low-VOC (volatile organic compound) cleaner (100% EPA-exempted solvents) used
 to loosen and remove dirt and other contaminants from the surface of exposed EPDM membrane prior to applying
 Carlisle EPDM Primer. Available in 1 and 5-gallon pails.
- 7. **90-8-30A Bonding Adhesive:** A high-strength, yellow colored, synthetic rubber adhesive used for bonding Sure-Seal/Sure-White EPDM membranes to various surfaces.
- 8. **EPDM x-23 Low-VOC Bonding Adhesive**: A Low-VOC (volatile organic compound) bonding adhesive (less than 250 grams/liter) used for bonding Sure-Seal/Sure-White EPDM membranes to various surfaces. Adhesive is available in 5-gallon pails.
- 9. **Low-VOC Bonding Adhesive**: A Low-VOC (volatile organic compound) bonding adhesive (less than 250 grams/liter) used for bonding Sure-Seal/Sure-White EPDM membranes to various surfaces. Adhesive is available in 5-gallon pails.
- Aqua Base 120 Bonding Adhesive: A semi pressure-sensitive water based adhesive; used as a 2-sided contact
 adhesive for bonding Sure-Seal/Sure-White EPDM membrane to various surfaces. Complies with the South Coast Air
 Quality Management District Rule 1168.
- 11. **CAV-GRIP III Low-VOC Aerosol Contact Adhesive/Primer:** a low-VOC, methylene chloride-free adhesive that can be used for a variety of applications including: priming unexposed asphalt prior to applying Flexible FAST Adhesive, adhering Sure-Seal EPDM, horizontally, for the field of the roof, and for adhering Sure-Seal FleeceBACK and Sure-Seal EPDM membrane to vertical walls. Coverage rate is approximately 2,000-2,500 sq. ft. per 40 lb cylinder and 4,000-5,000 sq. ft. per 85 lb cylinder as a primer, in a single-sided application and 750 sq. ft. per 40 lb cylinder and 1,500 sq. ft. per 85 lb cylinder as an adhesive for vertical walls, in a double-sided application; 1,000 sq. ft. per 40 lb cylinder and 2,000 sq. ft. per 85 lb cylinder as an adhesive, horizontally, for the field of the roof, in a double-sided application.
- 12. **Water Cut-Off Mastic:** A one-component, low viscosity, self-wetting, butyl blend mastic used as a sealing agent between the EPDM membrane and applicable substrates.
- 13. **Pourable Sealer**: A black, two-component, solvent-free, polyurethane based product used for tie-ins and as a sealant around hard-to-flash membrane penetrating objects such as clusters of pipes and for a daily seal when the completion of flashings and terminations cannot be completed by the end of each work day.
- 14. **One-Part Pourable Sealer:** A black, one-component, moisture curing, elastomeric polyether sealant used for attaching lightning rod bases and ground cable clips to the membrane surface and as a sealant around hard-to-flash penetrations such as clusters of pipes.
- 15. **Universal Single-Ply Sealant** A one-part polyether, non-sagging sealant designed for sealing expansion joints, control joints and counter flashings. Available in white or gray.

2.05 Fastening Components

A. Securement Strips (RUSS)

- 1. **Sure-Seal Pressure-Sensitive RUSS** (Reinforced Universal Securement Strip): A 6" or 9" wide, nominal 45-mil thick, clean, cured reinforced EPDM black membrane with 3" wide Pressure-Sensitive Tape laminated along one edge for the 6" wide RUSS and along both edges for the 9" wide RUSS.
 - a. 6" wide Pressure-Sensitive RUSS is used horizontally or vertically at the base of walls, curbs, etc., in conjunction with Fastening Plates or Bars below the EPDM deck membrane for additional membrane securement.
 - b. **9" wide Pressure-Sensitive RUSS** is utilized for perimeter membrane securement on Sure-Seal Mechanically Fastened Roofing Systems and primary securement on Metal Retrofit Roofing Systems.
- 2. Sure-White Pressure-Sensitive RUSS (Reinforced Universal Securement Strip): A 6" wide, nominal 45-mil

thick, clean, cured, reinforced EPDM membrane with 3" wide Pressure-Sensitive Tape laminated along one edge. Used on Sure-White Adhered Roofing Systems.

B. Fasteners

The following Table illustrates criteria for fastening of Carlisle Insulation with the referenced roof deck and includes minimum penetration requirements and pilot hole criteria.

Insulation Fastening Criteria

Deck Type	Carlisle Fasteners (1)	Min. Penetration	Pilot Hole Depth	Pilot Hole Diameter
Steel or Lightweight Insulating Concrete over Steel	HP, HP-X, ASAP or InsulFast™	3/4"	N/A	N/A
Structural Concrete, rated 3,000 psi	CD-10	1"	Note (2)	7/32"
or greater	HD 14-10	1"	Note (2)	3/16"
Wood Plank, min. 15/32" thick Plywood or min. 7/16" OSB	HP, HP-X, ASAP or InsulFast	Min. 1" (3)	N/A	N/A
Cementitious Wood Fiber	Polymer Gyptec	1-1/2"	Note (4)	N/A
Cementitious Wood Fiber	Lite-Deck Fastener	2"	Note (4)	N/A
Gypsum	Polymer Gyptec	1-1/2"	Note (2)	7/16", 1/2" or 9/16" (5)
Gypsum	Lite-Deck Fastener	2"	Note (5)	Note (6)

Notes: N/A = Not Applicable

- (1) Only 3" diameter insulation fastening plates can be used for insulation attachment.
- (2) The pilot hole must be predrilled to a sufficient depth to prevent contact between the fastener point and any accumulated dust in the predrilled hole. This will help prevent bottoming out of the fastener during installation.
- (3) For wood planks only, fastener penetration shall not exceed 1-1/2".
- (4) Most cementitious wood fiber decks do not require pre-drilling; however, Carlisle should be contacted prior to installation for verification of specific types that may require a pilot hole to be predrilled.
- (5) Pilot hole size may be varied to maximize pullout resistance.
- (6) Gypsum hardness varies, and the desired pullout may determine pilot hole size. This could range from 1/2" to 5/16.

All Sure-Seal Fasteners listed below can be used with Sure-Seal or Sure-White Roofing Systems. Refer to the applicable specification for specific requirements.

- 1. **HP Fastener**: A threaded E-coat square head fastener for insulation and Reinforced membrane attachment for Mechanically Fastened Systems in conjunction with 2" diameter polymer seam plates. Used into steel, wood plank, minimum 15/32" thick plywood or minimum 7/16" thick oriented strand board (OSB).
- 2. **HP-X Fastener**: A high-performance fastener with an oversized, heavy shank with #15 thread diameter for single-ply membrane or insulation attachment, used to secure steel decks (20- [0.91 mm] or 22-gauge [0.76 mm]) or wood, minimum 15/32" thick CDX plywood).
- 3. **HP-Xtra Fastener: An** oversized diameter (.315") steel, threaded fastener used in conjunction with HP-Xtra Polymer Seam Plates for membrane securement into minimum 22-gauge steel or wood decks on Mechanically Fastened Roofing Systems.
- 4. **Pre-Assembled ASAP Fastener**: Carlisle's InsulFast Fastener pre-assembled with a 3" diameter plastic plate used for insulation attachment only on Adhered and Mechanically Fastened Roofing Systems.
- 5. **InsulFast Fastener**: A threaded Phillips drive fastener used with Carlisle Insulation Plates for insulation attachment to steel or wood decks.
- HD 14-10 Concrete Fastener: A #14 threaded fastener with a #3 Phillips drive used for minimum 3,000 psi concrete decks.
- 7. **CD-10 Fastener**: A hammer-driven, non-threaded E-Coat fastener for use with structural concrete decks rated 3,000 psi or greater.
- 8. **Polymer Gyptec Fastener**: A non-penetrating, plastic fastener and corresponding plate used with lightweight deck substrates such as fibrous cement and gypsum.
- 9. Lite-Deck Fastener: A deep, coarse threaded fastener used to secure insulation to gypsum and cementitious

wood fiber decks in conjunction with Lite-Deck Plates.

10. **HP Term Bar Nail-In**: A 1-1/4" long expansion anchor with threaded drive pin used for fastening Sure-Seal Termination Bar or Seam Fastening Plates to concrete, brick or block walls. The fastener is set by hammering the drive pin into place.

C. Fastening Plates and Bars

- 1. **HP Polymer Seam Plate**: A 2" diameter plastic barbed fastening plate used with Carlisle HP Fasteners for membrane and Pressure-Sensitive RUSS securement for Mechanically Fastened Roofing Systems over steel roof decks.
- HP-Xtra Polymer Seam Plate: A 2 3/8" diameter plastic barbed fastening plate used with HP-Xtra Fasteners for membrane and Pressure-Sensitive RUSS securement for Mechanically Fastened Roofing Systems over steel roof decks.
- 3. **Seam Fastening Plates**: A 2" diameter metal plate used for insulation attachment on Mechanically Fastened Roofing Systems or membrane securement on Adhered Roofing Systems in conjunction with the appropriate Carlisle Fastener.
- 4. **Insulation Fastening Plates**: A nominal 3" diameter metal plate used for insulation attachment in conjunction with the appropriate Carlisle Fastener.
- 5. **SecurFast Insulation Fastening Plates:** A nominal 2-7/8" hexagon metal plate used for insulation attachment in conjunction with the appropriate Carlisle Fastener.
- 6. **Accutrac Insulation Plates:** A nominal 3" square, recessed or flat bottomed, metal plate used for insulation attachment in conjunction with the appropriate Carlisle Fastener. Flat bottom plate is used with manufactured Philips Head fasteners only.
- 7. **Gyptec Plates**: A 3" (26 gauge) steel plate for insulation and a 2" (22 gauge) steel plate for membrane attachment. The plates are stamped galvalume-coated steel.
- 8. **Polymer Batten Strip**: A 1" wide by 1/20" thick polymer bar which is pre-punched 6" o. c. packaged in 250' long coils used for membrane securement on Mechanically Fastened Roofing Systems in conjunction with HP or HP-X Fasteners. Refer to applicable Product Data Sheets.
- 9. **Metal Fastening Bar**: A 1" wide metal bar which is pre-punched 6" o. c. and packaged in 10' long strips to be used for membrane securement on Mechanically Fastened Roofing Systems.

2.06 Insulation Securement Adhesive

- 1. **Flexible FAST Adhesive:** A spray (full coverage) or bead-applied, two-component polyurethane, construction grade, low-rise expanding foam adhesive used for attaching approved insulations to compatible roof decks or existing smooth or gravel surfaced BUR, modified bitumen or cap sheets.
- 2. **Flexible FAST Dual Tank:** A two component (Part A and B), extrusion applied, low rise adhesive for bonding insulation to various surfaces. Flexible FAST Dual Tanks utilize an HFO blowing agent. HFO (hydrofluoroolefin) blowing agents are widely recognized as the next-generation environmentally friendly blowing agent, replacing their HFC (hydrofluorocarbon) predecessor. When extruded at 12" on center the coverage rate is 3,500 to 3,700 sq.ft. per set of Dual Tanks.
- 3. Flexible FAST Dual Cartridge and 5-gallon Jug Adhesive: A two component (Part A and B), extrusion applied, low rise adhesive for bonding insulation to various surfaces. When extruded at 12" on center the coverage rate is 400-600 sq.ft. per carton of Dual Cartridges or 2,000-2,500 sq.ft. per set of 5-gallon Jug Adhesive.
- 4. **OlyBond 500 Bag in a Box** A two-component, polyurethane, low-rise expanding adhesive used to bond insulation to various substrates. Packaged in 5-gallon boxes of Part A and Part B formulations that are applied using a mechanical dispenser system. Applied in 1/2" to 3/4" beads or ribbons at the rate of 1 gallon per 150-250 square feet for 12" o.c. bead spacing. Perimeter bead spacing patterns and acceptable insulation and deck types are listed in the applicable Product Data Sheet.
- 5. OlyBond 500 BA Spot Shot A two-component, polyurethane construction grade, low-rising expanding adhesive designed for bonding insulation to various substrates. Applied in 1/2" to 3/4" beads or ribbons using a portable 1:1 applicator (oversized, dual-cartridge caulking gun). Refer to the Product Data Sheet for bead spacing with reference to building height.

2.07 Vapor/Air Barrier

1. General

- a. The use of a vapor retarder to protect insulation and reduce moisture accumulation within an insulated roofing assembly should be investigated by the specifier, especially on projects with high interior humidity, such as, swimming pools, breweries, pulp mills, etc.
- b. If insulation is to be adhered to the vapor retarder with FAST Adhesive, the vapor retarder must be compatible and shall be fully adhered to the substrate. Available products include Carlisle's VapAir Seal 725TR Air and Vapor Barrier, VapAir Seal MD Air and Vapor Barrier and spray or roller applied butyl coatings. Installation requirements for Carlisle's VapAir Seal 725TR Air and Vapor Barrier are identified in Spec Supplement G-08 "Application Procedures for Carlisle's VapAir Seal 725TR Air and Vapor Barrier/Temporary Roof" and Carlisle's VapAir Seal MD Air and Vapor Barrier are identified in Spec Supplement G-12 "Application Procedures for Carlisle's VapAir Seal MD Air and Barrier" in the Carlisle Technical Manual.
- 2. **Carlisle VapAir Seal 725TR Air and Vapor Barrier** A 40-mil thick composite consisting of 35-mil self-adhering rubberized asphalt membrane laminated to a 5-mil UV resistant poly film with an anti-skid surface which is fully compatible with FAST Adhesive. 725TR can also function as a temporary roof for up to 120 days. Available in rolls 39" wide by 100' long (325 square feet).
- 3. **Carlisle VapAir Seal MD Air and Vapor Barrier** a reinforced composite aluminum foil with self-adhesive SBS backing and removable poly release film. Used for direct application over metal decks. Available in rolls 42.5" wide by 131.23' long (460 square feet).
- 4. **CAV-GRIP III Low-VOC Aerosol Contact Adhesive/Primer:** a low-VOC, methylene chloride-free adhesive that can be used for a variety of applications including: enhancing the bond between Carlisle's VapAir Seal 725TR and various substrates. Coverage rate is approximately 2,000-2,500 sq. ft. per #40 cylinder and 4,000-5,000 sq. ft. per #85 cylinder as a primer, in a single-sided application.
- 5. CCW-702 Primer and 702LV Primer (Low-VOC) A single component, solvent based, high-tack primer used to provide maximum adhesion between Carlisle 725TR Air and Vapor Barrier and an approved substrate. Applied by spray or long nap roller with a coverage rating ranging from approximately 300 to 350 square feet per gallon on smooth finishes (i.e., concrete) to 75 square feet per gallon on porous surfaces (i.e., DensDeck Prime gypsum board). Available in 5-gallon containers. CCW-702LV Primer contains less than 250g/L VOCs and meets South Coast Air Quality Management District (SCAQMD) and Leadership in Energy and Environmental Design (LEED) Requirements for Volatile Organic Compounds.
- 6. CCW-702WB a high-tack, water-based contact adhesive for promoting adhesion of Carlisle air/vapor barrier membranes and an approved substrate (i.e., concrete, DensDeck Prime and Securock). Applied by roller, brush or spray with an application rate of approximately 200 sq. ft. per gallon. Available in 5-gallon containers. CCW-702WB Primer contains 57g/L VOCs and meets South Coast Air Quality Management District (SCAQMD) and Leadership in Energy and Environmental Design (LEED) Requirements for Volatile Organic Compounds.

2.08 Edges And Terminations

A. General

Products listed below can be used with any of the available Carlisle Roofing Systems. Refer to the applicable Carlisle details and installation instruction manuals for specific installation criteria.

B. Products

1. Fascia Products

- a. **SecurEdge CF Snap-on Fascia:** A two-part snap-on assembly including a base plate and decorative snap-on cover. Includes a 20-gauge retainer base plate with pre-slotted holes for fasteners. The fascia is available in 0.040" or .050" aluminum with mill-finish, anodized-finish or Kynar ® 500 finish or 22- or 24-gauge galvanized steel with Kynar ® 500 finish or acrylic coated galvalume finish. Available in a variety of standard colors. Custom colors are available upon request. Available in sizes from 3-1/2" to 12-1/4" face heights. ANSI/SPRI/FM-4435 ES-1 certified.
- b. **SecurEdge One Fascia:** A snap-on edge system consisting of a 20-gauge galvanized steel formed rail with pre-punched slots, a 6" stainless steel spring clip. corrosion resistant fasteners with a 24-gauge galvanized steel or 0.040", 0.050" or 0.063" Kynar® finished aluminum fascia cover. Available in a variety of standard colors. Custom colors are available upon request. Available in 12' standard lengths with face sizes of 4", 5", 6" and 8". ANSI/SPRI/FM-4435 ES-1 certified.
- c. SecurEdge Snap-On Canted Fascia: A snap-on edge system consisting of a 24-gauge galvanized metal water dam with pre-punched holes, a 24-gauge stainless steel spring clip and a snap-on cover. The cover is available in 0.040", 0.050" or 0.063" thick mill-finish, anodized, or Kynar® 500 finish aluminum or 22- or 24-gauge steel with Kynar® 500 finish. The fascia is available in a variety of standard colors. Custom colors are available upon request. Available in 12' standard lengths and heights varying from 5" to 12-1/2". ANSI/SPRI/FM-4435 ES-1 certified.
- d. **SecurEdge Crimp-On Canted Fascia:** A crimp-on edge system featuring a 24-gauge, galvanized metal water dam with pre-punched holes, a 24-gauge stainless steel spring clip and a snap-on cover. The fascia cover is available in 0.040", 0.050" or 0.063" thick mill-finish, anodized, or Kynar® 500 finish aluminum or 22- or 24-gauge steel with Kynar® 500 finish. The fascia is available in a variety of standard colors. Custom colors are available upon request. Available in 12' standard lengths and heights varying from 5-1/4" to 12-3/4". ANSI/SPRI/FM-4435 ES-1 certified.
- e. **SecurEdge EX Snap-On Fascia: An** anchor bar roof edge fascia system consisting of heavy 0.100" thick extruded aluminum bar, corrosion resistant stainless-steel fasteners and snap-on fascia cover used with Adhered, Mechanically Fastened assemblies. The fascia cover is available in 0.040", 0.050" or 0.063" thick mill-finish, anodized, or Kynar® 500 finish aluminum or 22- or 24-gauge steel with Kynar® 500 finish. The fascia is available in a variety of standard colors. Custom colors are available upon request. Available in 12' standard lengths and 4", 5-1/2", 7" and 8-1/2" heights. ANSI/SPRI/FM-4435 ES-1 certified.

2. Coping Products

- a. SecurEdge Snap-on Coping: A snap-on coping system that incorporates 20-gauge anchor cleats with preslotted holes, a concealed joint cover and 10' or 12' continuous sections of coping cap consisting of 40, 50 or 63-mil thick clear and colored anodized, and Kynar 500 finish or 24-gauge steel with Kynar® 500 finish. The coping cap is available in a variety of standard colors. Custom colors are available upon request. Also available in a variety of widths including custom pieces such as tees, crosses, radius copings, etc. ANSI/SPRI/FM-4435 ES-1 certified.
- b. SecurEdge Snap-on Gold Coping: A snap-on coping system that incorporates 20-gauge, galvanized steel anchor clips and 12", 20-gauge, factory-applied stainless-steel springs. Available with 22- and 24-gauge steel with Kynar® 500 finish or 0.040", 0.050" and 0.063" mill-finish, anodized or Kynar® 500 coated aluminum. A variety of standard colors are available. Custom colors are available upon request. ANSI/SPRI/FM-4435 ES-1 certified.
- c. **SecurEdge CF Snap-on Coping:** A snap-on coping system that incorporates 20-gauge, galvanized steel anchor cleats with pre-slotted holes, a concealed joint cover and 0.040", 0.050" and 0.063" thick mill-finish, anodized or Kynar® 500 finish or 22- or 24-gauge Kynar 500® coated steel. The coping cap is available in a

variety of colors and widths, including custom pieces such as tees, crosses, and radius copings. Custom colors are available upon request. Available in standard 12' lengths with 6" to 16" wall heights. ANSI/SPRI/FM-4435 ES-1 certified.

Also available in SecurEdge CF Gold Coping with 16-gauge anchor cleats for added performance.

- d. **SecurEdge One Coping:** A mechanically fastened coping system consisting of a 22-gauge retainer bar (face side only), corrosion resistant fasteners and a .040", .050" or .063" mill-finish, anodized or Kynar® 500 coated aluminum and 22- or 24-gauge, Kynar® 500 coated steel coping cover. A variety of standard colors are available. Custom colors are available upon request. Available for wall thicknesses up to 12". ANSI/SPRI/FM-4435 ES-1 certified.
- e. **SecurEdge Continuous Cleat Coping:** An engineered coping system, featuring continuous, 20-gauge galvanized steel cleats on both the inside and outside face of the parapet. Available with 0.040", 0.050" and 0.063" mill-finish, anodized or Kynar® 500 coated aluminum and 22- and 24-gauge Kynar® 500 coated steel. A variety of standard colors are available. Custom colors are available upon request. Custom fabricated for specific project requirements. Cleat available in standard 12' lengths. ANSI/SPRI/FM 4435/ES-1 Certified. Miami-Dade approved.

3. Water Control Products

- a. SecurEdge Gravel Stop: A two-piece assembly that consists of a continuous 22-gauge steel cleat with prepunched holes and snap-on gravel stop cover. The gravel cover is available in 0.040", 0.050", and 0.063" mill-finish, anodized or Kynar® 500 coated aluminum or 22- and 24-gauge steel with galvanized Kynar® 500 coated or acrylic coated galvalume finish. Available in a variety of standard colors. Custom colors are available upon request. Available in 12' standard lengths with 3" to 10" heights and 1" and 3" flange widths. ANSI/SPRI/FM-4435 ES-1 Certified.
- b. SecurEdge Drip Edge: Designed for use on Adhered and Mechanically Fastened Roofing Systems. Includes a 22-gauge continuous 12' pre-punched, 90-degree angle cleat and 10' or 12' long fascia sections, including concealed joint covers. Available in 0.032" or 0.040" mill-finish, anodized or Kynar® 500 coated aluminum or 24-gauge Kynar 500 coated steel. A variety of standard colors are available. Custom colors are available upon request. ANSI/SPRI/FM-4435 ES-1 certified.
- c. **SecurEdge EX Drip Edge:** Featuring an extruded aluminum anchor bar with pre-punched holes for roof membrane securement. The cover is manufactured from 0.040" aluminum with mill-finish, anodized or Kynar[®] 500 finish or 24-gauge steel with Kynar[®] 500 finish. Available in standard 12' lengths with sizes ranging from 3" to 7.5" face heights. A variety of standard colors are available. Custom colors are available upon request. ANSI/SPRI/FM 4435/ES-1 certified. Miami-Dade approved.
- d. SecurEdge WR Gutter: system incorporates 1" wide extruded internal gutter brackets and aluminum or galvanized steel gutter. Available in 0.040", 0.050 or 0.063" aluminum, and 22-gauge or 24-gauge with Kynar® 500 finish. Gutter support brackets are extruded aluminum. Available in box style, chamfer style, and offset profiles. ANSI/SPRI/FM 4435/ES-1 certified.
- e. **Sure-Seal Ballast Retaining Bar**: A ballast retaining perimeter securement system comprised of a slotted (4" on center) extruded mil aluminum retention bar with an integrated compression fastening strip. 1-1/2" stainless steel fasteners with Neoprene washers are provided for stable securement.
- f. **Termination Bar**: A 1" wide and 98-mil thick extruded aluminum bar pre-punched 6" on center which incorporates a sealant ledge to support Lap Sealant and provide increased stability for membrane terminations.
- g. **SureTite Snap-On Fascia Cleat:** Prefabricated, 22-gauge, Galvalume steel, continuous, snap-on cleat with pre-punched holes. Used for use on single ply roofing applications when Carlisle metal flat sheets are used to shop fabricate the fascia or coping cover. Available in 12' standard lengths and 4-1/4" to 8-1/4" face heights. ES-1 certified.
- h. **SureTite Drip Edge Cleat:** Prefabricated, 22-gauge, Galvalume steel, continuous, cleat with pre-punched holes. Used for use on single ply roofing applications when Carlisle metal flat sheets are used to shop fabricate the drip edge, gravel stop or flat coping cover. Available in 12' standard lengths and 3", 5" 6" and 7" heights. ES-1 certified.
- 4. Other Carlisle Metal Edgings / Copings suitable for use with roofing system included in the section, can be found in the Specification Supplement G-11 Metal Edging.

2.09 Roof Walkways

Walkways are to be specified at all traffic concentration points (i.e., roof hatches, access doors, rooftop ladders, etc.), and if regular maintenance, once a month or more, is necessary to service rooftop equipment.

1. Walkway types:

- a. Sure-Seal / Sure-White or Sure-Seal Gray Pressure-Sensitive Walkway Pads: Sure-Seal (black), Sure-White (white) or Sure-Seal Gray (gray) molded walkway pads with Pressure-Sensitive TAPE used to provide protection for areas of EPDM membrane that are exposed to regular rooftop maintenance.
- b. **Sure-Seal Interlocking** TM **Rubber Pavers**: 24" X 2" thick rubber paver weighing approximately 24 pounds per unit, 6 pounds per square foot manufactured from recycled rubber, which provides a resilient, shock absorbing, weather resistant surface. Designed primarily for use as a walkway or on terrace areas offering a unique, environmentally sound advantage over concrete pavers. Features include freeze/thaw stability, bidirectional drainage and no breakage concerns. Available in black and terra cotta.
- c. **Hanover Ballast and Lightweight Ballast Pavers:** The standard, 24" x 24" x 1-13/16" thick, Ballast Paver comes in a natural color and a non-slip Diamond finish and weighs 22 lbs/sq. ft. The Lightweight, 23-1/2" x 23-1/2" x 1-1/4" thick, Ballast Paver comes in a natural color and a non-slip diamond finish and weighs 15 lbs/sq. ft. Both pavers can be used as ballast or walkways.

2.10 Other Carlisle Accessories

Refer to Spec Supplement P-01 "Related Products" for additional accessories.

Part III - EXECUTION

Prior to commencing with the installation of any of the EPDM Membrane Systems refer to Paragraph 1.05 "Warranty Tables" for applicable components and proper securement method suitable for the appropriate warranty coverage.

Requirements listed in this specification are considered minimum and are intended for the sole purpose of obtaining a Carlisle Warranty. Additional requirements dictated by Regulatory Agencies, Building Insurance or Specifiers must be complied with and are considered to be beyond the scope of this specification.

3.01 General

- A. Safety Data Sheets (SDS) must be on location at all times during transportation, storage and application of materials. The applicator shall follow all safety regulations as recommended by OSHA and other agencies having jurisdiction.
- B. Subject to project conditions, it is recommended to begin the application of this roofing system at the highest point of the project area and work to the lowest point to prevent water infiltration. This will include completion of all flashings, terminations and daily seals.
- C. A proper substrate shall be provided by the building owner. The structure shall be sufficient to withstand normal construction loads and live loads.

3.02 Roof Deck/Substrate Criteria

- A. Proper decking shall be provided by the building owner. The building owner or their designated representative must ensure that the building structure is investigated by a registered engineer to assure its ability to withstand the total weight of the specified roofing system, as well as construction loads and live loads, in accordance with all applicable codes. The specifier must also designate the maximum allowable weight and location for material loading and storage on the roof.
- B. When insulation is mechanically fastened to the roof deck, withdrawal resistance tests are strongly suggested to determine the suitability of the roof deck. Refer to Design Reference DR-06 "Withdrawal Resistance Criteria" in the Carlisle Technical Manual proper procedures for conducting pullout tests.
- C. Defects in the substrate surface must be reported and documented to the specifier, general contractor and building owner for assessment. The Carlisle Authorized Roofing Applicator shall not proceed with installation unless defects are corrected.
- D. On structural concrete decks, when a vapor retarder is not used, gaps in the deck along the perimeter and around penetrations must be sealed along with vertical joints between tilt-up panels, if present, to prevent infiltration of hot

humid air and possible moisture contamination resulting from condensation. This is specifically important when polyurethane adhesive is used to attach the roof insulation.

- E. **For all projects** (new or retrofit), the substrate must be relatively even without noticeable high spots or depressions. Accumulated water, ice or snow must be removed to prevent the absorption of moisture in the new roofing components and roofing system.
- F. Prior to the placement of membrane underlayment, clear the substrate of debris and foreign material that may be harmful to the roofing system. Gaps greater than 1/4" must be filled with an appropriate material.
- G. For direct application over an acceptable roof deck/substrate or when HP Protective Mat is specified and approved by Carlisle as the membrane underlayment in accordance with the Roof Deck and Substrate Criteria Table, the substrate must be smooth, steel trowel finished (structural concrete), free of debris, protrusions, sharp edges and loose and foreign material. Cracks or voids in the substrate, greater than 1/4", must be filled with an appropriate material.
- H. On retrofit recover projects, cut and remove wet insulation, as identified by the specifier, and fill all voids with new insulation of type specified so it is relatively flush (+/- 1/4") with the existing surface.
 - 1. Entrapment of water between the old and new membrane can damage and deteriorate new insulation/underlayment between the two membranes. If a vapor retarder or air barrier is not specified, Carlisle recommends the existing membrane be perforated to avoid potential moisture accumulation and to allow the detection of moisture to enable the building owner to take corrective action. This can be accomplished by drilling approximately 3/4" diameter holes every 100 square feet in the existing built-up roof or single-ply membrane (excluding PVC membrane).
 - For existing PVC membranes, if the membrane is not removed, it must be cut into maximum 10' by 10' sections. All PVC flashings at the perimeter, roof drains and roof penetrations must be removed.
 - When installing this roofing system over an existing gravel surfaced built-up roof, loose gravel must be removed. Power brooming is recommended by Carlisle to remove the loose gravel, which may trap moisture. Any uneven areas of the substrate must be leveled to prevent insulation from bridging.
 - 4. On retrofit projects, all existing phenolic insulation must be removed.
 - 7. Refer to the table below for other Recover/Retro-fit considerations.
- The following table identifies the acceptable roof decks/substrates and the minimum underlayment requirements for Carlisle's EPDM Roofing Systems.

Note: Refer to the Warranty Tables, Paragraph 1.05, of this specification, for the minimum underlayment requirements for a specific Warranty Coverage.

Roof Deck & Substrate Criteria

Certain warranty restrictions apply for projects with warranties greater than 15 YR. Refer to Table V "Re-Roofing Substrate Criteria" for warranty limitations in paragraph 1.05.

Acceptable Roof Deck/Substrate	EPDM Membrane					
NEW CONSTRUCTION	Adhered - Design "A"	Ballasted - Design "B"	Mechanically Fastened			
Steel (min. 22 gauge) (1)(2)	Insulation	Insulation	Insulation			
Structural Concrete (min. 3000 psi)	Direct Application (11)	Insulation	HP Protective Mat (10)			
Plywood (min. 15/32" thick) or Oriented Strand Board (min. 7/16" thick)	Direct Application (11)	Insulation	Direct Application (11)			
Wood Planks (minimum 3/4" thick)	Direct Application	Insulation	Direct Application (11)			
Fibrous Cement	Insulation	Insulation	HP Protective Mat			
Lightweight Insulating Concrete	Note 3 (10)	HP Protective Mat (10)	Direct Application (10)			
RETROFIT / NO TEAR-OFF	Adhered - Design "A"	Ballasted - Design "B"	Mechanically Fastened			
Existing Smooth Surface BUR or Mineral Surface Cap Sheet	Direct Application (4) (11)	Insulation	Direct Application (4) (11)			
Gravel Surfaced BUR (5)	Insulation	Insulation	Insulation			
Coal Tar Pitch (5)(6)	Insulation (9)	Insulation	Insulation			
Modified Bitumen	Direct Application (8) (11)	Insulation	Direct Application (8) (11)			
Existing Single-Ply	Insulation	Insulation (7)	Direct Application (7) (11)			
Sprayed-in-place Urethane	Complete Tear-off Required	Insulation	Complete Tear-off Required			
RETROFIT / TEAR-OFF	Adhered - Design "A"	Ballasted - Design "B"	Mechanically Fastened			
Existing roof material removed (regardless of deck type)	Insulation	Insulation	Insulation			

Notes:

- (1) Local codes must be consulted regarding thermal barrier requirements.
- (2) Mechanically Fastened Systems cannot be specified on steel decks less than 22 gauge or for corrugated steel decks, regardless of gauge.
- (3) The Design "A" Adhered Roofing System may be specified directly over a new approved cellular or perlite lightweight insulating concrete substrate with a minimum compressive strength of 225 psi. Except when the lightweight insulating concrete is poured over slotted steel decks, pressure relief vents must be specified at a minimum rate of 1 every 2000 square feet. Direct Application is not permitted where the lightweight concrete is poured over an existing roofing material. Refer to Spec Supplement G-04 "Adhered Application Over Lightweight Insulating Concrete".
- (4) Sure-Seal (black) Adhered and Mechanically Fastened Systems may be applied directly to the substrate provided asphalt on existing smooth surfaced built-up roof has a softening point above 185°F (85°C). Sure-White (white-on-black) Roofing Systems are not recommended for direct application to the substrate due to possible staining of the membrane surface. For direct application over smooth BUR or granule surface BUR or in conjunction with HP Mat make sure substrate is clean and free of roofing cement and fresh asphalt to avoid sheet contamination and staining of white color membrane.
- (5) Loose gravel must be removed to avoid entrapment moisture.
- (6) Existing coal tar could drip back into the building, especially when new insulation does not provide sufficient thermal value to prevent the surface of the coal tar from softening.
- (7) An approved Insulation/underlayment is required over existing ballasted single-ply systems and PVC roofing systems of any type. (8) Direct application permitted over smooth surfaced modified bitumen. Membrane shall be positioned with length of sheets parallel to modified bitumen field seams. At end laps or other locations where EPDM splices intersect modified bitumen field seams, 6" wide Elastoform or Pressure-Sensitive Flashing must be applied over intersections.
- (9) If insulation is specified to be secured to an existing coal tar pitch roof with Carlisle FAST Adhesive or hot asphalt, minimum 1.5" thick Polyisocyanurate insulation is the required minimum thickness when Sure-Seal (black) EPDM is specified. Minimum 1" thick Polyisocyanurate is the required minimum thickness when Sure-White (white) EPDM is specified.

(10) For direct application, membrane system warranties are limited to 15 YR unless specifically approved by Carlisle.

(11) Maximum warranty available is 20 YR with 55 MPH warranty wind speed (72 MPH warranty wind speed over structural concrete, wood planks or plywood) Peak gust wind speed coverage. Carlisle may be contacted for other options.

J. Vapor Retarder Installation

For Carlisle's Vapor Retarder refer to Spec Supplement G-08 "Application Procedures for 725TR Air and Vapor Barrier". Follow the respective vapor retarder manufacturer's recommended installation procedures and the specifier's instructions for the installation of the product specified. When insulation is to be set in adhesive, verify compatibility with Carlisle when Vapor Retarder by others is specified.

K. Wood Nailers

- Install wood nailers in locations that have been designated by the specifier and as approved by Carlisle. Refer
 to Design Reference DR-08 "Wood Nailers and Securement Criteria" for Wood Nailer Criteria.
- 2. Wood nailers are not covered by the Carlisle Warranty.

3.03 Insulation/Underlayment

A. General

- 1. Roof insulation thickness must be determined by the thermal value required for each project and may be subject to code approval limitations. On projects where a vapor retarder is used, the specifier must calculate insulation thickness to ensure the temperature at the vapor retarder will not fall below the dew point.
- 2. For new construction projects in cold climate regions, the use of vapor retarders or air barriers is strongly recommended to protect insulation from moisture generated during construction.
- 3. Multiple layers of insulation are recommended with all joints staggered between layers.
- 4. Do not install more insulation/underlayment than can be covered by membrane in the same day.
- 5. All insulation boards must be butted together with no gaps greater than 1/4". Gaps greater than 1/4" are not acceptable.

6. Restrictions:

- a. Carlisle Roofing Systems cannot be specified in conjunction with Phenolic Insulation.
- b. Fiberglass insulation cannot be specified with Carlisle's Design "A" Adhered and Mechanically Fastened Roofing Systems, even if overlaid with additional insulation or membrane underlayment.
- c. Do not specify perlite boards directly under the EPDM membrane on Design "A" Adhered or Mechanically Fastened Roofing Systems.
- d. Wood fiberboard manufactured by others is not an acceptable underlayment for use with Design "A" Adhered Roofing Systems unless approved in writing by Carlisle prior to installation.
- e. For all EPDM Roofing Assemblies, the use of insulation by others is not acceptable when a Carlisle Membrane System Warranty is specified. Carlisle insulation must be used.

3.04 Insulation Attachment

A. General

1. Prior to proceeding with insulation securement refer to Warranty Tables, Paragraph 1.05, for attachment method and appropriate fastening density required for the specific Carlisle Warranty.

B. Adhered Roofing Systems

1. **Mechanical Attachment**, insulation fastening density will vary based on insulation type, thickness, and required warranty. Warranty Tables in Paragraph 1.05 should be referenced for fastening density and the appropriate Carlisle detail may be consulted to identify acceptable fastening pattern.

- a. For code compliance, increased fastening density may be required depending upon project wind speed and wind uplift requirement. Refer to Design Reference DR-05 "Insulation Fastening Patterns" for fastening pattern reference.
- b. When insulation securement is to comply with Factory Mutual (FM) approvals, follow the requirements of the specifier concerning additional securement at the roof perimeter and corners. Also refer to Design Reference DR-05 "Insulation Fastening Patterns" for various fastening patterns.
- c. On Reroof/No Tear off projects with a maximum roof height of 40', any Carlisle Insulation (i.e., 1/2" SecurShield HD, HP Recovery Board, Polyisocyanurate less than 1-1/2" thick) may be secured at the minimum rate of 11 Fasteners per 4' x 8' board (5 Fasteners per 4' x 4' board).
- d. When Oriented strand board (OSB) is specified for membrane underlayment, utilize StormBase OSB/Polyiso Composite, mechanically fastened to the deck at the rate 17 fasteners for 4 x 8 board in accordance with Carlisle Details. When positioning OSB, butt edges and stagger joints of adjacent panels.
- 2. Adhesive attachment, Carlisle Urethane Adhesive Full Spray (Flexible FAST) or Bead (Flexible FAST or Olybond) may be used. When bead adhesive is specified bead spacing will vary based on Warranty coverage, refer to Warranty Tables, Paragraph 1.05 and appropriate Carlisle Details. CAUTION: Apply adhesive bead so that the distance from the edge of the board does not exceed half the bead spacing (i.e. within 6" of bead spacing of 12" O.C.).
 - a. CAUTION: Do not apply urethane adhesives directly to un-weathered asphalt, (new or residual).
 - b. CAUTION: Especially in cold regions on tear-off projects or new construction gaps between horizontal and vertical surfaces of the roof area as well as gaps around penetrations must be sealed to prevent interior warm air from infiltrating and condensing within the roofing assembly. Condensing moisture could weaken bottom insulation facer and eventually result in dislodgement or loose boards when adhesive is used.
 - c. On FM Global insured projects, consult FM Global's local representative concerning the use of adhesive to attach insulation to steel decks.
 - d. Check to ensure the substrate is clean, free of debris, other contaminants, and dry. Adhesive cannot be applied to a wet or a damp surface.
 - e. Apply Adhesive over the dry substrate area at the coverage rates indicated in Spec Supplement G-03
 "Insulation Attachment with Flexible FAST Adhesive".
 - f. Allow the adhesive to rise up approximately 1/8" to 3/4", depending on dispensing method, and develop strings prior to setting insulation boards into adhesive.

Note: String-time is measured by touching the adhesive with a splice wipe and looking for development of "strings" of adhesive as you pull the splice wipe out of the adhesive. With Flexible FAST Adhesive, string time is generally around 1-1/2-2 minutes after application at room temperature.

g. Walk the boards into the adhesive and roll using the 30" wide, 150-pound segmented steel roller to ensure full embedment. Optimal set up time should be approximately 5 to 7 minutes.

CAUTION: Walking on the boards immediately after placement in adhesive can cause slippage/movement until the adhesive has started to set up.

CAUTION: If the boards easily slide, string time has not been achieved.

On roofs with a slope greater than 1/2" in 12", begin adhering insulation at the low point and work upward to avoid slippage.

One person should be designated to walk/roll in all boards. Relief cuts may be necessary to allow lifted board to lay flat, or constant weight (a minimum 10 lbs for 5-15 minutes per lifted area) may be necessary to achieve adequate adhesion.

- h. Refer to Spec Supplement G-02 "Flexible FAST Adhesive Equipment and Set-Up Requirements" and G-03 "Insulation Attachment with Flexible FAST Adhesive" for application procedures and coverage rates.
- 3. **Alternate attachment method**, the specifier may select an alternate insulation attachment that incorporates a solid mopping of the insulation with hot asphalt (ASTM D312, Type III or IV). If the attachment method is to be covered by the Carlisle Warranty, Carlisle must be contacted for specific requirements. Upon review and acceptance by Carlisle, the maximum warranty coverage available is limited to 20 Year with maximum Peak Gust Wind Speed Coverage of 72 mph.
 - Extruded or Expanded Polystyrene insulation are not acceptable when this alternate attachment method is specified.
 - b. The existing gravel surfaced built-up roof must be scraped to remove all loose gravel. Large blisters that may prevent continuous embedment of insulation must be repaired. The surface of the substrate must also be dry and clear of foreign material.
 - c. On coal tar pitch, when deemed compatible by the specifier, minimum 1.5" Polyisocyanurate is the required membrane underlayment when using Sure-Seal (black) membrane. If Sure-White (white) membrane is used, minimum 1" thick Polyisocyanurate is required.
 - d. For successful attachment, proper asphalt temperatures must be maintained and the specifier's requirements concerning the installation of a base sheet (where required) and quantity of hot asphalt must be followed.
 - e. The maximum insulation board size shall not exceed 4' X 4'. Trim insulation boards around crickets and saddles to ensure continuous embedment.
 - f. Care must be exercised to prevent contamination of the top surface of the insulation. Asphalt oozing through insulation joints must be wiped from the surface. Contact with fresh asphalt can result in discoloration of the Sure-White membrane.
 - g. Use of grid nailer, subdividing the roof into individual sections of 2400 square feet, is not required, but its use is strongly recommended.
 - h. The wood nailers are installed relatively flush with the insulation surface and the membrane is to be fastened with seam fastening plates and Carlisle HP fasteners on 12" o.c. For wood nailer installation, refer to Design Reference DR-08 "Wood Nailers and Securement Criteria".

C. Ballasted Roofing Systems

1. Insulation boards shall be loose laid over the substrate.

Note: If insulation securement is specified, only Carlisle approved insulation adhesive may be used. Mechanical securement of roof insulation is not permitted due to increased probability of membrane puncture during ballast installation or periodic rooftop maintenance.

1. Refer to Roof Deck/Substrate Criteria in Paragraph 3.02 for further information.

Note: The use of cover boards, such as SecurShield HD, SecurShield HD Plus, DensDeck or DensDeck Prime or DensDeck StormX Prime, Securock or DEXcell®, is not permitted in conjunction with Ballasted Assemblies to reduce possible membrane punctures. Hard cover boards do not provide sufficient cushioning beneath the membrane and therefore when the assembly is subjected to traffic, the membrane is subjected to higher point loading resulting in puncture.

D. Mechanically Fastened Roofing Systems

- Carlisle Fasteners and Fastening Plates are required for insulation securement. Refer to Insulation
 Fastening Criteria Table in Paragraph 2.05, for appropriate fastener and deck penetration. The fastener can be
 used with either 2" diameter Sure-Seal Seam Fastening Plates or 3" diameter Sure-Seal Insulation Fastening
 plate.
- 2. **Any Carlisle approved insulation or cover board** shall be mechanically fastened to the roof deck at the minimum rate of **1.25 fasteners and plate per every 8 square feet** (5 fasteners in a 4 x 8 board) for warranties up to 15 year. Projects with up to 20 year or greater warranties (with standard wind speed coverage) require the use of 6 fasteners and plates in a 4' x 8' board (1 per 5.333 square feet).

CAUTION: Sure-Seal Polyisocyanurate Insulation with a thickness less than 1.5" installed over an

existing roofing membrane without a tear-off must be mechanically fastened to the roof deck with a minimum of **1 fastener and plate for every 4 square feet** or less of insulation.

3. Use of DensDeck, DensDeck Prime, DensDeck StormX Prime and DEXcell® should be limited to assemblies with slopes greater than 2" per foot to ensure compliance with external fire codes, care shall be exercised to ensure polymer seam plates are fully seated.

3.05 Membrane Placement and Securement

A. General

- 1. **Ensure** that water does not flow beneath any completed sections of the membrane system by completing all flashings, terminations and daily seals by the end of each workday.
- 2. **Sweep** all loose debris from the substrate.
- 3. If aesthetics are of concern when Sure-White EPDM is to be used, protection should be specified to avoid discoloration of the white membrane surface resulting from adhesive residue or excess foot traffic.
- 4. Adjoining sheets of EPDM membrane are spliced together using SecurTAPE and Primer.
- 5. In addition to the primary membrane securement (Bonding for Adhered, Ballasting for Ballasted Systems and Fastening for Mechanically Fastened assemblies), additional membrane securement is required at the perimeter of each roof level, roof section, curb, skylight, interior wall, penthouse, etc., at any inside angle change where slope or combined slopes exceed 2" in one horizontal foot, and at other penetrations in accordance with the applicable Carlisle details. Refer to Paragraph G for additional membrane securement.

B. Membrane Placement

EPDM membrane with factory applied tape is available in various widths. Prior to unrolling sheets ensure the tape side is properly located so that seams are properly shingled down slope. (Pre-applied SecurTAPE should always be facing downwards once the sheet is unrolled).

- 1. **Position** EPDM membrane over the acceptable substrate without stretching. For mechanically fastened assemblies ensure proper number of perimeter sheets are properly positioned along the perimeter of the roof. And field sheets are positioned perpendicular to the steel deck flutes.
- 2. **Allow** the membrane to relax approximately 1/2 hour prior to splicing (Ballasted systems), bonding (Adhered Systems) or fastening (Mechanically Fastened).
- Place adjoining membrane sheets in the same manner, overlapping edges appropriately to provide for the minimum splice width (2-1/2" or 5-1/2" depending on warranty duration). It is recommended all splices be shingled to avoid bucking of water.

C. Membrane Securement / Bonding - Adhered Roofing Systems (90-8-30A, EPDM x-23 LVOC, Low-VOC Bonding Adhesive or Aqua Base 120)

- 1. Adhere EPDM membrane to an acceptable substrate with Carlisle Bonding Adhesive. Comply with Labels, Safety Data Sheet (SDS) and Product Data Sheets for installation procedures and use. Contact type bonding adhesive must be applied to both the membrane and the surface to which it is being bonded.
- On projects at high altitudes (6,000' and above), rapid flash-off (drying) of Bonding Adhesive and Primers will occur due to low atmospheric pressure.
- 3. **Fold** membrane sheet back so approximately half of the underside of the sheet is exposed. Sheet fold should be smooth without wrinkles or buckles.
- 4. **Stir** Bonding Adhesive thoroughly scraping the sides and the bottom of the can (minimum 5 minutes stirring is recommended). Bonding surfaces must be dry and clean.

CAUTION: If aesthetics are of concern when Sure-White EPDM membrane is used, protect the white surface next to the edges of the folded membrane sheet so Bonding Adhesive will not discolor the white surface. Do not place Bonding Adhesive containers or their lids directly on the white surface of the Sure-White EPDM membrane.

5. Apply Bonding Adhesive evenly, without globs or puddles, with a plastic core medium nap paint roller. A 9"

roller will easily fit into the 5-gallon containers.

Apply contact type bonding adhesive to both the membrane sheet and the substrate to achieve continuous coating of both surfaces at a coverage rate of approximately 120 square feet per gallon per one surface (membrane or substrate) or approximately 60 square feet per gallon per finished surface (includes coverage on both membrane and substrate). **Depending on adhesive used and the substrate type adhesive coverage rate will vary**. Refer to Product Data Sheets for the appropriate adhesive for the proper coverage rate.

A mechanical roller dispenser or a mechanical sprayer can be used to apply Bonding Adhesive when the continuous coating and coverage rate noted above are maintained. When used, the adhesive must be rolled after applying with a plastic core medium nap paint roller to provide continuous coverage.

CAUTION: Due to solvent flash-off, condensation may form on freshly applied Bonding Adhesive when the ambient temperature is near the dew point. If condensation develops, possible surface contamination may occur and the application of Bonding Adhesive must be discontinued. Allow the surface to dry and apply a thin freshener coat at the coverage rate, which is approximately half of the coverage rate stated above to the previously coated surface when conditions allow for continuing.

- 6. Allow adhesive to flash-off until it is tacky but will not string or transfer to a dry finger touch.
- 7. **Roll** the coated membrane into the coated substrate while avoiding wrinkles.
- 8. **Brush** down the bonded half of the membrane sheet, immediately after rolling the membrane sheet into the adhesive, **with a soft bristle push broom** to achieve maximum contact.
- 9. Fold back the unbonded half of the membrane sheet and repeat the bonding procedure.

D. Membrane Securement - Self-Adhering Technology (SAT™) (Application Option 1)

- 1. Sure-Seal SAT™ membrane must be allowed to relax and expand reaching the required minimum sheet temperature prior to installing.
 - i. Minimum temperature requirements for Sure-Seal SAT™ installation are based on substrate and fastening method as follows:20° (-6.7°C) ambient and sheet temperature after relaxation for all approved substrates and fastening methods.
 - ii. Use a temperature gun to ensure the membrane is 20° (6.7°C) prior to installation.
- 2. Prior to membrane placement, the surface of the insulation or underlayment board must be cleaned of dust and other foreign matter using a fine push broom or blower.
- 3. Unroll membrane and allow to relax for 30 minutes.
- 4. **Remove** the release liner on one-half of the sheet, starting from the split in the liner at the middle of the sheet. The liner should be removed at an angle to reduce splitting or tearing.
- 5. **Pull** the membrane onto the substrate at an angle, avoiding wrinkles. When installing Sure-Seal SAT membrane, it is recommended to maintain a large curve (radius) on the leading edge of the membrane. This will help eliminate creases and bubbles that cannot be removed after the sheet is in place.
- 6. Broom the membrane in place, starting from the middle of the 10'-wide sheet and working the outer edge.
- 7. Fold back the remaining half of the sheet and repeat the above process.
- 8. After brooming, roll the membrane with a segmented roller to ensure full contact with the substrate. Roller must weigh at least 50 lbs. (22 kg) per linear foot.
- 9. To complete seam between two adjoining membrane panels, apply primer to the splice area in conjunction with Carlisle's Factory Applied Tape.
- 10. Strip-in end laps with 6" Pressure-Sensitive Cured Cover Strip.

E. Membrane Securement – Self-Adhering Technology (SAT™) (Application Option 2)

- SAT™ membrane must be allowed to relax and expand reaching the required minimum sheet temperature prior to installing.
- 2. Minimum temperature requirements for Sure-Seal SAT™ installation are based on substrate and fastening method as follows:
 - i. 20° (-6.7°C) ambient and sheet temperature after relaxation for all approved substrates and fastening

methods.

- ii. Use a temperature gun to ensure the membrane is 20° (6.7°C) prior to installation.
- 3. Prior to membrane placement, the surface of the insulation or underlayment board must be cleaned of dust and other foreign matter using a fine push broom or blower.
- 4. **Unroll** membrane and allow to relax for 30 minutes.
- 5. **Pull** both release liners off simultaneously from underneath the membrane at a low angle, similarly to removing the release film from splice tape.
- 6. **Push** a broom lengthwise down the middle of the sheet to tack it in place. Continue brooming to push air out from the middle of the sheet towards the edges.
- 7. After brooming, roll the membrane with a segmented roller to ensure full contact with the substrate. Roller must weigh at least 50 lbs. (22 kg) per linear foot.
- 8. To complete seam between two adjoining membrane panels, apply primer to the splice area in conjunction with Carlisle's Factory Applied Tape.
- 9. **Strip-in** end laps with 6" Pressure-Sensitive Cured Cover Strip.

F. Membrane Securement / Bonding - Adhered Roofing Systems (CAV-GRIP III)

- 1. **Adhere** EPDM membrane to an acceptable substrate with CAV-GRIP III Bonding Adhesive. Comply with Labels, Safety Data Sheet (SDS) and Product Data Sheets for installation procedures and use. Contact type bonding adhesive must be applied to both the membrane and the surface to which it is being bonded.
- 2. On projects at high altitudes (6,000' and above), rapid flash-off (drying) of Bonding Adhesive and Primers will occur due to low atmospheric pressure.
- Fold membrane sheet back so approximately half of the underside of the sheet is exposed. Sheet fold should be smooth without wrinkles or buckles.
- 4. Connect CAV-GRIP III Cylinder with hose and spray gun. Bonding surfaces must be dry and clean.
 - **CAUTION:** If aesthetics are of concern when Sure-White EPDM membrane is used, protect the white surface next to the edges of the folded membrane sheet so Bonding Adhesive will not discolor the white surface. Do not place CAV-GRIP III Cylinders directly on the white surface of the Sure-White EPDM membrane.
- 5. **Spray apply CAV-GRIP III** Bonding Adhesive evenly to both the membrane and substrate with a minimum 2" overlap to ensure 100% coverage. Avoid heavy areas or puddles that can skin over, trap solvent and create a blister. Refer to Product Data Sheets for the proper coverage rate.
 - **CAUTION:** Solvent flash-off can lower surface temperature below the dew point causing moisture to form on the adhesive. Slide your hand across the flashed-off adhesive on the insulation or cover board to ensure moisture has evaporated and the adhesive surface is dry and tacky prior to installing the membrane.
- Allow adhesive to flash-off, especially the heavy areas of adhesive, until it is tacky but will not string or transfer to a dry finger touch.
- 7. **Roll** the coated membrane into the coated substrate while avoiding wrinkles.
- 8. **Brush** down the bonded half of the membrane sheet, immediately after rolling the membrane sheet into the adhesive, **with a soft bristle push broom**.
- 9. Roll the membrane with a 150 lb weighted segmented steel roller after brooming to achieve maximum contact.
- 10. Fold back the unbonded half of the membrane sheet and repeat the bonding procedure.

G. Membrane Securement / Ballasting - Ballasted Roofing Systems

1. Ballasting - General

- a. Use of temporary ballast to prevent wind uplift is the responsibility of the Carlisle Authorized Roofing Applicator. For immediate protection against wind uplift, Carlisle requires ballast to be installed as each section of the installation is completed.
- b. When using polystyrene insulation directly beneath the membrane, ballast must be applied immediately after membrane installation to prevent potential damage to polystyrene insulation products from excessive heat.
- c. Care must be exercised during application of gravel or pavers. Heavily traveled areas during ballast installation must be protected by placing temporary protection courses to prevent possible damage to the EPDM deck membrane and insulation.

2. Ballast Types/Coverage Rates

- a. The coverage rates listed in this section are considered minimum and are required by Carlisle for issuance of the standard Carlisle warranty. Depending on specific project conditions (building height, parapet height and project location), additional ballast may be necessary to provide wind uplift protection. Refer to "Attachment I" at the end of this section for suitable ballast types and coverage rates. Comply with the specifier's requirements when an additional ballast coverage rate is specified.
- b. **Rounded Water-Worn Gravel** must be applied over the EPDM membrane at the minimum rate of **1000 pounds per square** and must be evenly distributed to maintain an average of 10 pounds per square foot.

ASTM D 7765 SIZE NUMBER	MINIMUM COVERAGE RATE (pounds per square)	AVERAGE COVERAGE RATE (lbs./sq. ft. continuously distributed)
4 (1-1/2" nominal diameter)	1000	10
3 (2" nominal diameter)	1000	10
2 (2-1/2" nominal diameter)	1300	13
1 (3-1/2" nominal diameter)	1300	13

Notes: In the field of the roof, some bare spots resulting from installation are permitted; however, they must not exceed 64 square inches and must be limited to no more than 2 per square (100 square feet). No bare spots are permitted in the perimeter area of the roof that is 10' wide.


- c. Crushed Stone must be applied in conjunction with Sure-Seal HP Protective Mat placed over the EPDM membrane. The crushed stone must be applied at the minimum rate of 1000 pounds per square and must be evenly distributed to maintain an average of 10 pounds per square foot.
- d. Smooth Surfaced Individual Concrete Pavers or Lightweight Interlocking Concrete Pavers
 - 1) Lightweight interlocking pavers and individual concrete pavers with a surface other than steel troweled finish must be installed over Sure-Seal HP Protective Mat. Contact Carlisle for verification of acceptable pavers.
 - Individual Concrete Pavers, when specified, must be installed loose laid and butted with no gaps greater than 1/2".


Note: Do not install pavers heavier than 100 pounds per unit unless approved in writing by Carlisle.


- Lightweight Interlocking Concrete Pavers, when specified, must be installed in accordance with the respective manufacturer's specification and as approved by Carlisle prior to installation.
- 3. Ballast Criteria for Up to 20 Year Extended Warranty
 - Refer to installations below for calculating corner/perimeter areas for the noted warranty wind speeds available.

Ballast Requirements for 72 mph Warranty

Ballast Requirements for 80 mph Warranty







- A (Corners) = .4 Times the Building Height (10' minimum)
- B (Perimeters) = 10'
- b. At corner and/or perimeter areas, ballast shall be 2-1/2" nominal rounded water worn gravel conforming to gradation #1 or #2 in accordance with ASTM -D7765 method of sizing. Coverage rate shall be a minimum of 13 pounds per square foot.
- c. In field areas, ballast shall be 1-1/2" nominal rounded water worn gravel conforming to gradation #4 in accordance with ASTM-D7765 method of sizing. Coverage rate shall be a minimum of 10 pounds per square foot.

4. Placement of Sure-Seal HP Protective Mat

- a. When specified or required by Carlisle, position Sure-Seal HP Protective Mat loosely over the membrane with all edges overlapped a minimum of 6".
- b. Extend the mat a minimum of 2" above the anticipated ballast level at the perimeter and around penetrations except for roof drains and scuppers.
- The mat must extend to drain bases, scupper openings and the base of Dutch gutters but must not restrict drainage.
- d. Additional matting must be installed around penetrations to prevent direct contact between crushed stone or pavers and flashing.

Note: Following the placement of the HP Protective Mat, it is necessary to install the ballast or temporary ballast to prevent the movement or displacement of unballasted fabric.

H. Membrane Securement / Mechanically Fastened Roofing Systems (Fastening)

1. EPDM membrane shall be mechanically attached to the structural deck with specified Carlisle Fasteners and designated Plates or Bars, for fastening densities and numbers of perimeter sheets refer to Warranty Tables, Paragraph 1.05.

Membrane Fastener Selection

Deck Type	Carlisle Fasteners*	Carlisle Plate
Steel or Lightweight Insulating	HP	HP Polymer or Seam Fastening Plates**
Concrete over Steel	HP-Xtra	HP-Xtra Polymer
Structural Concrete, rated 3,000 psi	CD-10	HP Polymer or Seam Fastening Plates
or greater	HD 14-10	HP Polymer or Seam Fastening Plates
Wood Plank, min. 15/32" thick Plywood or min. 7/16" OSB	HP	HP Polymer or Seam Fastening Plates
Cementitious Wood Fiber	Polymer Gyptec	Gyptec Plates – 2" Dia.
Gypsum	Polymer Gyptec	Gyptec Plates – 2" Dia.

Refer to Warranty Tables in Paragraph 1.05 for fastening densities and number of perimeter sheets.

- 3. On steel decks, membrane shall be positioned with seams perpendicular to the steel deck flutes. This allows the external forces on the roof assembly to be distributed between multiple steel deck panels. Refer to Design Reference DR-06 "Withdrawal Resistance Criteria" in the Carlisle Technical Manual.
- 4. When mechanical securement is not provided in some of the Carlisle Universal Details (i.e., pipes and pourable sealer pockets), additional Seam Fastening Plates must be used for membrane securement. The plates must be positioned a maximum of 12" away from the penetration, spaced a maximum of 12" on center and flashed in accordance with the applicable Carlisle Detail.

5. Perimeter Sheets

The number of perimeter sheets and fastener spacing is dependent on the building height, wind zone location and warranty duration as outlined in Warranty Tables in Paragraph 1.05.

The roof perimeter is defined as all edges of each roof section (i.e., parapets, building expansion joints at adjoining walls, penthouse walls, etc.). When multi-level roofs meet at a common wall, the adjacent edge of the upper roof is treated as a roof perimeter if the difference in height is greater than 10'. Perimeter sheets are not required at the base of the wall at the lower level.

Note: Expansion joints, control joints and fire walls in the field of the roof or roof ridges with slopes less than 3" to the horizontal foot are not considered as part of the roof perimeter.

Perimeter sheets can be formed by using individual 5', 6.5' wide sheets or by sub-dividing 8' or 10' wide field sheet using 9" Pressure-Sensitive RUSS strip or row of seam fastening plates as described below.

a. Individual perimeter sheets (5', 6.5')

Position membrane along the perimeter of the roof over the acceptable insulation/underlayment. The perimeter membrane width from line of securement to line of securement should be approximately 4.5' - 6.0' wide depending on perimeter sheet size.

b. RUSS (Reinforced Universal Securement Strip) Method

- When field sheets are positioned parallel to a roof perimeter, 9" wide Pressure-Sensitive RUSS shall be placed approximately down the center of the 8' or 10' wide field membrane sheets. When a RUSS divides a field sheet in half, two perimeter sheets are created.
- When a 8' or 10' wide reinforced EPDM membrane sheet extends perpendicular to the edge of the roof, install 9" wide Pressure-Sensitive RUSS beneath the EPDM membrane sheet approximately of 3'-6" for the 8' field sheet to approximately of 4' -0" for the 10' field sheet from the edge of the roof. When multiple perimeter sheets are required, additional RUSS may be positioned approximately 3'-6" to 4'-0" from the previous RUSS to create additional perimeter sheets.

CAUTION: 6" wide Pressure-Sensitive RUSS is only available with 3" wide SecurTAPE on one side and therefore cannot be used to form perimeter sheets.

^{*}Determine proper fastener length for deck penetration, refer to Table 2.05B.

^{**}Seam Fastening Plates for Base of Wall Angle Change Only

3) Refer to Applicable Carlisle Details for installation.

c. Fastening Plates Method (When Option a and b are not feasible)

When field sheets extend to the edge of the roof, approved fastening plates can be installed through the reinforced membrane 3'-6" to 4'-6" from the roof edge which will be flashed with 6" wide Pressure-Sensitive Cured Cover Strip. When field sheets are positioned parallel to the roof edge, fastening through the membrane along the centerline creates two perimeter sheets. When multiple perimeter sheets are required, additional fastening plates shall be positioned 3'-6" to 4'-6" from the previously installed fastening plates. Refer to applicable Carlisle Details for installation.


d. Building with Special Conditions:

Air pressurized buildings, canopies and buildings with large openings where the total wall openings exceed 10% of the total wall area on which the openings are located (such as airport hangars, warehouses and large maintenance facilities) will typically require additional perimeter membrane securement, an increased fastening density or other enhancement.

e. Buildings with large openings

When any wall contains major openings with a combined area which exceeds 10% of the total wall area on which the openings are located, either four 5' or 6.5' wide or two 10' wide reinforced EPDM membrane sheets (centered over the opening) must be specified as shown.

- 1) 9" wide Pressure-Sensitive RUSS (Reinforced Universal Securement Strip) shall be specified in conjunction with the 8' or 10' wide membrane sheets.
- 2) The 9" wide Pressure-Sensitive RUSS is to be positioned beneath the 8' or 10' wide membrane sheet along the centerline and shall be secured with Polymer Seam Plates (required for steel decks) or Seam Fastening Plates. All fasteners and plates shall be spaced at the rate required at the roof perimeter as shown on the membrane securement charts on the previous pages.



3) As an option to the above perimeter securement, an adhered membrane section


may be used in lieu of the mechanically fastened membrane at large openings in accordance with the Carlisle Specification for the Sure-Seal/Sure-White Adhered Roofing System.

NOTE: Depth of perimeter area, noted above, shall not be less than 2.5 times the width of the opening.

f. Buildings with overhangs

The membrane must be specified with securement 3-1/2' to 4-1/2' over the entire overhang area extending onto the main roof deck a minimum of 3-1/2' when at the same level.

- This can be achieved utilizing 8' or 10' wide membrane sheets in conjunction with 9" wide Pressure-Sensitive RUSS as described above.
- As an option, an adhered membrane section may be used in lieu of the mechanically fastened membrane at building overhangs in accordance with the Carlisle Specification for the Sure-Seal/Sure-White Adhered Roofing System.



6. Field Membranes

a. **Position** field membrane sheets adjacent to perimeter membrane to allow a minimum 6" overlap, 3" from the center of the plate or bar in front and back.

Note: For 20-year warranty projects with a roof slope less than 1/4" in 12" (minimum 1/8" slope required) or when splices buck water, strip in seams with a 6" Pressure Sensitive Overlayment or Cured Cover Strip.

b. **Secure the field and perimeter membrane sheets** along the pre-printed blue line approximately 3" from the edge of the membrane sheet at the approved fastening density with the required Carlisle Fastener and Carlisle Seam Plates or Bars. Refer to "Membrane Fastener Selection" Table in Paragraph 3.05 for further information.

Correct fastener placement must conform to the following:

- The minimum distance between the bottom membrane edge and the nearest edge of the fastening plate or bar must be 2".
- The minimum distance between the overlapping membrane edge and the nearest edge of the fastening plate or bar must be 2".
- c. On new construction projects, where direct application of the membrane is specified over HP Protection Mat over lightweight insulating concrete, standard 2" diameter Seam Fastening Plates must be used since the Polymer Seam Plates will not properly seat.
- d. **Position** adjoining membrane sheets to allow a minimum overlap of 6" where Fastening Plates are located (along length of the membrane); at the same time overlap end roll sections (width of the membrane) a minimum of 3", for Projects with a maximum 15 Year Warranty. For 20 Year Warranties, end roll sections should be overlapped 6" with 6" SecurTAPE.
- e. Work shall progress across the roof with a minimum 6" overlap provided at the previously secured sheet edge. The opposite length of the sheet must be secured with approved Fastening Plates or bars and overlapped accordingly.

I. Membrane Splicing

1. General

- a. Sure-Seal/Sure-White Adhered or Ballasted Roofing Systems
 - 1) Projects with 10-, 15-, 20- and 25-year warranties

Side Laps / End Laps: Tape splices must be a minimum of 2-1/2" wide using 3" wide field-applied Pressure Sensitive SecurTAPE OR 3" Factory-Applied TAPE (FAT). (Detail U-2A or as an option Detail U-2A.1)

Splice Intersections: 'T'-Joints are to be flashed with a bead of lap sealant and 6"x6" minimum (black) or 7"x9" (white) Pressure-Sensitive 'T'-Joint Cover, (for membranes of maximum thickness of 75 mil). (**Detail U-2A**). **For membranes of thickness of 90 mil**, Apply a second layer of 12"x12" Pressure-Sensitive 'T'-Joint Cover centered over 6"x6" 'T'-Joint Cover. (**Detail U-2A.1**)

Note: In lieu of the 6"x6" or 12"x12" Pressure-Sensitive 'T'-Joint cover, a 6"x6" or 12"x12" section of Pressure-Sensitive Elastoform flashing may be used as a 'T'-Joint cover. Pressure-Sensitive Elastoform flashing is available in rolls of 6", 9" and 12".

2) Projects with 30-year warranties

OPTION 1:

Side Laps / End Laps: Tape splices may be a minimum 3" wide Factory-Applied Tape (FAT) OR 3" wide Field-Applied SecurTAPE. In addition the entire field splice must be overlaid with a continuous 6" wide Pressure Sensitive Overlayment Strip. (See Detail U-2A).

Splice Intersections: Overlay the entire field splice with a continuous 6" wide Pressure-Sensitive Overlayment Strip. Apply Lap Sealant at all Intersections between Pressure-Sensitive Overlayment Strip. (See **Detail U-2A.1**).

OPTION 2:

Side Laps / End Laps: Tape splices may be a minimum of 5-1/2" wide using 6" wide Factory-Applied Tape (FAT) OR 6" wide Field-Applied SecurTAPE. (Detail U-2A.1).

Splice Intersections: 'T'-Joints are to be flashed with a bead of lap sealant and 6"x6" minimum Pressure-Sensitive 'T'-Joint Cover. Apply a second layer of 12"x12" Pressure-Sensitive 'T'-Joint Cover centered over 6" x 6" 'T'-Joint Cover. (Detail U-2A.1).

Note: Pressure Sensitive Elastoform flashing is available only in rolls of 6", 9" or 12" rolls. Material used for Overlayment shall be cut from the appropriate roll.

b. Sure-Tough or Sure-White (reinforced) Mechanically Fastened Roofing Systems

1) Projects with 10-, 15-, 20- and 25-year Warranties

Side Laps: Regardless of Warranty duration, where fastening plates are placed, shall be spliced using **6" wide Factory-Applied Tape (FAT) OR 6" wide Field-Applied SecurTAPE**. The splice tape shall be centered over the plates to extend approximately 2" on each side. SecurTAPE must extend approximately 1/8" beyond the edge of the overlapping membrane. (Detail MF-2A).

End Laps: Shall be spliced using either **3" wide SecurTAPE** resulting in a minimum splice of 2-1/2" wide for a maximum of 20-year warranties. (Detail MF-2B).

Splice Intersections: 'T'-Joints are to be flashed with a bead of lap sealant and 6"x6" pressure sensitive 'T'-Joint Cover, (for membranes of maximum thickness of 75 mil). (Detail MF-2A).

2) Projects with 30-year Warranties

Side Laps: Where fastening plates are placed, shall be spliced using 6" wide Factory-Applied Tape (FAT) OR 6" wide Field-Applied SecurTAPE. The splice tape shall be centered over the plates to extend approximately 2" on each side. SecurTAPE must extend approximately 1/8" beyond the edge of the overlapping membrane. (Detail MF-2D).

End Laps: Shall be spliced using 6" wide Factory-Applied Tape (FAT) OR 6" wide Field-Applied SecurTAPE resulting in a minimum splice of 5-1/2" wide for a maximum of 30-year warranties. (Detail MF-2B.1).

Splice Intersections: 'T'-Joints are to be flashed with a bead of lap sealant and 6"x6" Pressure Sensitive 'T'-Joint Cover. Apply a second layer of 12"x12" Pressure Sensitive 'T'-Joint Cover centered over 6" x 6" 'T'-Joint Cover. (Detail MF-2D).

2. For Splicing procedures, cautions and warnings refer to Spec Supplement E-02 "EPDM Membrane Splicing and Splice Repairs" for information.

J. Additional Membrane Securement

Securement must be provided at the perimeter of each roof level, roof section, expansion joint, curb flashing, skylight, interior wall, penthouse, etc., at any inside angle change where slope exceeds 2" in one horizontal foot, **and at other penetrations** in accordance with Carlisle's details and securement options as listed below.

Securement may be achieved as follows:

1. Pressure-Sensitive RUSS (Reinforced Universal Securement Strip)

Pressure-Sensitive RUSS is a 6" wide strip of reinforced EPDM membrane with factory-applied 3" wide SecurTAPE and is installed in conjunction with Sure-Seal Fasteners and 2" diameter Seam Fastening Plates spaced a maximum of 12" on center below the EPDM deck membrane (Polymer Seam Plates or Polymer Batten Strips are required for Mechanically Fastened Roofing Systems over steel decks). The securement strip can be fastened horizontally to the structural deck or vertically at walls and curbs.

a. Loose lay the 6" wide Pressure-Sensitive RUSS along parapet walls 6" to 9" from corners and fasten with Seam Fastening Plates and the appropriate Carlisle fastener to the roof deck or into the parapet wall. Spacing of the Seam Fastening Plates shall be a maximum of 12" on center for up to 20-year warranties (less than 90 mph

warranty wind speed) and a maximum of 6" on center for 25- and 30-year warranties.

- 1) For horizontal attachment, the reinforced strip must be positioned a minimum of 1/8" to a maximum of 6" away from the angle change with pressure sensitive side facing away from the parapet and towards the roof plane.
- 2) For vertical attachment, the reinforced strip must be attached to the vertical wall with pressure sensitive side extending onto the roof surface.

CAUTION: Horizontal RUSS attachment is required when insulation is attached with adhesives to a vapor barrier or an existing asphalt based roof. For various options, Refer to Spec Supplement G-08 "Application Procedures for Carlisle's VapAir Seal 725TR Air and Vapor Barrier".

- b. Adjoining sections of the reinforced strip need not be overlapped; however, gaps between adjoining sections must not exceed 1".
 - **CAUTION:** When RUSS is used for membrane securement along metal edgings, refer to the appropriate detail for applicable installation criteria. For some metal edge details, adjoining sections of the reinforced strip must be overlapped and spliced.
- c. When using Pressure-Sensitive RUSS, clean the underside of the membrane with Carlisle Primer and allow proper flash-off prior to removing the release film from the RUSS.

CAUTION: On Adhered Systems discontinue bonding adhesive application on the underside of the membrane in area of the sheet where contact with the Pressure-Sensitive RUSS is to occur. Contact between Pressure-Sensitive RUSS and membrane coated with bonding adhesive can result in poor peel and shear values.

2. Seam Fastening Plates

When the use of Pressure-Sensitive RUSS is not feasible (at smaller curbs or skylights), a 2" diameter Seam Fastening Plates may be used.

- a. Seam Fastening Plates may be installed horizontally into the structural deck or into walls or curbs.
- b. Securement of the EPDM membrane with the approved Carlisle Fasteners and Seam Fastening Plates must be a maximum of 12" on center starting 6" minimum to 9" maximum from inside and outside corners.
- c. If horizontal wood nailers are provided, secure the Seam Fastening Plates to the wood nailer with Carlisle HP Fasteners. Nails (i.e. ringshank, roofing, etc.) are not acceptable for securement.
- d. After securing the Seam Fastening Plates, flash in accordance with the appropriate Carlisle Detail.

3.06 Flashings

For other requirements which must be complied with in order for Carlisle warranty to be issued, refer to Spec Supplement G-05 "Flashing Considerations / Metal Work".

A. General Considerations

- All vertical field splices at the base of a wall or curb must be overlaid with Pressure-Sensitive "T" Joint Covers, a 6" x 6" section (with rounded corners) of Sure-Seal/Sure-White Pressure-Sensitive Uncured Elastoform Flashing centered over the field splice.
- Pressure-Sensitive Uncured Elastoform Flashing must be limited to the overlayment of vertical seams (as required at angle changes), or to flash inside/outside corners, vent pipes, scuppers and other unusually shaped penetrations where the use of Pre-molded Pipe Seals, cured EPDM membrane or Pressure-Sensitive Cured Cover Strip or Overlayment Strip is not practical

Note: When using Pressure-Sensitive products in colder temperatures, use a heat gun to warm the product. Apply heat to the EPDM flashing side of the product. Do not apply heat directly to the preapplied adhesive. The Pressure-Sensitive Flashing must be applied immediately after Primer flashes off. Refer to "Membrane Splicing with SecurTAPE" for application procedures in colder temperatures.

3. When using Pressure-Sensitive Cured Cover Strip or Overlayment Strip to overlay Seam Fastening Plates or

metal edging, etc., Sure-Seal HP-250 or LOW-VOC Primer must be used to clean the membrane and metal flanges.

4. Special requirements may apply for certain flashing details for projects with extended warranty durations. Refer to Carlisle published details for applicable requirements when warranty coverage exceeds beyond 20 years.

B. Walls, Parapets, Curbs, Skylights, etc.

- Use continuous deck membrane with Pressure-Sensitive RUSS or Seam Fastening Plates along the angle change.
 - a. When using Pressure-Sensitive RUSS, refer to Paragraph 3.05 G, Additional Membrane Securement, for attachment criteria.
 - b. When Seam Fastening Plates are used to secure continuous deck membrane, use minimum 6" wide Pressure-Sensitive Cured Cover Strip or Overlayment Strip to overlay fasteners and plates.
- 2. When the use of continuous deck membrane for wall flashing is not feasible, a separate piece of cured EPDM membrane may be used.

NOTE: 60-mil cured non reinforced membrane may be used as a separate wall flashing with projects of warranty 20 years or greater. The flashing may also incorporate membrane equal of thickness to that of the EPDM membrane at the deck level.

- 3. Adhere flashing to the wall and terminate in accordance with the applicable Carlisle Detail.
- 4. Use a "T" Joint Cover or 6" x 6" Pressure-Sensitive Elastoform Flashing with rounded corners to overlay vertical splices as shown on the applicable Carlisle Detail.
- 5. Refer to applicable Carlisle Details for various corner flashing options.
- C. Flashing of other Penetrations, refer to Spec Supplement G-05 for "Flashing Considerations / Metal Work" and the applicable Carlisle detail for specific requirements.
- D. Flashing of Difficult Penetrations, refer to Spec Supplement G-13 for "LIQUISEAL Liquid Flashing" for additional information and specific requirements.

3.07 Roof Walkways

Walkways are to be installed at all traffic concentration points (i.e., roof hatches, access doors, rooftop ladders, etc.), other locations designated by specifier, and if regular maintenance (once a month or more) is necessary to service rooftop equipment. Refer to Spec Supplement G-06 "Roof Walkway Installations".

3.08 Daily Seal

On phased roofing, when the completion of flashings and terminations is not possible by the end of each workday, provisions must be taken to temporarily close the membrane to prevent water infiltration. Refer to Spec Supplement G-07 "Daily Seal / Clean Up".

3.09 Optional Color Coating

- If optional color coating is specified, Carlisle's final inspection for warranty must be conducted prior to the coating application. This will permit the completion of any "Repair for Warranty" items without consideration for the removal and reapplication of the coating. The owner will then verify that the coating was applied after receiving the warranty.
- 2. If **Sure-Seal X-Tenda Coat** is specified to color the membrane surface, refer to the Carlisle X-Tenda Coat Specification for installation requirements.

3.10 Clean Up

For Daily tie-off or cleaning procedures refer to Spec Supplement G-07 "Daily Seal / Clean Up" in the Carlisle Technical

1. General

- a. Termination bars and surface mounted reglets must be installed directly to the wall surface.
- b. Carlisle recommends SecurEdge Metal Edging/Coping, Sure-Seal Termination Bar or Sure-Seal Drip Edge for membrane termination. Installation instruction sheets for Carlisle supplied accessories are available from Carlisle.

Note: Refer to Warranty Tables in Section 1.05 for specific metal edge requirements for projects with Total System Warranties or those with extended peak gust wind speed coverage greater than 80 miles per hour.

- c. Metal work by others, when specified, must be fastened to prevent the metal from pulling free or buckling and sealed to prevent moisture from entering the roofing system or building. Unless supplied by Carlisle, metal work securement is not included in this specification and is excluded from the Carlisle warranty.
- d. **On retrofit projects**, existing counter flashing, edging, expansion joint covers, copings, etc., shall not be reused unless investigated by the specifier to determine its compliance to Carlisle's current details.

Copyright 2025 Carlisle Construction Materials Incorporated
Carlisle, CAV-GRIP, Elastoform Flashing, Flexible FAST Adhesive, FAT and Factory Applied Tape, FleeceBACK, HPX Fasteners,
InsulBase, InsulFast, LIQUISEAL, Piranha Plate, Pre-Kleened, SAT/Self Adhering Technology, SecurEdge, Securfast, SecurShield,
SecurTAPE, StormBase, Sure-Seal, Sure-Tough, Sure-White, VapAir Seal and X-Tenda Coat are Trademarks of Carlisle Construction
Materials Incorporated

Insulfoam, InsulLam and R-Tech are Trademarks of Insulfoam
Thermapink, Foamular and Durapink are Trademarks of Owens Corning
DensDeck, DensDeck Prime and DensDeck StormX Prime are Trademarks of Georgia-Pacific Corporation
Securock are Trademarks of USG
DEXcell® is a trademark of Gold Bond Building Products, LLC

Styrofoam is a Trademark of the DOW Chemical Company OlyBond is a Trademark of OMG, Inc.

This specification represents the applicable information available at the time of its publication. Owners, specifiers and Carlisle authorized roofing applicators should consult Carlisle or their Carlisle Manufacturer's Representative for any information that has subsequently been made available. Review the appropriate Carlisle warranty for specific warranty coverage, terms, conditions and limitations.



Sure-Seal® Design "B" Loose-Laid Ballasted Roofing Systems "Attachment I" Ballast Criteria

July 2025

A. General

The specifier must evaluate the various conditions by which the ballast requirements are dictated. Building height, parapet height and project wind zone are major factors when specifying a minimum ballast requirement. The guidelines for ballast requirements which have been published by the following organizations should be referenced:

- 1. American National Standards Institute, ANSI/SPRI RP-4 (current edition) Wind Design Guide for Ballasted Single-Ply Roofing Systems. This standard is referenced in the current edition of the International Building Code (IBC).
- 2. Factory Mutual (FM) Research Corporation Loss Prevention Data Sheets 1-28 and 1-29.

B. Ballast Types/Coverage Rates

The coverage rates listed below are considered minimum and are required by Carlisle for the issuance of the Carlisle warranty. Additional ballast coverage rates may be specified to provide additional wind uplift resistance.

- Rounded Water-Worn Gravel may be placed directly on the EPDM membrane without additional membrane protection.
 - a. Minimum acceptable gradation:
 - Nominal 1-1/2" rounded water worn gravel which conforms to the following gradation: 50% retained by a 3/4" screen, 95% retained by a 1/2" screen and 98% retained by a 1/4" screen. Use ASTM C136 method for sizing gravel.
 - 2) Alternately, #4, #3 and #24 stone (sized in accordance with ASTM D7765 method of sizing) may be used in lieu of the stone listed above.
 - 3) Coverage rate shall be no less than 1000 pounds per 100 square feet and ballast must be evenly distributed to maintain an average of 10 pounds per square foot.
 - b. Nominal 2-1/2" rounded water worn gravel which conforms to gradation #1 or #2 when sized in accordance with ASTM D7765 method of sizing. Coverage rate shall be no less than 1300 pounds per 100 square feet and gravel must be evenly distributed to maintain an average of 13 pounds per square foot.

2. Standard sizes of coarse aggregate - Based on ASTM D7655

Size Number	1	2	3	4
Nominal Size Square Openings	3-1/2" to 1-1/2"	2-1/2" to 1-1/2"	2" to 1"	1-1/2" to 3/4"
Α	mounts Passing Each	Lab Sieve (Square	Opening), Percent	(%)
4"	100			
3-1/2"	90 to 100			
3"		100		
2-1/2"	25 to 60	90 to 100	100	
2"		35 to 70	90 to 100	100
1-1/2"	0 to 15	0 to 15	0 to 15	90 to 100
1"				20 to 55
3/4"	0 to 5	0 to 5		0 to 15
1/2"			0 to 5	
3/8"				0 to 5

- 3. **Crushed Stone**, when specified, shall conform to the gradations approved for rounded water-worn gravel and must be installed in conjunction with Sure-Seal HP Protective Mat.
 - a. HP Protective Mat must extend a minimum of 2" above the crushed stone at the perimeter and penetrations, but must be discontinued at scuppers, Dutch gutters and at drain bases.
 - b. A minimum 6" overlap between adjacent sheets of HP Protective Mat must be specified.

4. Individual Concrete Pavers

- a. Individual pavers with a minimum weight of 18 pounds per square foot may be substituted for nominal 1-1/2" stone. Individual pavers with a minimum weight of 22 pounds per square foot may be substituted for nominal 2-1/2" stone.
- b. Individual pavers must be a maximum of two feet square. Unless otherwise required by Carlisle, pavers must weigh no more than 100 pounds per unit to allow for easy removal and replacement.
- c. Individual pavers with a surface other than a steel troweled finish as approved by Carlisle, must be installed over Sure-Seal HP Protective Mat and must be accepted by Carlisle prior to installation.

Elevating pavers should increase life expectancy, reduce freeze/thaw effects and promote more positive drainage. Acceptable pedestals can be specified under corners of pavers to elevate paver.

d. Individual concrete pavers shall be loose laid and butted together with no gaps greater than 1/2".

5. Lightweight Interlocking Concrete Pavers

- a. Depending on the type of lightweight interlocking system, Sure-Seal HP Protective Mat or manufacturer's recommended matting may be required by Carlisle as a protection layer for the membrane. Carlisle must be consulted prior to installation concerning protective matting requirements.
- b. Lightweight interlocking pavers (minimum 10 pounds per square foot) may be substituted for nominal 1-1/2" stone or nominal 2-1/2" stone.
- c. When lightweight interlocking pavers are specified, the respective paver manufacturer must be consulted concerning installation criteria.

CAUTION:

The securement method suggested by the respective interlocking paver manufacturer must be reviewed by Carlisle to determine membrane accessibility. If access to the membrane system is impaired by the paver interlocking mechanism (mechanical clips, strapping, adhesive, etc.), the building owner must assume the responsibility of providing access to the membrane for the purpose of investigation and warranty related repairs.

d. Lightweight Ballast Paver – 2' x 2' x 1.25" weighing 15 lbs/sq. ft.

Walkways

CAUTION: Molded Walkway pads not recommended within 10 feet of the perimeter of the roof on ballasted systems to avoid discontinuation of the primary membrane securement (ballast). In lieu of molded walkway pads, concrete pavers can be used when walkway is to be extended into the perimeter area.

- a. Sure-Seal/Sure-White Pressure-Sensitive Walkway Pads: Sure-Seal (black) or Sure-White (white) molded walkway pads with Pressure Sensitive TAPE used to provide protection for areas of EPDM membrane that are exposed to regular rooftop maintenance.
- b. **Carlisle Sure-Seal Interlocking Rubber Pavers**: A 2' x 2" thick rubber paver weighing approximately 24 pounds per unit, 6 pounds per square foot manufactured from recycled rubber, which provides a resilient, shock absorbing, weather resistant surface. Designed primarily for use as a walkway or on terrace areas offering a environmentally sound design. Paver features bi-directional drainage and freeze/thaw stability. The Sure-Seal Rubber Paver can be installed directly over the EPDM membrane without a separation layer.
- c. **Hanover Pedestal Paver** Used for light traffic areas associated with rooftop or garden roof applications. 2'x2'x2.25" thick precast concrete pavers weighing 22 psf with an elevated clearance of 1/2" from incorporated footing. The pedestal paver can either be installed in conjunction with a separation layer of HP Protective Mat or using Pedestal and shims.

Note: EPDM Pedestal and Leveling Shims – A 3/8" fixed height EPDM rubber pedestal incorporating 1/8" spacer tabs. The pedestal allows pavers to follow the contour of the roof and may be combined with 1/8" or 1/16" leveling shims to prevent paver movement and provide a more stable feel. Both Hanover Pavers and leveling shims are available from Carlisle. (Refer to product section **Spec Supplement P-01 "Related Products"**.)

d. **Hanover Ballast and Lightweight Ballast Paver** - The standard, 24" x 24" x 1-13/16" thick, Ballast Paver comes in a natural color and a non-slip Diamond finish and weighs 22 lbs/sq. ft. The Lightweight, 23-1/2" x 23-1/2" x 1-1/4" thick, Ballast Paver comes in a natural color and a non-slip diamond finish and weighs 15 lbs/sq. ft. Both pavers can be used as ballast or walkways.

e. Other Walkway Considerations:

Smooth concrete pavers when specified in conjunction with insulation that is mechanically fastened, must be loose laid over a slip sheet of membrane or 2 layers of HP Protective Mat. When insulation is attached with Flexible FAST Adhesive, concrete pavers may be placed over one layer of HP Protective Mat. Pavers cannot weigh more than 100 pounds per paver for ease of removal.

- 1. Walkways are considered a maintenance item and are excluded from the Carlisle warranty.
- 2. Window washing equipment will require special maintenance. Runways or window washing tracks must be utilized to prevent damage to membrane or insulation. Such details must be reviewed by Carlisle to determine reasonable access to the membrane and associated insulation/underlayment components.

END OF SECTION



Sure-Seal®/Sure-White®/Sure-Tough™ EPDM Roofing Systems Adhered, Ballasted and Mechanically Fastened

"Attachment II" 25/30 Year Warranty Design Enhancements

July 2025

Information contained in this Attachment outlines necessary enhancements required for projects where a 25 or 30-year Warranty is specified. At the applicator's or specifier's discretion, projects may be forwarded to Carlisle for warranty review prior to installation or bid.

Sec	ction	Page
A.	General	58
В.	Membrane Criteria	58
	Non-Reinforced Membrane Criteria and Hail Coverage Table	59
	Reinforced Membrane Criteria and Hail Coverage Table	60
C.	Adhered System Design Criteria	61
D.	Mechanically Fastened System Design Criteria	62
E.	Ballasted System Design Criteria	64
F.	Roof Deck Criteria	65
G.	Flashing/Terminations	66

A. General

- 1. All products specified for these roofing assemblies must be products manufactured or marketed by Carlisle.
- 2. On retrofit projects, all existing roofing material shall be totally removed.
- 3. All projects, a final shop drawing shall be approved by Carlisle prior to installation. Shop drawings must include all pertaining details. As-Built projects are not recommended.
- 4. The roof assembly will vary based on warranty wind speed and hail coverage. As identified in Warranty Tables, included in this attachment.
- 5. An air/vapor barrier shall be used when required and must be sealed around perimeter and roof penetrations. When not specified, the roof membrane shall be adhered over perimeter wood nailer along edges to prevent air infiltration along edging, regardless of assembly type (Ballasted, Adhered and Mechanically Fastened).
- 6. Due to warranty length, covered in this attachment, special consideration should be given to the total R-Value of the roof assembly. Utilizing the International Energy Conservation Code (IECC) to determine the minimum level of insulation for the building project's location is recommended.
- 7. To optimize energy efficiency, insulation shall be installed in multiple layers with joints staggered.
- 8. For limitations and specific types of insulation/underlayments refer to "Section E Insulation/Underlayments"
- 9. 1/4" per horizontal foot slope is preferred; however, 1/8" slope with sufficient number of drains and crickets / saddles may be accepted. Assemblies described in this attachment are governed by the maximum slope limit described in the current Carlisle publication.
- Refer to Spec Supplement E-02 "EPDM Membrane Splicing and Splice Repairs" and applicable Carlisle Details for additional design enhancements.

B. Membrane Criteria

Adhered Roofing Systems, the roofing membrane shall be a minimum of 60-mil thick Sure-Seal/Sure-White Non-Reinforced Membrane utilizing enhanced details for 25 Year Warranty Duration

OR

90-mil Sure-Seal Non-Reinforced Membrane OR 75-mil thick Sure-Tough Reinforced Membrane utilizing enhanced details for 30 Year Warranty Duration.

 Ballasted Roofing Systems, the roofing membrane shall be a minimum of 60-mil thick Sure-Seal Non-Reinforced Membrane utilizing enhanced details for 30 Year Warranty Duration

OR

90-mil thick Sure-Seal Non-Reinforced Membrane utilizing enhanced details for **30 Year Warranty** Duration. Maximum membrane width, not to exceed 10' wide.

 Mechanically Fastened Roofing Systems, the roofing membrane shall be a minimum of 75-mil thick Sure-Tough Reinforced Membrane utilizing enhanced details for 25- or 30-Year Warranty Duration.

4. Non-Reinforced Membrane Criteria and Hail Coverage

	Sure-Seal or Sure-White Non-Reinforced Membranes									
	Warranty Wind Speed Coverage									
Years	55, 72 c	or 80 mph	90 to 100 mph	110 to 120 mph	Minimum Membrane	Hail Coverage				
	Adhered (2)	Ballasted (1)	Adhered (2)	Adhered (2)	Thickness					
25 year	NA	√	NA	NA	Sure-Seal 45- mil	Adhered Systems: 1" Dia. Hail Coverage requires a min. 60-mil Adhered to Cover Board. 2" Dia. Hail Coverage requires a min. 90-mil				
25 year	~	NA	√	NA	Sure-Seal / Sure-White 60- mil	Additional Design Requirement: Cover Board set in Flexible FAST Adhesive (SecurShield HD, SecurShield HD Plus,				
30 year	NA	~	NA	NA	Sure-Seal 60- mil	DensDeck Prime, DensDeck StormX Prime, Securock, Securock Ultralight Coated Glass Mat Board – Adhered Only.) Ballasted Systems:				
30 year	~	√	√	NA	Sure-Seal / Sure-White 90- mil	(Sure-Seal) 1" Dia. Hail Coverage requires a min. 45-mil. 2" Dia. Hail Coverage requires a min. 60-mil. 3" Dia. Hail Coverage requires a min. 90-mil				

Notes:

N/A = Not Acceptable

✓ = Acceptable

Sure-White membrane is not recommended for ballasted systems.
 Standard 90-8-30A, EPDM x-23 Low-VOC, or CAV-GRIP III Bonding Adhesive must be utilized.

5. **Reinforced Membrane Criteria and Hail Coverage**

	Tremioree	Sure-Tough Reinforced Membranes									
		Wa	arranty Wind	Speed Cove							
Years	55, 72 o	r 80 mph	90 to 100 mph		110 to 120 mph		Minimum Membrane	Hail Coverage			
	Adhered (1)	Mech. Fastened	Adhered (1)	Mech. Fastened	Adhered (1)	Mech. Fastened	Thickness				
25 year	√	✓	•	√	NA	NA	Sure- Tough 75- mil	Adhered Systems: 1" Dia. Hail Coverage requires a min. 60-mil Adhered to Cover Board. 2" Dia. Hail Coverage requires a min. 75-mil Adhered to Cover Board. Additional Design Requirement: Cover Board set in Flexible FAST Adhesive (SecurShield HD, SecurShield HD Plus, DensDeck Prime, DensDeck StormX Prime, Securock, DEXcell Glass Mat®, DEXcell FA™, DEXcell® Cement Roof Board, or DEXcell FA VSH®, Securock Ultralight Coated Glass Mat Board – Adhered Only.)			
30 year	√	√	√		NA		Sure- Tough 75- mil	Ballasted Systems: (Sure-Seal) 1" Dia. Hail Coverage requires a min. 45-mil. 2" Dia. Hail Coverage requires a min. 60-mil. 3" Dia. Hail Coverage requires a min. 90-mil			

EPDM 7/2025 62

Notes: N/A = Not Acceptable ✓ = Acceptable
(1) Standard 90-8-30A, EPDM x-23 Low-VOC, or CAV-GRIP III Bonding Adhesive must be utilized.

C. Adhered System Design Criteria (25 YR to 30 YR Warranty)

- 1. Building height shall not exceed 100'. For projects where building height exceeds 100' or warranty wind speed exceeds 100 mph, please submit to Carlisle for review.
- 2. All Field Splice "T-Joints" must be overlaid as described in **Detail U-2A.1**.
- 3. The criteria is for compliance with Carlisle's requirements for warranty, when FM Compliance is required for a specific project refer to FM Documentation and Carlisle Code Listings.
- 4. 6" on center fastening required for Pressure Sensitive RUSS.
- 5. New or Tear-off applications for Steel Decks: Cover boards must be installed over minimum 1" thick approved Carlisle insulation.
- 6. Table below outlines insulation/underlayment requirements and application attachment methods:

Maximum	Minimum Membrane Underlayment		Insulation/	Underlaymen	t Attachment		
Peak Gust Wind Speed Warranty			# of Fasteners per 4' x 8' Adhesive Ribbon Spacing for 4' x 4' size board			Metal Edging	
vvarranty			board size	Field	Perimeter		
	_	1-1/2" to 2" (25 psi) Polyisocyanurate (1)					
	ation	ation	1/2" HP Recovery Board (2)(6)				SecurEdge Drip Edge
	Cover Board over Insulation	1/2" SecurShield HD or 1/2" SecurShield HD Eco (3)				Edge may be fastened with ring shank nails staggered 4" on center.	
55 or 72 MPH	o p	1/2" SecurShield HD Plus (3)	16	6" (4)	6"	Carlisle HP or HP-X	
	Boar	1/4" DensDeck Prime (3)				Fasteners may also be used fastened 12" on	
	Cover	1/4" Securock and 1/4" Securock Ultralight Coated Glass-Mat (3)				center.	
		1/4" DEXcell Glass Mat [®] or 1/4" DEXcell FA™(3)					
	ation	1-1/2" to 2" (25-psi) SecurShield Polyiso or 1-1/2" to 2" (25-psi) SecurShield Eco	20				
	er Insula	1/2" SecurShield HD or 1/2" SecurShield HD Eco (3)	16			SecurEdge Drip Edge	
80 MPH	H H Cover Board over Insulation	1/2" SecurShield HD Plus (3)	16	6"	6"	(5), SecurEdge EX Drip	
		1/2" DensDeck Prime (3) 1/2" Securock and 1/2" Securock				Edge	
		Ultralight Coated Glass-Mat (3)	16				
	Š	1/2" DEXcell Glass Mat [®] or 1/2" DEXcell FA™ (3)	20				
	a	1/2" SecurShield HD or 1/2" SecurShield HD Eco (3)	24				
	Cover Board over Insulation	1/2" Securock and 1/2" Securock Ultralight Coated Glass-Mat (3)		FS			
90 MPH	r Boa		1/2" DensDeck Prime (3)		FS	SecurEdge EX Drip Edge	
	Cover	1/2" DEXcell Glass Mat [®] or 1/2" DEXcell FA™(3)					
		1/2" SecurShield HD Plus (3)	20				
		5/8" DensDeck Prime or 5/8" DensDeck StormX Prime (3)					
	Ę	5/8" Securock and 5/8" Securock					
	ılatic	Ultralight Coated Glass-Mat (3)					
	Insu	1-1/2" StormBase (OSB/Polyiso Composite) (3)					
100 MPH	over	1/2" EcoStorm VSH (3)	16	FS	FS	SecurEdge EX Drip Edge	
	Cover Board over Insulation	5/8" DEXcell Glass Mat [®] , 5/8" DEXcell FA™, 5/8" DEXcell [®] Cement Roof					
	over	Board or 5/8" DEXcell FA VSH [®] (3)					
	J	2" SecurShield HD Composite (3)					
		1/2" SecurShield HD Plus (3)	24				

Notes:

FS = Full Spray or Ribbons @ 4" O.C.

All Carlisle Products listed for higher wind speed coverage can also be used for Warranties for lower speed coverage. (i.e. 72 MPH underlayment may be used for 55 MPH underlayment)

- (1) Not for use directly on concrete decks when adhesion is specified to the structural deck.
- (2) For Building heights between 51'-100', enhance 12'-wide perimeter with 50% more fasteners and plates.
- (3) Hail coverage offered with substrate when Flexible FAST Adhesive is used for cover board attachment.
- (4) Structural Concrete Field @ 12" O.C. / Perimeter @ 6" O.C.
- (5) Carlisle HP or HP-X Fasteners must be used to secure Carlisle Drip Edge to perimeter wood nailers.
- (6) 1/2" Recovery Board limited to 55 mph.

D. Mechanically Fastened System Design Criteria (25 YR to 30 YR Warranty)

- 1. Building height limitation depends on structural deck type. Projects with structural concrete or steel decks are limited to 100' in height. Projects with plywood decks (3/4" min.) are limited to a maximum height of 60' or with Wood plank (1" min.) are limited to a maximum height of 60'. For projects where building height exceeds 100' or warranty wind speed exceeds 100 mph, please submit to Carlisle for review.
- 2. All Field Splice "T-Joints" must be overlaid as described in Detail MF-2D.
- 3. This criteria is for compliance with Carlisle's requirements for extended warranties, when FM Compliance is required for a specific project refer to FM Documentation and Carlisle Code Listings.
- 4. Fasteners covered in this attachment are limited to a length not to exceed 12". Assemblies with Tapered Insulation, requiring longer fasteners than 12", shall be reviewed by Carlisle.
- 5. 6" on center fastening required for Pressure Sensitive RUSS.
- 6. Table below outlines insulation/underlayment requirements and application attachment methods:

Maximum Peak Gust	Maximum Peak Gust Wind Speed Warranty Maximum Deck Type Thickness		Minimum Membrane	Insulation Underlayment Attachment			
Wind Speed					Metal Edging		
Un to 72	Steel, Concrete	< 5"	1-1/2" to 2-1/2" InsulBase, InsulBase Eco, SecurShield Polyisocyanurate or SecurShield Eco		SecurEdge Drip Edge may be fastened with ring shank		
Up to 72 MPH	or Wood Deck	•	'	Overlay 1/2" SecurShield HD or SecurShield HD Eco Cover Board over InsulBase, InsulBase Eco SecurShield Polyisocyanurate or SecurShield Eco	4	nails staggered 4" on center. Carlisle HP or HP-X Fasteners may also be used fastened 12" on center.	
80 MPH	Steel or Concrete Deck	Any Thickness	Overlay 1/2" SecurShield HD or SecurShield HD Eco Cover Board over InsulBase, InsulBase Eco, SecurShield Polyisocyanurate or SecurShield Eco	4	SecurEdge Drip Edge or SecurEdge EX Drip Edge		
90 MPH	Steel or Any Concrete Deck Thickness		Overlay 1/2" SecurShield HD or SecurShield HD Eco Cover Board over InsulBase, InsulBase Eco, SecurShield Polyisocyanurate or SecurShield Eco	4	SecurEdge EX Drip Edge		

Notes:

- (1) Carlisle HP or HP-X Fasteners must be used to secure Carlisle Drip Edge to perimeter wood nailers.
- (2) An air/vapor barrier shall be used when required and must be sealed around perimeter and roof penetrations. When not specified, the roof membrane shall be adhered over perimeter wood nailer along edges to prevent air infiltration along edging, regardless of assembly type.

(Sure-Tough Only) 22 GA. Steel Deck or Structural Concrete

		Min. Number of Perimeter Sheets					Fastening	Fastening
Peak Gust Wind Speed	Max. Building	Building Distance from Coastline			Field Membrane	Perimeter Sheet	Density (Field	Density (Perimeter
Warranty	Height	Greater than 7 miles	3 to 7 miles	Less than 3 miles	Width	Width	Sheets)	Sheets)
SE MOU	Up to 60'	2	3	4	10'	Note 3	12" O.C. (1)	12" O.C. (1)
55 MPH	61' to 100'	3	3	4	10'	Note 3	6" O.C. (1)	6" O.C. (1)
	Up to 60'	3	3	4	10'	Note 3	6" O.C. (1)	6" O.C. (1)
72 MPH	61' to 100'	4	5	5	10'	Note 3	6" O.C. (1)	6" O.C. (1)
00 11011	Up to 60'	4	4	5	10'	Note 3	12" O.C. (2)	12" O.C. (2)
80 MPH	61' to 100'	4	5	5	10'	Note 3	12" O.C. (2)	12" O.C. (2)
OO MDU	Up to 60'	4	5	5	10'	Note 3	12" O.C. (2)	12" O.C. (2)
90 MPH	61' to 100'	5	5	5	10'	Note 3	12" O.C. (2)	6" O.C. (2)

- (1) Using HP Fasteners on Steel Deck with 2" Polymer Seam Plates
 (2) Using HP-Xtra Fasteners and 2-3/8" Polymer (HP-Xtra) Seam Plates
 (3) Split Field sheet using a 9" Pressure Sensitive RUSS along the center of the sheet.

(Sure-Tough Only) Wood Decks

Peak Gust Wind Speed	Projected Deck Type Pull-Out		Min. Number of Perimeter Sheets Building Distance from Coastline		Field Membrane	Perimeter Sheet	Fastening Density (Field &	
Warranty	ï	Values	Greater than 7 miles	Less than or equal to 7 miles	Width	Width	Perimeter Sheets)	
55 MPH	3/4" Plywood (2)	450 lbs	2	2	10'	Note 1	12" O.C.	
72 MPH	Wood Plank (2)	540 lbs	2	2	10'	Note 1	12" O.C.	
/2 WPH	3/4" Plywood (2)	450 lbs	2	4	10'	Note 1	12" O.C.	
80 MPH	Wood Plank (2)	540 lbs	2	4	10'	Note 1	6" O.C.	

- (1) Split Field sheet using a 9" Pressure Sensitive RUSS along the center of the sheet.(2) Maximum Building Height Up to 60'

EPDM 7/2025 65

E. Ballasted Design Criteria (25 YR to 30 YR Warranty)

- 1. Building height shall not exceed 60'. For projects where building height exceeds 60' or warranty wind speed exceeds 80 mph, please submit to Carlisle for review.
- 2. All Field Splice "T-Joints" must be overlaid as described in Detail U-2A.1.
- 3. For applicable membrane thickness, refer to Tables in Section B4.
- 4. 6" on center fastening required for Pressure Sensitive RUSS.

General

1. Carlisle Polyisocyanurate or Insulfoam EPS Insulation shall be applied in multiple layers with joints staggered between layers, following current energy codes. The layer directly under the membrane shall be 1-1/2" thick insulation and shall be loose-laid or, if specified, may be secured with bead adhesive (12" O.C. bead spacing is acceptable).

CAUTION: The use of Mechanically Fasteners is not permitted for insulation securement.

Polyisocyanurate Insulation

1. When Polyisocyanurate insulation is specified, Carlisle InsulBase or SecurShield (20 or 25 psi) shall be utilized and is recommended. On structural and lightweight structural concrete, to safeguard against residual moisture, the use of SecurShield Polyisocyanurate is required.

Expanded Polystyrene (EPS) Insulation

- 1. When EPS (Expanded Polystyrene) insulation is to be utilized, only Insulfoam EPS may be used as follows:
 - a. Insulfoam I (1.0 pcf density) EPS.
 - b. Insulfoam VIII (1.25 pcf density) EPS.
- 2. On steel decks, install EPS insulation in conjunction with thermal barrier, if required for code compliance.
- 3. When directly installed on steel deck, total thickness of insulation must be adequate to span deck flutes.

Ballast Types/Coverage Rates

- a. The coverage rates listed in this attachment are considered minimum and are required by Carlisle for issuance of the standard Carlisle warranty. Depending on specific project conditions (building height, parapet height and project location), additional ballast may be necessary to provide wind uplift protection. Refer to "Attachment I" in this Specification for suitable ballast types and coverage rates. Comply with the specifier's requirements when an additional ballast coverage rate is specified.
- b. **Rounded Water-Worn Gravel** must be applied over the EPDM membrane at the minimum rate of **1000 pounds per square** and must be evenly distributed to maintain an average of 10 pounds per square foot.

ASTM D 7765 SIZE NUMBER	MINIMUM COVERAGE RATE (pounds per square)	AVERAGE COVERAGE RATE (lbs./sq. ft. continuously distributed)
4 (1-1/2" nominal diameter)	1000	10
3 (2" nominal diameter)	1000	10
2 (2-1/2" nominal diameter)	1300	13
1 (3-1/2" nominal diameter)	1300	13

Notes: In the field of the roof, some bare spots resulting from installation are permitted; however, they must not exceed 64 square inches and must be limited to no more than 2 per square (100 square feet). No bare spots are permitted in the perimeter area of the roof that is 10' wide.

c. Smooth Surfaced Individual Concrete Pavers

1) When the use of concrete paver is specified, Carlisle supplied Hanover Pedestal Paver is recommended and can


be covered by the Carlisle Warranty. A pedestal system is recommended, due to increased life expectancy, however, field fabricated, cut sections (8" x 8") of Sure-Seal/Sure-White Walkway Pads, beneath pavers, at corners of pavers.

- 2) Individual pavers must be a maximum of two feet square. Unless otherwise required by Carlisle, pavers must weigh no more than 100 pounds per unit to allow for easy removal and replacement.
- 3) Individual pavers with a surface other than a steel troweled finish as approved by Carlisle, must be installed over Sure-Seal HP Protective Mat and must be accepted by Carlisle prior to installation.
- 4) Elevating pavers should increase life expectancy, reduce freeze/thaw effects and promote more positive drainage. Acceptable pedestals can be specified under corners of pavers to elevate paver.
- 5) Individual concrete pavers shall be loose laid and butted together with no gaps greater than 1/2".

Ballast Criteria for Up to 30 Year Extended Warranty


b. Refer to installations below for calculating corner/perimeter areas for the noted warranty wind speeds available.

Ballast Requirements for 72 mph Warranty



A (Corners) = .4 Times the Building Height (10' minimum)

Ballast Requirements for 80 mph Warranty



- A (Corners) = .4 Times the Building Height (10' minimum)
- B (Perimeters) = 10'
- At corner and/or perimeter areas, ballast shall be 2-1/2" nominal rounded water worn gravel conforming to gradation #1 or #2 in accordance with ASTM D7765 method of sizing. Coverage rate shall be a minimum of 15 pounds per square foot.
- 3. In field areas, ballast shall be 1-1/2" nominal rounded water worn gravel conforming to gradation #4 in accordance with ASTM-D7765 method of sizing. Coverage rate shall be a minimum of 12 pounds per square foot.
- 4. Other ballasting configurations may be authorized by Carlisle, upon review and approval, prior to construction.

F. Roof Deck Criteria

 Steel (22-gauge or heavier) – HP, HP-X, HP-Xtra or InsulFAST Fasteners are required, with a minimum pullout of not less than 360 pounds per fastener for adhered systems and 425 pounds per fastener for mechanically fastened systems.

NOTE: Carlisle InsulFAST fasteners may be used with adhered systems only, if the minimum pullout requirement is met.

2. Structural Concrete (minimum 3,000 psi) – HD 14-10 (threaded) Fasteners are required with a minimum pullout of 800 pounds per fastener. Sure-Seal CD-10 (hammer-driven) is also applicable for adhered membrane assemblies. In lieu of fastening, Flexible Adhesive is an acceptable alternative for insulation attachment for adhered assembly when used in conjunction with coated glass faced insulation and full spray.

NOTE: The use of standard (paper) faced Polyisocyanurate is not acceptable. Due to possible presence of residual

moisture in concrete slabs.

3. Wood Plank (minimum 1" thick) or minimum 3/4" thick Plywood – HP, HP-X, HP-Xtra or InsulFAST Fasteners are required with a minimum pullout of 425 pounds for plywood and wood plank; 450 pounds for mechanically fastened systems. The minimum pullout value for adhered systems is 360 pounds per fastener.

NOTE: Carlisle InsulFAST fasteners may be used with adhered systems only, if the minimum pullout requirement is met

4. For **Ballasted Assemblies**, the structural deck must be able to sustain the weight of a ballasted assembly (12-15 lbs of ballast, as well as other components, i.e. membrane, insulation and vapor barriers, if applicable). The structural deck must be sufficient to support concentrated construction traffic and point loading.

G. Flashing, Terminations and Other Considerations (All Assemblies)

- 1. All existing flashing must be removed prior to the application of new membrane. New membrane flashing must not conceal weep holes or cover existing through wall counterflashing.
- 2. Wall flashings shall extend above the anticipated slush line, above the roof surface, prior to written approval from Carlisle is required for lower heights of flashing.
- 3. Pre-fabricated accessories must be utilized, where applicable.
- 4. Project details must be reviewed by Carlisle, preferably prior to bid, and a written approval must be obtained. As a warranty prerequisite, the approval shall be included as part of the project submittals along with the Request for Warranty form that is required for project approval.
- 5. Only Carlisle supplied Sheet Metal and Edging is to be used on all projects, unless prior authorization from Carlisle has been obtained.
- 6. Carlisle Termination Bar is required in locations where a compression bar termination has been specified. The Termination Bar must be used in conjunction with new or existing counterflashing.
- 7. Where new or existing counterflashing is used, Carlisle's Termination Bar must be used as the primary termination.
- 8. Certain metal accessories by others may be permitted upon Carlisle acceptance for wind speed coverage less than 72 mph.





Sure-Seal®/Sure-White®/Sure-Tough™ EPDM Roofing Systems Adhered, Ballasted and Mechanically Fastened

Installation Details


TABLE OF CONTENTS


July 2025

Carlisle SecurEdge Snap-on Canted Fascia. B-1A Mechanically Fastened Carlisle SecurEdge Snap-on Canted Fascia. Mechanically Fastened EPDM Securement – Option 1. Mechanically Fastened EPDM Securement – Option 1. Mechanically Fastened EPDM Securement – Option 2 (RUSS). MF-2.2 Mechanically Fastened EPDM Securement – Option 3 (RUSS). MF-2.2 Mechanically Fastened EPDM Membrane Splice MF-2.4 Mechanically Fastened EPDM Membrane Splice (30 Year Warranty). MF-2.4 Mechanically Fastened EPDM Membrane Splice Intersection (30 Year Warranty) MF-2.8.1 Mechanically Fastened EPDM Membrane Splice Intersection (30 Year Warranty) MF-2.8.1 Mechanically Fastened EPDM Membrane Splice Intersection (30 Year Warranty) MF-2.8.1 Mechanically Fastened EPDM Membrane Splice Intersection (30 Year Warranty) MF-2.8.1	Ballasted	Detail
Mechanically Fastened Carlisle SecurEdge Snap-on Canted Fascia		
Carlisle SecurÉdge Snap-on Canted Fascia MF-1A Mechanically Fastened EPDM Securement – Option 1 MF-2.1 Mechanically Fastened EPDM Securement – Option 2 (RUSS) MF-2.2 Mechanically Fastened EPDM Membrane Splice MF-2.4 Mechanically Fastened EPDM Membrane Splice (30 Year Warranty) MF-2A-1 Mechanically Fastened EPDM Membrane Splice (30 Year Warranty) MF-2A-1 Mechanically Fastened EPDM Membrane Splice Intersection MF-2B-1 End Lap Splice MF-2B-1 Roof Drain with Sump Exceeding 3" Per Foot MF-2B-1 Fressure-Sensitive Pipe Seal with 20" Pressure-Sensitive Cured Flashing MF-8A Fressure-Sensitive Pipe Seal with 20" Pressure-Sensitive Cured Flashing MF-8A Ridge Membrane Attachment MF-22 Metal Edges and Gravel Stops Sartisle SecurEdge Snap-on Canted Fascia JU-1A Carlisle SecurEdge Snap-on Canted Fascia JU-1A Carlisle SecurEdge Snap-on Canted Fascia (30 Year Warranty) JU-1B Carlisle SecurEdge Snap-on Canted Fascia & SecurEdge Snap-on Fascia JU-1C Carlisle SecurEdge Snap-on Fascia & SecurEdge Snap-on Fascia JU-1C Carlisle SecurEdge Snap-on Fascia & SecurEdge Snap-on Fascia JU-1C SecurEdge Drip Edge JU-1	Deck-to-Deck Expansion south	D-0/-
Mechanically Fastened EPDM Securement — Option 2 (RUSS) MF-2.2 Mechanically Fastened EPDM Securement — Option 3 (RUSS) MF-2.2 Mechanically Fastened EPDM Securement — Option 3 (RUSS) MF-2.23 Mechanically Fastened EPDM Membrane Splice MF-2.24 Mechanically Fastened EPDM Membrane Splice Intersection MF-2.21 Mechanically Fastened EPDM Membrane Splice Intersection MF-2.21 Mechanically Fastened EPDM Membrane Splice Intersection (30 Year Warranty) MF-2.21 End Lap Splice MF-2.21 Roof Drain with Sump Exceeding 3° Per Foot MF-88 Pressure-Sensitive Pipe Seal MF-88 Pressure-Sensitive Pipe Seal with 20° Pressure-Sensitive Cured Flashing MF-80 Pressure-Sensitive Pipe Seal with 20° Pressure-Sensitive Cured Flashing MF-80 Ridge Membrane Attachment MF-80 Metal Edges and Gravel Stops U-1A Carlisle SecurEdge Snap-on Canted Fascia U-1A Carlisle SecurEdge Snap-on Canted Fascia (30 Year Warranty) U-1A Carlisle SecurEdge Snap-on Fascia & SecurEdge Snap-on Fascia U-1C Carlisle SecurEdge Opip Edge (30 Year Warranty) U-1C SecurEdge Drip Edge (30 Year Warranty) U-		
Mechanically Fastened EPDM Securement — Option 3 (RUSS) MF-2.2 Mechanically Fastened EPDM Securement — Option 3 (RUSS) MF-2.3 Mechanically Fastened EPDM Membrane Splice (30 Year Warranty) MF-2A.1 Mechanically Fastened EPDM Membrane Splice (30 Year Warranty) MF-2B.1 Mechanically Fastened EPDM Membrane Splice Intersection (30 Year Warranty) MF-2B.1 Mechanically Fastened EPDM Membrane Splice Intersection (30 Year Warranty) MF-2B.1 Fand Lap Splice MF-2B.1 Roof Drain with Sump Exceeding 3" Per Foot. MF-2B.1 Pressure-Sensitive Pipe Seal MF-6B. Pressure-Sensitive Pipe Seal with 20" Pressure-Sensitive Cured Flashing. MF-8A.1 Field Fabricated Pipe Wrap MF-8B.1 Kidge Membrane Attachment. MF-22 Metal Edges and Gravel Stops Carlisle SecurEdge Snap-on Canted Fascia U-1A.1 Carlisle SecurEdge Snap-on Canted Fascia (30 Year Warranty) U-1A.1 Carlisle SecurEdge Snap-on Fascia & SecurEdge Snap-on Fascia U-1C.2 SecurEdge Drip Edge U-1C.2 SecurEdge Drip Edge (30 Year Warranty) U-1D.1 SecurEdge Drip Edge (30 Year Warranty) U-1D.1 SecurEdge Drip Edge (30 Year Warranty) U-		
Mechanically Fastened EPDM Securement – Option 3 (RUSS) MF-23 Mechanically Fastened EPDM Membrane Splice MF-24 Mechanically Fastened EPDM Membrane Splice MF-26 Mechanically Fastened EPDM Membrane Splice (30 Year Warranty) MF-28.1 Mechanically Fastened EPDM Membrane Splice Intersection MF-28.1 Mechanically Fastened EPDM Membrane Splice Intersection (30 Year Warranty) MF-28.1		
Mechanically Fastened EPDM Membrane Splice (30 Year Warranty) MF-2A.1 Mechanically Fastened EPDM Membrane Splice Intersection MF-2B.1 Mechanically Fastened EPDM Membrane Splice Intersection (30 Year Warranty) MF-2B.1 Mechanically Fastened EPDM Membrane Splice Intersection (30 Year Warranty) MF-2B.1 Roof Drain with Sump Exceeding 3" Per Foot MF-8B.2 Foresure-Sensitive Pipe Seal with 20" Pressure-Sensitive Cured Flashing MF-8A.1 Field Fabricated Pipe Wrap MF-8B.2 Ridge Membrane Attachment MF-8B.2 Metal Edges and Gravel Stops WF-22 Carlisle SecurEdge Snap-on Canted Fascia U-1A.2 Carlisle SecurEdge Snap-on Canted Fascia (30 Year Warranty) U-1A.1 Carlisle SecurEdge Snap-on Canted Fascia (30 Year Warranty) U-1B.1 Carlisle SecurEdge Snap-on Canted Fascia (30 Year Warranty) U-1B.1 Carlisle SecurEdge Snap-on Fascia & SecurEdge Snap-on Fascia U-1C Carlisle SecurEdge Snap-on Fascia & SecurEdge Snap-on Fascia U-1B.1 SecurEdge Drip Edge U-1D.1 SecurEdge Orip Edge (30 Year Warranty) U-1D.1 SecurEdge Gravel Stop U-1D.1 SecurEdge Gravel Stop U-1D.1 <td></td> <td></td>		
Mechanically Fastened EPDM Membrane Splice (30 Year Warranty) MF-2A.1 Mechanically Fastened EPDM Membrane Splice Intersection MF-2B.1 End Lap Splice MF-2B.1 End Lap Splice MF-2B.1 End Lap Splice MF-2B.1 MF-8A Pressure-Sensitive Pipe Seal MF-8A Pressure-Sensitive Pipe Seal MF-8A Pressure-Sensitive Pipe Seal MF-8A Pressure-Sensitive Pipe Seal with 20' Pressure-Sensitive Cured Flashing MF-8A Ridge Membrane Attachment MF-8B Ridge Membrane Attachment MF-2B.1 ME-8B Ridge Sand Gravel Stops Carlisle SecurEdge Snap-on Canted Fascia Carlisle SecurEdge Snap-on Canted Fascia (30 Year Warranty) U-1A.1 Carlisle SecurEdge Snap-on Canted Fascia (30 Year Warranty) U-1B.1 Carlisle SecurEdge Solo (30 Year Warranty) U-1B.1 Carlisle SecurEdge Solo (30 Year Warranty) U-1B.1 Carlisle SecurEdge Solo (30 Year Warranty) U-1C SecurEdge Drip Edge U-1D SecurEdge Drip Edge (30 Year Warranty) U-1B.1 Metal Bar Edge Termination U-1F Membrane Splice EPDM Membrane Splice (30 Year Warranty) U-2A.1 EPDM Membrane Splice Intersection (30 Year Warranty or 90-mil Membrane) U-2B.1 EPDM Membrane Splice Intersection (30 Year Warranty or 90-mil Membrane) U-2B.2 Expansion Joints Expansion Joints Deck-to-Deck Expansion Joint U-3A Deck-to-Deck Expansion Joint U-3B		
Mechanically Fastened EPDM Membrane Splice Intersection (30 Year Warranty) MF-2B.1 Mechanically Fastened EPDM Membrane Splice Intersection (30 Year Warranty) MF-2B.1 MF-2B.1 MF-2B.1 MF-2D.1 MF-2		
Mechanically Fastened EPDM Membrane Splice Intersection (30 Year Warranty) End Lap Splice MF-2D Roof Drain with Sump Exceeding 3" Per Foot. MF-80 Pressure-Sensitive Pipe Seal MF-80 MF-80 Pressure-Sensitive Pipe Seal MF-80 MF-80 MF-80 MF-80 Iside Fabricated Pipe Wrap MF-80 M		
End Lap Splice MF-2D Roof Drain with Sump Exceeding 3" Per Foot MF-6B Pressure-Sensitive Pipe Seal MF-8A Pressure-Sensitive Pipe Seal with 20" Pressure-Sensitive Cured Flashing MF-8A Frield Fabricated Pipe Wrap MF-8B Ridge Membrane Attachment MF-8B Metal Edges and Gravel Stops WF-22 Carlisle SecurEdge Snap-on Canted Fascia U-1A Carlisle SecurEdge Snap-on Canted Fascia (30 Year Warranty) U-1A.1 Carlisle SecurEdge 300 U-1B.1 Carlisle SecurEdge 300 (30 Year Warranty) U-1B.1 Carlisle SecurEdge 300 (30 Year Warranty) U-1B.1 Carlisle SecurEdge Graye Snap-on Fascia & SecurEdge Snap-on Fascia U-1D SecurEdge Drip Edge U-1D SecurEdge Drip Edge (30 Year Warranty) U-1B.1 SecurEdge Drip Edge (30 Year Warranty) U-1D.1 Metal Bar Edge Termination U-1D.1 Metal Bar Edge Termination U-1D.1 Membrane Splices U-2A EPDM Membrane Splice Intersection U-2A EPDM Membrane Splice Intersection U-2A EPDM Membrane Splices at Ang		
Roof Drain with Sump Exceeding 3" Per Foot. Pressure-Sensitive Pipe Seal. Pressure-Sensitive Pipe Seal. MF-8A Pressure-Sensitive Pipe Seal with 20" Pressure-Sensitive Cured Flashing. MF-8A Ridge Membrane Attachment. MF-8B Ridge Sand Gravel Stops Carlisle SecurEdge Snap-on Canted Fascia. U-1A Carlisle SecurEdge Snap-on Canted Fascia (30 Year Warranty). U-1A.1 Carlisle SecurEdge 300. U-1B Carlisle SecurEdge 300 (30 Year Warranty). U-1B.1 Carlisle SecurEdge EX Snap-on Fascia & SecurEdge Snap-on Fascia. U-1C SecurEdge Drip Edge. U-1D SecurEdge Drip Edge (30 Year Warranty). U-1D.1 SecurEdge Gravel Stop. U-1E Metal Bar Edge Termination. U-1F Membrane Splices EPDM Membrane Splice (30 Year Warranty). U-2A.1 EPDM Membrane Splice Intersection. U-2B.2 EPDM Membrane Splice Intersection. U-2B.3 EPDM Membrane Splice Intersection. U-2B.4 EPDM Membrane Splice Intersection. U-2B.5 EPDM Membrane Splice Intersection. U-2B.6 EPDM Membrane Splice Splices at Angle Change. U-2C SAT EPDM Membrane Splices at Angle Change. U-2C Expansion Joints Deck-to-Deck Expansion Joint U-3A.1 Deck-to-Deck Expansion Joint U-3A.1 Deck-to-Wall Expansion Joint U-3B.5 Curb Flashing Curb Flashing - Pressure-Sensitive Curb Wrap with 6" Tape. U-5B Curb Wilashing.		
Pressure-Sensitive Pipe Seal MF-8A Pressure-Sensitive Pipe Seal with 20" Pressure-Sensitive Cured Flashing MF-8A.1 Field Fabricated Pipe Wrap MF-8A Ridge Membrane Attachment MF-8B Metal Edges and Gravel Stops WI-18 Carlisle SecurEdge Snap-on Canted Fascia U-1A Carlisle SecurEdge Snap-on Canted Fascia (30 Year Warranty) U-1A Carlisle SecurEdge 300 U-18 Carlisle SecurEdge Snap-on Fascia & SecurEdge Snap-on Fascia U-1C Carlisle SecurEdge Drip Edge U-10 SecurEdge Drip Edge U-10 SecurEdge Drip Edge (30 Year Warranty) U-10.1 SecurEdge Gravel Stop U-16 Metal Bar Edge Termination U-16 Membrane Splices U-2A EPDM Membrane Splice (30 Year Warranty) U-2A EPDM Membrane Splice Intersection U-2A EPDM Membrane Splice Intersection (30 Year Warranty or 90-mil Membrane) U-2A EPDM Membrane Splices at Angle Change U-2C SAT EPDM Membrane Splices U-2C Expansion Joint U-3A Deck-to-Deck Expansion Joint <t< td=""><td></td><td></td></t<>		
Pressure-Sensitive Pipe Seal with 20" Pressure-Sensitive Cured Flashing		
Field Fabricated Pipe Wrap MF-8B Ridge Membrane Attachment MF-22 Metal Edges and Gravel Stops U-1A Carlisle SecurEdge Snap-on Canted Fascia (30 Year Warranty) U-1A.1 Carlisle SecurEdge 300. U-1B Carlisle SecurEdge 300 (30 Year Warranty) U-1B.1 Carlisle SecurEdge 300 (30 Year Warranty) U-1B.1 Carlisle SecurEdge EX Snap-on Fascia & SecurEdge Snap-on Fascia U-1C SecurEdge Drip Edge U-1D.1 SecurEdge Gravel Stop U-1D.1 Metal Bar Edge Termination U-1E Membrane Splices U-2A EPDM Membrane Splice U-2A EPDM Membrane Splice Intersection U-2A EPDM Membrane Splice Intersection (30 Year Warranty) U-2A EPDM Membrane Splice Intersection (30 Year Warranty or 90-mil Membrane) U-2B EPDM Membrane Splices at Angle Change U-2C SAT EPDM Membrane Splices at Angle Change U-2C Expansion Joints U-3C Deck-to-Deck Expansion Joint U-3A Deck-to-Deck Curbed Roof Expansion Joint U-3A Deck-to-Deck Curbed Roof Expansion Joint <td>Pressure-Sensitive Pipe Seal</td> <td> MF-8A</td>	Pressure-Sensitive Pipe Seal	MF-8A
Ridge Membrane Attachment. MF-22 Metal Edges and Gravel Stops Carlisle SecurEdge Snap-on Canted Fascia		
Metal Edges and Gravel Stops Carlisle SecurEdge Snap-on Canted Fascia U-1A. Carlisle SecurEdge Snap-on Canted Fascia (30 Year Warranty) U-1A.1 Carlisle SecurEdge 300. U-1B.1 Carlisle SecurEdge 300 (30 Year Warranty) U-1B.1 Carlisle SecurEdge EX Snap-on Fascia & SecurEdge Snap-on Fascia U-1D.1 SecurEdge Drip Edge U-1D.1 SecurEdge Drip Edge (30 Year Warranty) U-1D.1 SecurEdge Gravel Stop. U-1E Metal Bar Edge Termination U-1E Membrane Splices U-2A EPDM Membrane Splice (30 Year Warranty) U-2A EPDM Membrane Splice (10 Year Warranty) U-2A EPDM Membrane Splice Intersection. U-2B EPDM Membrane Splice Intersection (30 Year Warranty or 90-mil Membrane) U-2B EPDM Membrane Splices at Angle Change U-2C SAT EPDM Membrane Splices U-2D Expansion Joints U-3A Deck-to-Deck Expansion Joint U-3A Deck-to-Deck Expansion Joint U-3A Deck-to-Wall Expansion Cover U-3A Curb Flashing U-5A		
Carlisle SecurEdge Snap-on Canted Fascia U-1A Carlisle SecurEdge Snap-on Canted Fascia (30 Year Warranty) U-1A.1 Carlisle SecurEdge 300 U-1B.1 Carlisle SecurEdge 300 (30 Year Warranty) U-1B.1 Carlisle SecurEdge EX Snap-on Fascia & SecurEdge Snap-on Fascia U-1C SecurEdge Drip Edge U-1D SecurEdge Drip Edge (30 Year Warranty) U-1D.1 SecurEdge Gravel Stop. U-1E Metal Bar Edge Termination U-1E Membrane Splices EPDM Membrane Splice EPDM Membrane Splice (30 Year Warranty) U-2A.1 EPDM Membrane Splice Intersection U-2B.1 EPDM Membrane Splice Intersection (30 Year Warranty or 90-mil Membrane) U-2B.1 EPDM Membrane Splices at Angle Change U-2C SAT EPDM Membrane Splices U-2D Expansion Joints U-2D Expansion Joints U-3A Deck-to-Deck Expansion Joint U-3A Deck-to-Deck Curbed Roof Expansion Joint U-3B Shear/Expansion Cover U-3C Curb Flashing U-5A Curb Flashing - PPDM Membrane U-5B Curb Vith 20" Wide Pressure-Sensitive Curb Wrap with 6" Tape<	Ridge Membrane Attachment	MF-22
Carlisle SecurEdge Snap-on Canted Fascia U-1A Carlisle SecurEdge Snap-on Canted Fascia (30 Year Warranty) U-1A I Carlisle SecurEdge 300 U-1B I Carlisle SecurEdge 300 (30 Year Warranty) U-1B I Carlisle SecurEdge EX Snap-on Fascia & SecurEdge Snap-on Fascia U-1C SecurEdge Drip Edge U-1D SecurEdge Drip Edge (30 Year Warranty) U-1D I SecurEdge Gravel Stop U-1E Metal Bar Edge Termination U-1E Membrane Splices U-2A EPDM Membrane Splice (30 Year Warranty) U-2A I EPDM Membrane Splice (30 Year Warranty) U-2A I EPDM Membrane Splice Intersection U-2B I EPDM Membrane Splice Intersection (30 Year Warranty or 90-mil Membrane) U-2B I EPDM Membrane Splices at Angle Change U-2C SAT EPDM Membrane Splices U-2D Expansion Joints U-3A Deck-to-Deck Expansion Joint U-3A Deck-to-Deck Curbed Roof Expansion Joint U-3A Deck-to-Wall Expansion Joint U-3B Shear/Expansion Cover U-3C Curb Flashing U-5A Curb Flashing - Pressure-Sensitive Curb Wrap with 6" T	Motel Edges and Gravel Stans	
Carlisle SecurEdge Snap-on Canted Fascia (30 Year Warranty) U-1A.1 Carlisle SecurEdge 300. U-1B Carlisle SecurEdge 300 (30 Year Warranty) U-1B.1 Carlisle SecurEdge EX Snap-on Fascia & SecurEdge Snap-on Fascia U-1C SecurEdge Drip Edge U-1D.2 SecurEdge Drip Edge (30 Year Warranty) U-1D.1 SecurEdge Gravel Stop. U-1E Metal Bar Edge Termination U-1E Membrane Splices EPDM Membrane Splice (30 Year Warranty) U-2A.1 EPDM Membrane Splice (10 Year Warranty) U-2A.1 EPDM Membrane Splice Intersection U-2B.2 EPDM Membrane Splice Intersection (30 Year Warranty or 90-mil Membrane) U-2B.2 EPDM Membrane Splices at Angle Change U-2C.3 SAT EPDM Membrane Splices at Angle Change U-2C.3 Expansion Joints U-2D.2 Expansion Joints U-3A.1 Deck-to-Deck Expansion Joint U-3B.3 Shear/Expansion Cover U-3B.3 Curb Flashing U-5A.2 Curb Flashing - PPDM Membrane. U-5B.2 Curb Flashing - PPDM Membrane. U-5B.2 Curb Flashing - Perssure-Sensitive Curb Wrap with 6" Tape U-5B.2		11.4.4
Carlisle SecurEdge 300 U-18 Carlisle SecurEdge 300 (30 Year Warranty) U-18. Carlisle SecurEdge EX Snap-on Fascia & SecurEdge Snap-on Fascia U-10. Carlisle SecurEdge Drip Edge U-10. SecurEdge Drip Edge (30 Year Warranty) U-1D. SecurEdge Gravel Stop. U-1E Metal Bar Edge Termination U-1E Membrane Splices EPDM Membrane Splice EPDM Membrane Splice (30 Year Warranty) U-2A EPDM Membrane Splice Intersection U-2B EPDM Membrane Splice Intersection (30 Year Warranty or 90-mil Membrane) U-2B EPDM Membrane Splices at Angle Change U-2C SAT EPDM Membrane Splices U-2C SAT EPDM Membrane Splices U-2D Expansion Joints U-2D Deck-to-Deck Expansion Joint U-3A Deck-to-Wall Expansion Joint U-3A Deck-to-Wall Expansion Joint U-3B Shear/Expansion Cover U-3C Curb Flashing EPDM Membrane U-5A Curb Flashing - EPDM Membrane U-5B Curb Vith 20" Wide Pressure-Sensitive Curb Wrap with 6" Tape U-5C </td <td></td> <td></td>		
Carlisle SecurEdge 300 (30 Year Warranty) U-1B.1 Carlisle SecurEdge EX Snap-on Fascia & SecurEdge Snap-on Fascia U-1C SecurEdge Drip Edge U-1D SecurEdge Drip Edge (30 Year Warranty) U-1D.1 SecurEdge Gravel Stop U-1E Metal Bar Edge Termination U-1E Membrane Splices U-2A EPDM Membrane Splice (30 Year Warranty) U-2A.1 EPDM Membrane Splice Intersection U-2B EPDM Membrane Splice Intersection (30 Year Warranty or 90-mil Membrane) U-2B.1 EPDM Membrane Splices at Angle Change U-2B.1 SAT EPDM Membrane Splices U-2B.2 Expansion Joints U-2B.2 Expansion Joints U-3A.1 Deck-to-Deck Expansion Joint U-3A.1 Deck-to-Deck Expansion Joint U-3B.3 Shear/Expansion Cover U-3B.3 Curb Flashing U-5A.2 Curb Flashing - PPDM Membrane U-5A.2 Curb Flashing - PPessure-Sensitive Curb Wrap with 6" Tape U-5B.2 Curb With 20" Wide Pressure-Sensitive Cured Flashing U-5C.2		
Carlisle SecurEdge EX Snap-on Fascia & SecurEdge Snap-on Fascia U-1C SecurEdge Drip Edge U-1D SecurEdge Drip Edge (30 Year Warranty) U-1D.1 SecurEdge Gravel Stop U-1E Metal Bar Edge Termination U-1F Membrane Splices EPDM Membrane Splice (30 Year Warranty) U-2A EPDM Membrane Splice Intersection U-2B EPDM Membrane Splice Intersection (30 Year Warranty or 90-mil Membrane) U-2B.1 EPDM Membrane Splices at Angle Change U-2C SAT EPDM Membrane Splices U-2D Expansion Joints U-3A Deck-to-Deck Expansion Joint U-3A Deck-to-Deck Curbed Roof Expansion Joint U-3A Deck-to-Wall Expansion Gover U-3B Shear/Expansion Cover U-3C Curb Flashing EPDM Membrane Curb Flashing - Pressure-Sensitive Curb Wrap with 6" Tape U-5A Curb With 20" Wide Pressure-Sensitive Curd Flashing U-5C		
SecurEdge Drip Edge (30 Year Warranty) U-1D.1 SecurEdge Gravel Stop		
SecurEdge Drip Edge (30 Year Warranty)		
SecurEdge Gravel Stop		
Metal Bar Edge Termination U-1F Membrane Splices U-2A EPDM Membrane Splice (30 Year Warranty) U-2A.1 EPDM Membrane Splice Intersection U-2B EPDM Membrane Spice Intersection (30 Year Warranty or 90-mil Membrane) U-2B.1 EPDM Membrane Splices at Angle Change U-2C SAT EPDM Membrane Splices U-2D Expansion Joints U-3A Deck-to-Deck Expansion Joint U-3A.1 Deck-to-Deck Curbed Roof Expansion Joint U-3B Shear/Expansion Cover U-3C Curb Flashing U-3C Curb Flashing - EPDM Membrane U-5A Curb Flashing - Pressure-Sensitive Curb Wrap with 6" Tape U-5B Curb With 20" Wide Pressure-Sensitive Cured Flashing U-5B		
Membrane SplicesEPDM Membrane Splice (30 Year Warranty)U-2A.1EPDM Membrane Splice IntersectionU-2B.1EPDM Membrane Splice Intersection (30 Year Warranty or 90-mil Membrane)U-2B.1EPDM Membrane Splices at Angle ChangeU-2CSAT EPDM Membrane SplicesU-2DExpansion JointsU-3DDeck-to-Deck Expansion JointU-3A.1Deck-to-Deck Curbed Roof Expansion JointU-3A.1Deck-to-Wall Expansion JointU-3BShear/Expansion CoverU-3CCurb FlashingCurb Flashing - EPDM MembraneU-5ACurb Flashing - Pressure-Sensitive Curb Wrap with 6" TapeU-5BCurb With 20" Wide Pressure-Sensitive Cured FlashingU-5C		
EPDM Membrane Splice (30 Year Warranty) U-2A.1 EPDM Membrane Splice Intersection U-2B.1 EPDM Membrane Splice Intersection (30 Year Warranty or 90-mil Membrane) U-2B.1 EPDM Membrane Splices at Angle Change U-2C SAT EPDM Membrane Splices U-2D Expansion Joints Deck-to-Deck Expansion Joint U-3A.1 Deck-to-Deck Curbed Roof Expansion Joint U-3A.1 Deck-to-Wall Expansion Joint U-3B. Shear/Expansion Cover U-3C Curb Flashing Curb Flashing Curb Flashing - Pressure-Sensitive Curb Wrap with 6" Tape U-5B Curb With 20" Wide Pressure-Sensitive Cured Flashing U-5C	wetar bar Euge Termination	U-1F
EPDM Membrane Splice (30 Year Warranty) U-2A.1 EPDM Membrane Splice Intersection U-2B.1 EPDM Membrane Splice Intersection (30 Year Warranty or 90-mil Membrane) U-2B.1 EPDM Membrane Splices at Angle Change U-2C SAT EPDM Membrane Splices U-2D Expansion Joints Deck-to-Deck Expansion Joint U-3A.1 Deck-to-Deck Curbed Roof Expansion Joint U-3A.1 Deck-to-Wall Expansion Joint U-3B. Shear/Expansion Cover U-3C Curb Flashing Curb Flashing Curb Flashing - Pressure-Sensitive Curb Wrap with 6" Tape U-5B Curb With 20" Wide Pressure-Sensitive Cured Flashing U-5C	Membrane Splices	
EPDM Membrane Splice Intersection U-2B EPDM Membrane Spice Intersection (30 Year Warranty or 90-mil Membrane) U-2B.1 EPDM Membrane Splices at Angle Change U-2C SAT EPDM Membrane Splices U-2D Expansion Joints U-3A Deck-to-Deck Expansion Joint U-3A.1 Deck-to-Wall Expansion Joint U-3B Shear/Expansion Cover U-3C Curb Flashing U-5A Curb Flashing - Pressure-Sensitive Curb Wrap with 6" Tape U-5B Curb With 20" Wide Pressure-Sensitive Cured Flashing U-5C		U-2A
EPDM Membrane Splice Intersection U-2B EPDM Membrane Spice Intersection (30 Year Warranty or 90-mil Membrane) U-2B.1 EPDM Membrane Splices at Angle Change U-2C SAT EPDM Membrane Splices U-2D Expansion Joints U-3A Deck-to-Deck Expansion Joint U-3A.1 Deck-to-Wall Expansion Joint U-3B Shear/Expansion Cover U-3C Curb Flashing U-5A Curb Flashing - Pressure-Sensitive Curb Wrap with 6" Tape U-5B Curb With 20" Wide Pressure-Sensitive Cured Flashing U-5C	EPDM Membrane Splice (30 Year Warranty)	U-2A.1
EPDM Membrane Splices at Angle Change U-2C SAT EPDM Membrane Splices U-2D Expansion Joints U-3A Deck-to-Deck Expansion Joint U-3A.1 Deck-to-Wall Expansion Joint U-3B Shear/Expansion Cover U-3C Curb Flashing U-5A Curb Flashing - Pressure-Sensitive Curb Wrap with 6" Tape U-5B Curb With 20" Wide Pressure-Sensitive Cured Flashing U-5C	EPDM Membrane Splice Intersection	U-2B
SAT EPDM Membrane Splices U-2D Expansion Joints U-3A Deck-to-Deck Expansion Joint U-3A.1 Deck-to-Wall Expansion Joint U-3B Shear/Expansion Cover U-3C Curb Flashing U-5A Curb Flashing - Pressure-Sensitive Curb Wrap with 6" Tape U-5B Curb With 20" Wide Pressure-Sensitive Cured Flashing U-5C	EPDM Membrane Spice Intersection (30 Year Warranty or 90-mil Membrane)	U-2B.1
Expansion Joints Deck-to-Deck Expansion Joint	EPDM Membrane Splices at Angle Change	U-2C
Deck-to-Deck Expansion Joint		
Deck-to-Deck Expansion Joint	Funancian Idinta	
Deck-to-Deck Curbed Roof Expansion Joint		11.04
Deck-to-Wall Expansion Joint U-3B Shear/Expansion Cover U-3C Curb Flashing Curb Flashing - EPDM Membrane. U-5A Curb Flashing - Pressure-Sensitive Curb Wrap with 6" Tape U-5B Curb With 20" Wide Pressure-Sensitive Cured Flashing U-5C		
Shear/Expansion Cover		
Curb Flashing Curb Flashing – EPDM Membrane		
Curb Flashing – EPDM Membrane	Shear/Expansion Cover	0-3C
Curb Flashing – EPDM Membrane	Curb Flashing	
Curb Flashing - Pressure-Sensitive Curb Wrap with 6" Tape		U-5A
Curb With 20" Wide Pressure-Sensitive Cured Flashing	Curb Flashing - Pressure-Sensitive Curb Wrap with 6" Tape	U-5B


New Self-Flashing Metal Curb	U-5E
Drains	
Roof Drain	
Roof Drain – Reinforced Field Sheet with Sump Exceeding 3" Per Foot	
Sure-Seal Insert Drain	
Insert Drain Through Deck	
Suie-Seal Auu-on Diain	U-0E
Pipe Flashing	11.04
Pressure-Sensitive Pipe Seal	
Field Fabricated Pipe Wrap	
Field Fabricated Pipe Wrap (30 Year Warranty)	
Flexible Penetration	
Field Fabricated Hot Stack	
Field Fabricated Hot Stack (30 Year Warranty)	U-8D.1
Terminations	
Membrane Terminations, Page 1 of 3	U-9
Membrane Terminations, Page 2 of 3	U-9
Membrane Terminations, Page 3 of 3	U-9
Parapet / Curb Flashing	
Parapet / Curb with Continuous Membrane	U-12A
Parapet / Curb with Separate Membrane Flashing	
Parapet / Curb with Continuous Membrane – RUSS	
Parapet / Curb with Separate regular EPDM Flashing	U-12D
Parapet / Curb with Separate SAT Flashing	
Parapet / Curb with Continuous Membrane – Cover Strip	U-12F
Tie-Ins	
Built-Up Roofing Tie-In over Steel Roof Deck	U-13A
Built-Up Roofing Tie-In over Concrete Roof Deck	
Tie-In to Existing EPDM Membrane	
EPDM Tie-In over Concrete Deck	
Tie-In Shingled or Metal Panel Roof Tie-In Between New Carlisle Adhered & Ballasted Roof	
Tie-III Detween New Callisie Auflereu & Dallasteu Nooi	
Inside / Outside Corners Inside Corner Wall Flashing with RUSS (Option 1)	11.454
Inside Corner Wall Flashing with RUSS (Option 1)	
Inside Corner with Continuous EPDM Wall Flashing	II-15C
Inside Corner with Separate EPDM Wall Flashing	
Inside Corner Flashing for Projects with 90-mil Membrane or 30 Year Warranty	
Outside Corner with Pre-Cut Pressure-Sensitive Flashing	
Outside Corner with Pressure-Sensitive Elastoform Flashing (2 Piece)	U-15F
Outside Corner with Pressure-Sensitive Elastoform Flashing (1 Piece)	
Outside Corner Flashing for Projects with 90-mil Membrane or 30 Year Warranty	U-15G.1
Sealant Pocket	
Pressure-Sensitive Pourable Sealer Pocket.	U-16A
Pressure-Sensitive Pourable Sealer Pocket (30 Year Warranty)	
Field Fabricated Pourable Sealer Pocket	
Field Fabricated Pourable Sealer Pocket (30 Year Warranty)	
Extended Pourable Sealer Pocket	
Extended Pourable Sealer Pocket (30 Year Warranty)	U-16C.1
Through-Wall Scupper	
Scupper: Single Layer Flashing	
Scupper: Double Layers of Flashing (Page 1 of 2)	
Scupper: Double Layers of Flashing (Page 2 of 2)	U-18A.1

Lightning Rods Lightning Rod at Parapet (Vertical Attachment)	IJ-20A
Lightning Rod at Deck Level	U-20B
Valley	
Valley	U-22
Sleeper	
Sleeper	U-24
Penetration	
I-Beam Penetration	U-30










(A) NEW CONSTRUCTION OR REROOFING




REROOFING OR RECOVER OF EXISTING ROOF

NOTE:

1. ANY OF U-3 (A, B OR C) EXPANSION JOINT DETAIL CAN BE USED WITH THE "B" SYSTEM (BALLASTED STONE ASSEMBLY)








CARLISLE SecurEdge SNAP-ON CANTED FASCIA


CANTED TASCIA

MAXIMUM WARRANTY: 30 YEARS



MF-1A






- 1. REFER TO CARLISLE SPECIFICATIONS FOR REQUIRED NUMBER OF PERIMETER SHEETS, SHEET WIDTH AND MEMBRANE FASTENING DENSITY.
- HP FASTENERS AND POLYMER SEAM PLATES ARE REQUIRED OVER STEEL DECKS.




MECHANICALLY FASTENED EPDM SECUREMENT - OPTION 1

MAXIMUM WARRANTY: 30 YEARS







REINFORCED

EPDM

DETAIL A

1. REFER TO CARLISLE SPECIFICATIONS FOR REQUIRED NUMBER OF PERIMETER SHEETS, SHEET WIDTH AND MEMBRANE FASTENING DENSITY.

3

- 2. EPDM PRIMER MUST BE APPLIED TO THE BACK SIDE OF MEMBRANE SURFACE PRIOR TO ADHERING MEMBRANE TO PRESSURE-SENSITIVE RUSS.
- 3. HP FASTENERS AND POLYMER SEAM PLATES ARE REQUIRED OVER STEEL DECKS.

RUSS (REINFORCED UNIVERSAL SECUREMENT STRIP)

9" (23cm) WIDE-

RUSS

PRESSURE-SENSITIVE




MECHANICALLY FASTENED EPDM SECUREMENT — OPTION 2 (RUSS)


MAXIMUM WARRANTY: 30 YEARS





MF-2.2




GUIDELINES FOR ROOF PERIMETER









NOTES:

DETAIL A

- 1. REFER TO CARLISLE SPECIFICATIONS FOR REQUIRED NUMBER OF PERIMETER SHEETS, SHEET WIDTH AND MEMBRANE FASTENING DENSITY.
- 2. EPDM PRIMER MUST BE APPLIED TO THE BACK SIDE OF MEMBRANE SURFACE PRIOR TO ADHERING MEMBRANE TO PRESSURE—SENSITIVE RUSS.
- 3. HP FASTENERS AND POLYMER SEAM PLATES ARE REQUIRED OVER STEEL DECKS.
- 4. RUSS "FINGER" MUST EXTEND THE WIDTH OF THE REQUIRED PERIMETER.


RUSS (REINFORCED UNIVERSAL SECUREMENT STRIP)



MECHANICALLY FASTENED EPDM SECUREMENT - OPTION 3 (RUSS)


MF-2.3

MAXIMUM WARRANTY: 30 YEARS




- 1. HP FASTENERS AND POLYMER SEAM PLATES ARE REQUIRED OVER STEEL DECKS.
- 2. OVERLAP THE ENDS OF FIELD APPLIED SecurTAPE A MINIMUM OF 1" (2.5cm). APPLY LAP SEALANT AT TAPE OVERLAPS 2" (5cm) IN EACH DIRECTION AS SHOWN.
- 3. APPLY LAP SEALANT ALONG THE LEADING EDGE OF THE MEMBRANE SPLICE UNDER THE 6" (15cm) T-JOINT COVER, COVERING THE EXPOSED SPLICE TAPE 1/2" (1.5cm) IN ALL DIRECTIONS FROM THE SPLICE INTERSECTION.
- 4. END LAPS SHALL BE SPLICED USING 3" (7.5cm) WIDE SecurTAPE. REFER TO DETAIL MF-2B.
- 5. LAP SEALANT IS REQUIRED ON CUT EDGES OF REINFORCED EPDM MEMBRANE.






- 1. HP FASTENERS AND POLYMER SEAM PLATES ARE REQUIRED OVER STEEL DECKS.
- 2. END LAPS SHALL BE SPLICED USING 6" (15cm) WIDE SecurTAPE. REFER TO DETAIL U-2A.1.
- 3. OVERLAP THE ENDS OF FIELD APPLIED SecurTAPE A MINIMUM OF 1" (2.5cm). APPLY LAP SEALANT AT TAPE OVERLAPS 2" (5cm) IN ALL DIRECTIONS.
- 4. LAP SEALANT IS REQUIRED ON CUT EDGES OF REINFORCED EPDM MEMBRANE.







POSITION MEMBRANE TO ALLOW AN APPROXIMATE 7" (17.5cm) OVERLAP ALONG THE LENGTH OF THE MEMBRANE & 4" (10cm) AT END LAPS. THE PRE-MARKED LINE ON THE MEMBRANE EDGE CAN BE USED AS A GUIDE FOR TAPE PLACEMENT.




SPLICE SHEET B TO SHEET A AND APPLY SECOND PIECE OF SecurTAPE BETWEEN SHEET B AND C. TRIM RELEASE FILM AS SHOWN.



APPLY PRESSURE—SENSITIVE T—JOINT COVER OR 6" (15cm) WIDE SECTION OF PRESSURE—SENSITIVE ELASTOFORM FLASHING CENTERED OVER THE INTERSECTING POINT OF THE LEADING EDGES OF THE FIELD SPLICE INTERSECTION AS SHOWN.



FOLD SHEETS BACK AS SHOWN. APPLY EPDM PRIMER TO THE SPLICE AREA ON BOTH SURFACES AND ALLOW TO FLASH—OFF. APPLY SecurTAPE WITH RELEASE FILM ALIGNED WITH PRE—MARKED LINE.



SPLICE SHEET C TO SHEET A AND B, PRESS TOP SHEET ONTO BOTTOM SHEET USING HAND PRESSURE TOWARDS THE OUTER EDGE OF THE SPLICE AND ROLL THE SPLICE AREA WITH A 2" (5cm) WIDE STEEL ROLLER.

- 1. APPLY LAP SEALANT ALONG THE EDGE OF THE MEMBRANE SPLICE (BELOW THE 6" (15cm) T-JOINT COVER) COVERING THE EXPOSED SPLICE TAPE 1/2" (1.5cm) IN EACH DIRECTION FROM THE SPLICE INTERSECTION.
- 2. APPLY LAP SEALANT AT CUT EDGES OF REINFORCED MEMBRANE AND TAPE OVERLAPS. REFER TO DETAIL MF-2A.




MECHANICALLY FASTENED EPDM MEMBRANE SPLICE INTERSECTION


MAXIMUM WARRANTY: 25 YEARS




DETAIL NO.




POSITION MEMBRANE TO ALLOW AN APPROXIMATE (17.5cm) OVERLAP. THE PRE-MARKED LINE ON THE MEMBRANE EDGE CAN BE USED AS A GUIDE FOR TAPE PLACEMENT.




SPLICE SHEET B TO SHEET A AND APPLY SECOND PIECE OF SecurTAPE BETWEEN SHEET B AND C. TRIM RELEASE FILM AS SHOWN.



APPLY 6"(15cm) PRESSURE-SENSITIVE T-JOINT COVER AND 12"(30cm) PRESSURE-SENSITIVE T-JOINT COVER OR PRESSURE-SENSITIVE ELASTOFORM CENTERED OVER THE INTERSECTING POINT OF THE LEADING EDGES OF THE FIELD SPLICE INTERSECTION AS SHOWN.



FOLD SHEETS BACK AS SHOWN. APPLY EPDM PRIMER TO THE SPLICE AREA ON BOTH SURFACES AND ALLOW TO FLASH-OFF. SecurTAPE WITH RELEASE FILM ALIGNED WITH PRE-MARKED LINE.



SPLICE SHEET C TO SHEET A AND B, PRESS TOP SHEET ONTO BOTTOM SHEET USING HAND PRESSURE TOWARDS THE OUTER EDGE OF THE SPLICE AND ROLL THE SPLICE AREA WITH A 2' (5cm) WIDE STEEL ROLLER.

6"(15cm) PRESSURE-SENSITIVE T-JOINT COVER AND EPDM PRIMER

LAP SEALANT BELOW THE 6" (15cm) T-JOINT COVER

1

NOTES:

- 1. APPLY LAP SEALANT ALONG THE EDGES OF THE MEMBRANE SPLICE COVERING THE EXPOSED SPLICE TAPE 1/2" (1.5cm) IN EACH DIRECTION FROM THE SPLICE INTERSECTION.
- 2. APPLY LAP SEALANT AT CUT EDGES OF REINFORCED MEMBRANE AND TAPE OVER LAPS.




MECHANICALLY FASTENED EPDM MEMBRANE SPLICE INTERSECTION

MAXIMUM WARRANTY: 30 YEARS




DETAIL NO.


MF-2B.1



UP TO 25-YEAR WARRANTY




1 2




- APPLY EPDM PRIMER TO THE MEMBRANE SURFACES PRIOR TO INSTALLING PRESSURE-SENSITIVE FLASHING.
- 2. LAP SEALANT IS REQUIRED ON CUT EDGES OF REINFORCED EPDM MEMBRANE.





- 1. ALL BOLTS OR CLAMPS MUST BE IN PLACE TO PROVIDE CONSTANT COMPRESSION ON WATER CUT-OFF MASTIC.
- 2. REMOVE EXISTING LEAD, FLASHING MATERIAL & ENSURE THE DRAIN RING IS COMPLETELY CLEAN DOWN TO BARE METAL.
- 3. HP FASTENERS AND POLYMER SEAM PLATES ARE REQUIRED OVER STEEL DECKS.
- 4. THE HOLE IN THE MEMBRANE SHALL <u>EXCEED</u> THE DIAMETER OF THE DRAIN PIPE, BUT SHALL BE NO LESS THAN 1/2" (1.5cm) FROM THE ATTACHMENT POINTS OF THE DRAIN CLAMPING RING.
- 5. ROOF DRAIN SIZE AND NUMBER OF DRAINS SHALL BE IN ACCORDANCE WITH THE LOCAL CODES.






ROOF DRAIN WITH SUMP GREATER THAN 3" PER FOOT

MAXIMUM WARRANTY: 30 YEARS




MF-6E



- 1. REMOVE ALL LEAD AND OTHER FLASHING BEFORE INSTALLING PIPE SEAL.
- 2. TEMPERATURE OF PIPE MUST NOT EXCEED 180°F (82°C).
- 3. PRE-MOLDED PIPE SEAL MUST HAVE RIB INTACT AT THE TOP EDGE REGARDLESS OF PIPE DIAMETER.
- 4. INSTALL A MINIMUM OF 4 SEAM PLATES FOR PIPES WITH A DIAMETER UP TO 6" (15cm). ADDITIONAL SEAM PLATES WILL BE REQUIRED FOR PIPES GREATER THAN 6" (15cm) IN DIAMETER AND SHALL BE SPACED 12" (30cm) ON CENTER MAXIMUM.
- 5. HP FASTENERS AND POLYMER SEAM PLATES ARE REQUIRED OVER STEEL DECKS.
- 6. DECK FLANGES OF THE PRESSURE—SENSITIVE PIPE SEAL SHALL NOT BE OVERLAPPED, CUT OR APPLIED OVER ANY ANGLE CHANGE.

√ 3			20.
DIMENSIONS		cm	
A	6"	15	ТО
	12"	30	
B	1/2"	1.5	ТО
	6"	15	






2"

1. REMOVE ALL LEAD AND OTHER FLASHING BEFORE INSTALLING PIPE SEAL.

5

- 2. TEMPERATURE OF PIPE MUST NOT EXCEED 180°F (82°C).
- 3. PRE-MOLDED PIPE SEAL MUST HAVE RIB INTACT AT THE TOP EDGE REGARDLESS OF PIPE DIAMETER.
- 4. INSTALL A MIN. OF 4
 FASTENERS FOR PIPES WITH
 OUTSIDE DIAMETER <6"
 (15cm). SEE DETAIL MF-8B
 OR MF-8B.1 FOR WIDER
 PIPES.
- 5. DECK FLANGES OF THE PRESSURE—SENSITIVE PIPE SEAL SHALL NOT BE OVERLAPPED, CUT OR APPLIED OVER ANY ANGLE CHANGE.







PRESSURE-SENSITIVE PIPE SEAL WITH 20" PRESSURE-SENSITIVE CURED FLASHING

MAXIMUM WARRANTY: 30 YEARS




MF-8A.1





- 1. REMOVE ALL
 LEAD AND OTHER
 FLASHING
 BEFORE
 INSTALLING
 PRESSURE—
 SENSITIVE
 ELASTOFORM
 FLASHING.
- 2. HP FASTENERS
 AND POLYMER
 SEAM PLATES
 ARE REQUIRED
 OVER STEEL
 DECKS.
- 3. FOR STRUCTURAL STEEL TUBING GREATER THAN 12" ACROSS USE U-5 DETAILS.






FIELD FABRICATED PIPE WRAP


MAXIMUM WARRANTY: SEE EACH DETAIL



MF-8E





- 1. RIDGE MEMBRANE ATTACHMENT IS ONLY REQUIRED WHEN ROOF SLOPE EXCEEDS 3" TO THE HORIZONTAL FOOT (7.5cm/30cm).
- 2. REINFORCED EPDM MEMBRANE SHALL BE INSTALLED PARALLEL WITH RIDGE LINE (WITH MEMBRANE CENTERED OVER THE RIDGE LINE) AS SHOWN.
- 3. FOR PROPER MEMBRANE ATTACHMENT AND SPLICING, REFER TO APPLICABLE MF-2 DETAIL.
- 4. REFER TO CARLISLE SPECIFICATIONS FOR REQUIRED NUMBER OF PERIMETER SHEETS, SHEET WIDTH AND MEMBRANE FASTENING DENSITY.
- 5. HP FASTENERS AND POLYMER SEAM PLATES ARE REQUIRED OVER STEEL DECKS.
- 6. AS AN OPTION, 9" (23cm) WIDE PRESSURE-SENSITIVE RUSS MAY BE USED BENEATH EPDM FIELD SHEETS FOR PERIMETER SECUREMENT.




DIMENSIONS		cm	
\bigcirc	3'-6"	110	MIN.
	4'-6"	140	MAX.
\bigcirc B	12"O.C.	30	MAX.







- 1. MAXIMUM MEMBRANE THICKNESS GOING OVER THE WATER DAM IS 60-MIL. FOR THICKER MEMBRANES, RUN FIELD SHEET UNDER THE WATER DAM AND STRIP-IN WITH MAXIMUM 60-MIL MEMBRANE.
- 2. USE MF-1A FOR MECHANICALLY FASTENED SYSTEMS AND B-1A FOR BALLASTED SYSTEMS.






CARLISLE SecurEDGE SNAP-ON CANTED FASCIA


MAXIMUM WARRANTY: 25 YEARS



DETAIL NO.



- FIELD SPLICES AT THE ANGLE CHANGE SHALL BE OVERLAID WITH EPDM PRIMER AND TWO LAYERS OF PRESSURE—SENSITIVE ELASTOFORM FLASHING. PER DETAIL <u>U-2C</u>.
- 2. WHEN AND AIR/VAPOR BARRIER IS NOT SPECIFIED, THE ROOF MEMBRANE SHALL BE ADHERED OVER PERIMETER WOOD NAILER ALONG EDGES TO PREVENT AIR INFILTRATION ALONG EDGING, REGARDLESS OF ASSEMBLY TYPE (BALLASTED, ADHERED AND MECHANICALLY FASTENED).






CARLISLE SecurEdge SNAP-ON

CANTED FASCIA

MAXIMUM WARRANTY: 30 YEARS




DETAIL NO.
1 1 — 1 Δ




1. 6" (15cm) WIDE PRESSURE—SENSITIVE ELASTOFORM FLASHING, IN CONJUNCTION WITH EPDM PRIMER, MUST BE CENTERED OVER FIELD SPLICES AT THE ANGLE CHANGE.













- 1. FIELD SPLICES AT THE ANGLE CHANGE SHALL BE OVERLAID WITH EPDM PRIMER AND 2 LAYERS OF PRESSURE—SENSITIVE ELASTOFORM FLASHING PER DETAIL U-2C.
- 2. WHEN AIR/VAPOR BARRIER IS NOT SPECIFIED, THE ROOF MEMBRANE SHALL BE ADHERED OVER PERIMETER WOOD NAILER ALONG EDGES TO PREVENT AIR INFILTRATION ALONG EDGING, REGARDLESS OF ASSEMBLY TYPE (BALLASTED, ADHERED AND MECHANICALLY FASTENED).










CARLISLE SecurEdge 300


MAXIMUM WARRANTY: 30 YEARS




DETAIL NO.





- 1. IF INCIDENTAL/TEMPORARY PONDED WATER IS EXPECTED, THE SecurEdge MUST BE ELEVATED AND SCUPPERS PROVIDED FOR DRAINAGE.
- 2. ENSURE ROOF SLOPES AWAY FROM SecurEDGE.





- 1. DECK FLANGE MUST BE TOTALLY COVERED WITH MINIMUM 2" (5cm) COVERAGE PAST NAIL HEADS. TO REMOVE FINISHING OILS, SCRUB METAL FLANGE WITH WEATHERED MEMBRANE CLEANER; ALLOW TO DRY PRIOR TO APPLYING PRIMER.
- 2. LAP SEALANT MUST BE APPLIED AT FLASHING OVERLAPS AND INTERSECTIONS WITH JOINTS IN METAL EDGING.
- 3. T-JOINT COVER NOT NEEDED WHEN USING PS OVERLAYMENT STRIP ON MEMBRANE LESS THAN 90-MIL.
- 4. WHEN USING 90-MIL MEMBRANE INSTALL A 12" (30cm) T-JOINT COVER OVER THE 6" (15cm) T-JOINT COVER PER U-2B.1
- 5. DETAIL NOT FOR USE WITH DESIGN "B" (BALLASTED STONE ASSEMBLY).








SecurEdge DRIP EDGE

MAXIMUM WARRANTY: 25 YEARS




DETAIL NO.




- 1. DECK FLANGE MUST BE TOTALLY COVERED WITH MINIMUM 2" (5cm) COVERAGE PAST NAIL HEADS. TO REMOVE FINISHING OILS, SCRUB METAL FLANGE WITH WEATHERED MEMBRANE CLEANER; ALLOW TO DRY PRIOR TO APPLYING PRIMER.
- 2. LAP SEALANT MUST BE APPLIED AT FLASHING OVERLAPS AND INTERSECTIONS WITH JOINTS IN METAL EDGING.
- 3. ALL SPLICE INTERSECTIONS MUST BE OVERLAID WITH PRESSURE—SENSITIVE T—JOINT COVERS AND SEALED WITH CONTINUOUS LAP SEALANT. PRIOR TO DOING SO, APPLY LAP SEALANT ALONG THE LEADING EDGE OF THE MEMBRANE SPLICES (UNDER THE 6"X 6" (15cm X 15cm) T—JOINT COVER) COVERING THE EXPOSED SPLICE TAPE 1/2" (1.5cm) IN ALL DIRECTIONS FROM THE SPLICE INTERSECTION.
- 4. DETAIL NOT FOR USE WITH DESIGN "B" (BALLASTED STONE ASSEMBLY).






- 1. TO REMOVE FINISHING OILS, SCRUB METAL FLANGE WITH WEATHERED MEMBRANE CLEANER; ALLOW TO DRY PRIOR TO APPLYING PRIMER.
- LAP SEALANT MUST BE APPLIED AT FLASHING OVERLAPS AND INTERSECTIONS WITH JOINTS IN METAL EDGING.
- 3. T-JOINT COVER AT SPLICE INTERSECTION NOT NEEDED WHEN USING PS OVERLAYMENT STRIP ON MEMBRANE LESS THAN 90-MIL.
- 4. WHEN USING 90-MIL MEMBRANE INSTALL A 12" (30cm) T-JOINT COVER OVER THE 6" (15cm) T-JOINT COVER PER U-2B.1






- 1. FASTENING OF METAL
 TERMINATION OR BALLAST
 RETAINING BAR MUST PROVIDE
 CONSTANT COMPRESSION ON
 WATER CUT-OFF MASTIC.
- 2. BALLAST RETAINING BAR MUST EXTEND ABOVE GRAVEL SURFACE SUFFICIENTLY TO RETAIN GRAVEL AND PREVENT GRAVEL MIGRATION.
- 3. SLOTS IN BALLAST RETAINING BAR MUST BE FLUSH OR SLIGHTLY BELOW MEMBRANE LEVEL.









- 1. OVERLAP THE ENDS OF THE FIELD APPLIED SecurTAPE A MINIMUM OF 1" (2.5cm). APPLY LAP SEALANT AT TAPE OVERLAPS 2" (5cm) IN EACH DIRECTION AS SHOWN.
- 2. APPLY LAP SEALANT ALONG THE EXPOSED EDGE OF THE MEMBRANE SPLICE COVERING THE EXPOSED SPLICE TAPE 1/2" (1.5cm) IN EACH DIRECTION FROM THE SPLICE INTERSECTION AND OVERLAY WITH A 6" (15cm) T-JOINT COVER.
- 3. WHEN USING 90-MIL MEMBRANE, INSTALL A 12" (30cm) T-JOINT COVER CENTERED OVER THE FIRST T-JOINT COVER PER DETAIL U-2B.1.
- 4. LAP SEALANT IS REQUIRED ON CUT EDGES OF REINFORCED EPDM MEMBRANE.
- 5. REFER TO DETAIL MF-2A FOR MECHANICALLY FASTENED SPLICES.





OPTION 1












F.A.T. (FACTORY APPLIED SecurTAPE)


NOTES:

- APPLY LAP SEALANT AT ALL INTERSECTIONS BETWEEN PRESSURE-SENSITIVE OVERLAYMENT STRIP.
- 2. REFER TO DETAIL MF-2A.1 FOR MECHANICALLY-FASTENED SPLICES.


NOTE:

1. APPLY LAP SEALANT ALONG THE EXPOSED EDGE OF THE MEMBRANE SPLICE COVERING THE EXPOSED SPLICE TAPE 1/2" (1.5cm) IN EACH DIRECTION FROM THE SPLICE INTERSECTION AND OVERLAY WITH A 6" (15cm) T-JOINT COVER. INSTALL A 12" (30cm) T-JOINT COVER CENTERED OVER THE FIRST T-JOINT COVER PER DETAIL U-2B.1.







POSITION MEMBRANE TO ALLOW AN APPROXIMATE 4" (10cm) OVERLAP. MARK THE BOTTOM SHEET WITH AN INDELIBLE MARKER 1/2" (1.5cm) FROM THE EDGE OF THE TOP SHEET AS SHOWN. THE PRE-MARKED LINE ON THE MEMBRANE EDGE CAN ALSO BE USED AS A GUIDE.




SPLICE SHEET B TO SHEET A AND APPLY SECOND PIECE OF SecurTAPE BETWEEN SHEET B AND C. TRIM RELEASE FILM AS SHOWN.



APPLY PRESSURE—SENSITIVE T—JOINT COVER OR 6" (15cm) WIDE SECTION OF PRESSURE—SENSITIVE ELASTOFORM FLASHING CENTERED OVER THE INTERSECTING POINT OF THE LEADING EDGES OF THE FIELD SPLICE INTERSECTION AS SHOWN.



FOLD SHEETS BACK AS SHOWN. APPLY EPDM PRIMER TO THE SPLICE AREA ON BOTH SURFACES AND ALLOW TO FLASH—OFF. APPLY SecurTAPE WITH RELEASE FILM ALIGNED WITH MARKED LINE.



SPLICE SHEET C TO SHEET A AND B, PRESS TOP SHEET ONTO BOTTOM SHEET USING HAND PRESSURE TOWARDS THE OUTER EDGE OF THE SPLICE AND ROLL THE SPLICE AREA WITH A 2" (5cm) WIDE STEEL ROLLER.

- APPLY LAP SEALANT ALONG THE EDGE OF THE MEMBRANE SPLICE BELOW THE 6" (15cm) T-JOINT COVER, COVERING THE EXPOSED SPLICE TAPE 1/2" (1.5cm) IN EACH DIRECTION FROM THE SPLICE INTERSECTION.
- 2. APPLY LAP SEALANT AT CUT EDGES OF REINFORCED MEMBRANE AND TAPE OVERLAPS. REFER TO DETAIL U-2A.
- 3. REFER TO DETAIL U-2B.1 WHEN USING 90-MIL MEMBRANE.




EPDM MEMBRANE SPLICE INTERSECTION


MAXIMUM WARRANTY: 25 YEARS




II - 2R




POSITION MEMBRANE TO ALLOW AN APPROXIMATE 7" (17.5cm) OVERLAP. MARK THE BOTTOM SHEET WITH AN INDELIBLE MARKER 1/2" (1.5cm) FROM THE EDGE OF THE TOP SHEET AS SHOWN. THE PRE-MARKED LINE ON THE MEMBRANE EDGE CAN ALSO BE USED AS A GUIDE.




SPLICE SHEET B TO SHEET A AND APPLY SECOND PIECE OF SecurTAPE BETWEEN SHEET B AND C. TRIM RELEASE FILM AS SHOWN.



APPLY 6" (15cm) PRESSURE—SENSITIVE T—JOINT COVER AND 12" (30cm) PRESSURE—SENSITIVE T—JOINT COVER OR PRESSURE—SENSITIVE ELASTOFORM CENTERED OVER THE INTERSECTING POINT OF THE LEADING EDGES OF THE FIELD SPLICE INTERSECTION AS SHOWN.



FOLD SHEETS BACK AS SHOWN. APPLY EPDM PRIMER TO THE SPLICE AREA ON BOTH SURFACES AND ALLOW TO FLASH-OFF. APPLY SecurTAPE WITH RELEASE FILM ALIGNED WITH MARKED LINE.



SPLICE SHEET C TO SHEET A AND B, PRESS TOP SHEET ONTO BOTTOM SHEET USING HAND PRESSURE TOWARDS THE OUTER EDGE OF THE SPLICE AND ROLL THE SPLICE AREA WITH A 2" (5cm) WIDE STEEL ROLLER.

6" (15cm)
PRESSURE—SENSITIVE
T—JOINT
COVER AND
EPDM PRIMER

NOTES:

- 1. APPLY LAP SEALANT ALONG THE EDGES OF THE MEMBRANE SPLICE COVERING THE EXPOSED SPLICE TAPE 1/2" (15cm) IN EACH DIRECTION FROM THE SPLICE INTERSECTION.
- 2. APPLY LAP SEALANT AT CUT EDGES OF REINFORCED MEMBRANE AND TAPE OVER LAPS.




EPDM MEMBRANE SPLICE INTERSECTION (30 YEAR WARRANTY OR 90-MIL MEMBRANE)

MAXIMUM WARRANTY: 30 YEARS




DETAIL NO.


CONTINUOUS WALL FLASHING



SEPARATE WALL FLASHING



CONTINUOUS WALL FLASHING



NOTES:

- 1. APPLY LAP SEALANT ALONG THE LEADING EDGE OF THE MEMBRANE SPLICE (UNDER THE PRESSURE—SENSITIVE ELASTOFORM FLASHING) COVERING THE EXPOSED SPLICE TAPE APPROXIMATELY 1/2" (1.5cm) BEYOND THE SPLICE EDGE.
- 2. PRESSURE-SENSITIVE T-JOINT COVER OR 6" (15cm) WIDE PRESSURE-SENSITIVE FLASHING, IN CONJUNCTION WITH EPDM PRIMER, MUST BE CENTERED OVER FIELD SPLICES AT THE ANGLE CHANGE.
- 3. PROJECTS WITH 30-YEAR WARRANTY OR WHEN USING 90-MIL MEMBRANE REQUIRE FIELD SPLICES TO BE OVERLAID WITH TWO LAYERS OF PRESSURE-SENSITIVE ELASTOFORM FLASHING. THE BOTTOM LAYER SHALL BE 6" (15cm) WIDE COVERED WITH A 12" (30cm) WIDE TOP LAYER. BOTH LAYERS SHALL BE CENTERED.
- 4. SEAL EXPOSED LAYER WITH LAP SEALANT.



EPDM MEMBRANE SPLICES AT ANGLE CHANGE


MAXIMUM WARRANTY: 30 YEARS



DETAIL NO.


|U-2C


SIDE LAP SPLICE




END LAP SPLICE 6" (15cm) WIDE PRESSURÉ-SENSITIVE CURED 1 COVER STRIP, CENTERED OVER BUTTED END LAPS EPDM 1" (2.5cm) PRIMER MAX.

SECTION BB








NOTES:

- PRESSURE-SENSITIVE OVERLAYMENT STRIP CAN BE USED WHEN SAT IS OVERLAPPED A MINIMUM 1" (2.5cm) ELIMINATING THE NEED FOR T-JOINT COVERS.
- 2. APPLY LAP SEALANT ALONG THE EDGE OF THE MEMBRANE SPLICE UNDER THE 6" (15cm) T-JOINT COVER COVERING THE EXPOSED SPLICE TAPE 1/2" (1.5cm) IN EACH DIRECTION FROM THE SPLICE INTERSECTION.
- 3. APPLY A 6" (15cm) T-JOINT COVER OR PRESSURE-SÈNSITIVE ELASTOFORM FLASHING AND LAP SEAL THE EDGES.




SAT EPDM MEMBRANE SPLICES

MAXIMUM WARRANTY: 20 YEARS




- 1. MEMBRANE SHALL NOT BE ADHERED OVER THE EXPANSION JOINT SUPPORT.
- 2. FOR EXPANSION JOINT INTERSECTIONS AND INTERSECTIONS BETWEEN EXPANSION JOINTS TO WALL OR EDGING, USE TWO LAYERS OF PRESSURE—SENSITIVE ELASTOFORM FLASHING WITH SECOND LAYER 3" (7.5cm) LARGER THAN PREVIOUS LAYER IN ALL DIRECTIONS.
- 3. HP FASTENERS AND POLYMER SEAM PLATES ARE REQUIRED ON MECHANICALLY FASTENED SYSTEMS OVER STEEL DECKS.






- 1. MEMBRANE FLASHING SHALL <u>NOT</u> BE ADHERED OVER THE EXPANSION JOINT SUPPORT.
- 2. IN CASE THE ROOF TYPE IS DIFFERENT, DESIGNER TO PROVIDE ROOF TYPE AND ITS CONDITION TO CARLISLE TO DEVELOP A TIE-IN DETAIL ON THIS SIDE ACCORDINGLY.






- ALL OUTSIDE AND INSIDE CORNERS REQUIRE TWO COMPLETE CORNER APPLICATIONS OF PRESSURE-SENSITIVE ELASTOFORM FLASHING AS PER DETAILS U-15D.1 OR U-15G.1.
- 2. ROOF MEMBRANE SHALL BE LOOSE-LAID OVER THE EXPANSION JOINT SUPPORT OR SPONGE TUBING.
- 3. USE <u>DETAIL U-2C</u> FOR EPDM MEMBRANE SPLICES AT ANGLE CHANGES.
- 4. HP FASTENERS AND POLYMER SEAM PLATES ARE REQUIRED ON MECHANICALLY FASTENED SYSTEMS OVER STEEL DECKS.
- 5. MAXIMUM 6" (15cm) FASTENER SPACING FOR WARRANTY WIND SPEEDS GREATER THAN 90 MPH OR WARRANTIES EXCEEDING 20 YEARS.






- PRESSURE—SENSITIVE RUSS MAY BE INSTALLED INTO THE STRUCTURAL DECK. HP FASTENERS AND POLYMER SEAM PLATES ARE REQUIRED ON MECHANICALLY—FASTENED ROOFING SYSTEMS OVER STEEL DECKS.
- 2. USE DETAIL U-2C FOR EPDM MEMBRANE SPLICES AT ANGLE CHANGES.
- 3. SEAL FASTENERS BY APPLYING WATER CUT-OFF MASTIC UNDER THE COUNTER-FLASHING, OR USING EPDM WASHERS, OR CAULKING THE FASTENERS HEAD.
- 4. ALL OUTSIDE AND INSIDE CORNERS REQUIRE TWO COMPLETE CORNER APPLICATIONS OF PRESSURE-SENSITIVE ELASTOFORM FLASHING AS PER <u>DETAILS U-15D.1 OR U-15G.1.</u>
- 5. MAXIMUM 6" (15cm) FASTENER SPACING FOR WARRANTY WIND SPEEDS GREATER THAN 90 MPH OR WARRANTIES EXCEEDING 20 YEARS.





- 1. IN CASE THE THREADED FASTENERS ARE USED TO PENETRATE THE METAL COUNTER-FLASHING, USE EPDM WASHERS, APPLY WATER CUT-OFF MASTIC UNDER THE COUNTER-FLASHING OR SEAL THE FASTENER HEADS WITH SEALANT.
- 2. LAP SEALANT IS REQUIRED ON CUT-EDGES OF REINFORCED MEMBRANE.
- 3. SEAM PLATES AND FASTENERS MAY BE INSTALLED INTO THE STRUCTURAL DECK AND THEN HP FASTENERS AND POLYMER SEAM PLATES ARE REQUIRED FOR MECHANICALLY—FASTENED ROOFING SYSTEMS OVER STEEL DECKS.
- 4. MEMBRANE SPLICES SHALL INCORPORATE 3" (7.6cm) WIDE SecurTAPE FOR PROJECTS WITH 25-YEAR AND 6" (15.2cm) FOR 30-YEAR WARRANTIES.
- 5. IF THE VERTICAL SPLICE ON THE CURB FLASHING IS NOT LOCATED AT THE CORNER, USE DETAIL U-2C FOR EPDM MEMBRANE SPLICES AT ANGLE CHANGES.







CURB FLASHING - EPDM MEMBRANE

MAXIMUM WARRANTY: 30 YEARS






- 1. IN CASE THE THREADED FASTENERS ARE USED TO PENETRATE THE METAL COUNTER-FLASHING, USE EPDM WASHERS, APPLY WATER CUT-OFF MASTIC UNDER THE COUNTER-FLASHING OR SEAL THE FASTENER HEADS WITH SEALANT.
- 2. SEAM PLATES AND FASTENERS MAY BE INSTALLED INTO THE VERTICAL SUBSTRATE.
- 3. HP FASTENERS AND POLYMER SEAM PLATES ARE REQUIRED FOR MECHANICALLY FASTENED SYSTEMS OVER STEEL DECKS.
- 4. IF THE VERTICAL SPLICE ON THE CURB FLASHING IS NOT LOCATED AT THE CORNER, USE DETAIL U-2C FOR EPDM MEMBRANE SPLICES AT ANGLE CHANGES.




5B





- 1. IN CASE THE THREADED FASTENERS ARE USED TO PENETRATE THE METAL COUNTER-FLASHING, USE EPDM WASHERS, APPLY WATER CUT-OFF MASTIC UNDER THE COUNTER-FLASHING OR SEAL THE FASTENER HEADS WITH SEALANT.
- 2. 3" (7.5cm) FOR UP TO 25 YEARS AND 6" (15cm) FOR 30 YEARS WARRANTY.
- 3. HP FASTENERS AND POLYMER SEAM PLATES ARE REQUIRED FOR MECHANICALLY—FASTENED ROOFING SYSTEMS OVER STEEL DECKS.
- 4. IF THE VERTICAL SPLICE ON THE CURB FLASHING IS NOT LOCATED AT THE CORNER, USE DETAIL U-2C FOR EPDM MEMBRANE SPLICES AT ANGLE CHANGES.






CURB FLASHING — WITH 20" PRESSURE—SENSITIVE CURED FLASHING


MAXIMUM WARRANTY: 30 YEARS



U-5C



- LENGTH OF ROD STOCK IS LIMITED TO 4'
 (1.2m). USE INDIVIDUAL SECTIONS OF ROD
 STOCK FOR LONGER DIMENSIONS.
- 2. MEMBRANE SPLICES SHALL INCORPORATE 3" (7.6cm) WIDE SecurTAPE FOR PROJECTS WITH 25-YEAR AND 6" (15.2cm) FOR 30-YEAR WARRANTIES.
- 3. WHEN METAL FLANGE IS ON TOP OF MEMBRANE USE DETAIL <u>U-15F</u> (20 YEAR) OR <u>U-15G.1</u> (25/30 YEAR) TO ACHIEVE SUFFICIENT COVERAGE AT THE CORNERS.
- 4. DETAIL IS NOT ACCEPTABLE FOR VIBRATING ROOF TOP UNITS.






SELF—FLASHING CURB, ROOF HATCH OR SKYLIGHT


MAXIMUM WARRANTY: 30 YEARS



DETAIL NO.


U - 50







- NOTES:
- 1. CONSULT THE RESPECTIVE MANUFACTURER OF THE SELF-FLASHING METAL CURB FOR PROPER SECUREMENT.
- 2. WATER CUT-OFF MASTIC MUST BE HELD UNDER CONSTANT COMPRESSION.
- 3. USE DETAIL U-15F TO ACHIEVE SUFFICIENT COVERAGE OF METAL FLANGE AT CORNERS.
- 4. IF THE VERTICAL SPLICE ON THE CURB FLASHING IS NOT LOCATED AT THE CORNER, USE DETAIL U-2C FOR EPDM MEMBRANE SPLICES AT ANGLE CHANGES.





- ALL BOLTS OR CLAMPS MUST BE IN PLACE TO PROVIDE CONSTANT COMPRESSION ON WATER CUT-OFF MASTIC.
- 2. REMOVE EXISTING LEAD, FLASHING MATERIAL & ENSURE THE DRAIN RING IS COMPLETELY CLEAN DOWN TO BARE METAL.
- 3. INSULATION TAPER SHALL NOT BE GREATER THAN 6" (15cm) IN 12" (30cm) HORIZONTAL. REINFORCED EPDM IS LIMITED TO A TAPER LESS THAN 3" (7.5CM) PER FOOT. IF GREATER USE DETAIL U-6B.
- 4. THE HOLE IN THE MEMBRANE SHALL EXCEED THE DIAMETER OF THE DRAIN PIPE, BUT SHALL BE NO LESS THAN 1/2" (1.5cm) FROM THE ATTACHMENT POINTS OF THE DRAIN CLAMPING RING.
- 5. FIELD SPLICES MUST BE LOCATED AT LEAST 6" (15cm) OUTSIDE THE DRAIN SUMP.
- 6. ROOF DRAIN SIZE AND NUMBER OF DRAINS SHALL BE IN ACCORDANCE WITH THE LOCAL CODES.








ROOF DRAIN


MAXIMUM WARRANTY: 30 YEARS




DETAIL NO.




- ALL BOLTS OR CLAMPS MUST BE IN PLACE TO PROVIDE CONSTANT COMPRESSION ON WATER CUT-OFF MASTIC.
- 2. REMOVE EXISTING LEAD, FLASHING MATERIAL & ENSURE THE DRAIN RING IS COMPLETELY CLEAN DOWN TO BARE METAL.
- 3. USE DETAIL MF-6B FOR MECHANICALLY-FASTENED SYSTEMS.
- 4. THE HOLE IN THE MEMBRANE SHALL <u>EXCEED</u> THE DIAMETER OF THE DRAIN PIPE, BUT SHALL BE NO LESS THAN 1/2" (1.5cm) FROM THE ATTACHMENT POINTS OF THE DRAIN CLAMPING RING.
- ROOF DRAIN SIZE AND NUMBER OF DRAINS SHALL BE IN ACCORDANCE WITH THE LOCAL CODES.
- 6. FIELD SPLICES MUST BE LOCATED AT LEAST 6" (15cm) OUTSIDE THE DRAIN SUMP.
- 7. CARLISLE RECOMMENDS THE DRAIN TARGET SPLICE BE SHINGLED
- 7.1. CUT A SQUARE HOLE IN THE FIELD SHEET TO BE AT LEAST 6" (15cm) OUTSIDE THE DRAIN SUMP
- 7.2. APPLY PRIMER AND SecurTAPE TO THE BOTTOM OF THE FIELD SHEET
- 7.3. PRIME THE TARGET PIECE OF NR EPDM
- 7.4. MATE THE TARGET TO THE TAPE
- 7.5. APPLY BONDING ADHESIVE TO ADHERE FIELD AND TARGET MEMBRANE TO THE SUBSTRATE





- ALL BOLTS OR CLAMPS MUST BE IN PLACE TO PROVIDE CONSTANT COMPRESSION ON WATER CUT-OFF MASTIC.
- 2. INSULATION TAPER SHALL NOT BE GREATER THAN 6" (15cm) IN 12" (30cm) HORIZONTAL.
- 3. THE HOLE IN THE MEMBRANE SHALL EXCEED THE DIAMETER OF THE DRAIN PIPE, BUT SHALL BE NO LESS THAN 1/2" (1.5cm) FROM THE ATTACHMENT POINTS OF THE DRAIN CLAMPING RING.
- 4. FIELD SPLICES MUST BE LOCATED AT LEAST 6" (15cm) OUTSIDE THE DRAIN SUMP.
- 5. ROOF DRAIN SIZE AND NUMBER OF DRAINS SHALL BE IN ACCORDANCE WITH THE LOCAL CODES.







SURE-SEAL INSERT DRAIN


MAXIMUM WARRANTY: 30 YEARS






- 1. WATER CUT-OFF MASTIC MUST BE UNDER CONSTANT COMPRESSION.
- 2. CONSULT SPECIFIER OR APPLICABLE CODES FOR ADEQUATE DRAINAGE STRAINER TO AVOID PONDING WATER. DO NOT RESTRICT WATER FLOW.
- 3. FOR PROJECTS WITH 30-YEAR WARRANTIES, THE DRAIN INSERT FLANGE MUST BE OVERLAID WITH TWO LAYERS OF PRESSURE-SENSITIVE FLASHING. THE BOTTOM LAYER SHALL BE 6" (15cm) WIDE PRESSURE-SENSITIVE ELASTOFORM OR CURED COVER STRIP COVERED WITH A 9" (23cm) WIDE TOP LAYER OF PRESSURE-SENSITIVE ELASTOFORM FLASHING. SEAL TOP LAYER WITH CONTINUOUS LAP SEALANT.







- ALL BOLTS OR CLAMPS MUST BE IN PLACE TO PROVIDE CONSTANT COMPRESSION ON WATER CUT-OFF MASTIC.
- 2. INSULATION TAPER SHALL NOT BE GREATER THAN 6" (15cm) IN 12" (30cm) HORIZONTAL.
- 3. THE HOLE IN THE MEMBRANE SHALL EXCEED THE DIAMETER OF THE DRAIN PIPE, BUT SHALL BE NO LESS THAN 1/2" (1.5cm) FROM THE ATTACHMENT POINTS OF THE DRAIN CLAMPING RING.
- 4. FIELD SPLICES MUST BE LOCATED AT LEAST 6" (15cm) OUTSIDE THE DRAIN SUMP.
- 5. ROOF DRAIN SIZE AND NUMBER OF DRAINS SHALL BE IN ACCORDANCE WITH THE LOCAL CODES.





- REMOVE ALL LEAD AND OTHER FLASHING BEFORE INSTALLING PRESSURE—SENSITIVE PIPE SEAL.
- TEMPERATURE OF PIPE PENETRATION MUST NOT EXCEED 180'F (82'C).
- PRE-MOLDED PIPE FLASHING MUST HAVE RIB INTACT AT THE TOP EDGE REGARDLESS OF PIPE DIAMETER.
- 4. DECK FLANGES OF THE PRESSURE—SENSITIVE PIPE SEAL SHALL NOT BE OVERLAPPED, CUT OR APPLIED OVER ANY ANGLE CHANGE.
- 5. USE DETAIL <u>U-8A.1</u> WHEN PIPE BOOT INTERSECTS A SPLICE ON 30-YEAR WARRANTY.
- 6. ON MECHANICALLY—FASTENED ROOFING SYSTEMS, REFER TO DETAIL MF—8A.









PRESSURE-SENSITIVE PIPE SEAL


MAXIMUM WARRANTY: 30 YEARS



U-8A







- THIS DETAIL FOR USE WHEN A RELIEF CUT OR MEMBRANE SPLICE IS PRESENT AT THE PIPE SEAL. USE DETAIL <u>U-8A</u> WHEN NO CUT OR SPLICE IS PRESENT.
- REMOVE ALL LEAD AND OTHER FLASHING BEFORE INSTALLING PRESSURE—SENSITIVE PIPE SEAL.
- 3. PIPE SEAL MUST HAVE INTACT RIB AT TOP EDGE, REGARDLESS OF PIPE DIAMETER.
- 4. DECK FLANGES OF THE MOLDED PIPE SEAL SHALL NOT BE OVERLAPPED, CUT OR APPLIED OVER ANY ANGLE CHANGE.
- 5. ON MECHANICALLY FASTENED ROOFING SYSTEMS REFER TO DETAIL MF-8A.1.

Í	DIMENSIONS		cm	
	\bigcirc	3"	7.5	MIN.
	\bigcirc	1"	2.5	MIN.




PRESSURE-SENSITIVE PIPE SEAL WITH 90-MIL MEMBRANE OR 30-YEAR WARRANTY

MAXIMUM WARRANTY: 30 YEARS





DETAIL NO.



- 1. REMOVE ALL LEAD AND OTHER FLASHING BEFORE INSTALLING FIELD—FABRICATED FLASHING.
- 2. TEMPERATURE OF PIPE PENETRATION MUST NOT EXCEED 180°F (82°C).
- 3. ACCEPTABLE WITH SQUARE OR RECTANGULAR STRUCTURAL TUBING WITH ROUNDED CORNERS UP TO 12"(30cm). USE DETAIL U-5 IF GREATER THAN 12" (30cm).
- 4. IN COLDER TEMPERATURES, A HEAT GUN MUST BE USED WHEN FORMING PRESSURE—SENSITIVE ELASTOFORM OR CURED FLASHING.
- 5. ON MECHANICALLY FASTENED ROOFING SYSTEMS. REFER TO DETAIL MF-8B.
- 6. MEMBRANE SECUREMENT IS REQUIRED AROUND ALL ROUND PIPE PENETRATIONS GREATER THAN 18" (46cm) IN DIAMETER.

DIME	NSIONS	cm	Ì
\bigcirc	1/2"	1.5	MIN.
$^{\otimes}$	1"	2.5	MIN.
0	3"	7.5	MIN.






- 1. REMOVE ALL LEAD AND OTHER FLASHING BEFORE INSTALLING FIELD—FABRICATED FLASHING.
- 2. TEMPERATURE OF PIPE PENETRATION MUST NOT EXCEED 180'F (82'C).
- 3. PIPE FLASHING MAY BE USED WITH SQUARE OR RECTANGULAR STRUCTURAL TUBING WITH ROUNDED CORNERS.
- 4. FOR STRUCTURAL STEEL TUBING GREATER THAN 12" (30cm) ACROSS, USE $\frac{\text{DETAIL}(S)}{\text{DETAIL}(S)} = \frac{1}{2}$.
- 5. IN COLDER TEMPERATURES, A HEAT GUN MUST BE USED WHEN FORMING PRESSURE—SENSITIVE ELASTOFORM FLASHING.
- 6. ON MECHANICALLY FASTENED ROOFING SYSTEMS, REFER TO $\frac{\text{DETAIL}}{\text{MF}-8B.1}$.
- 7. MEMBRANE SECUREMENT IS REQUIRED AROUND ALL ROUND PIPE PENETRATIONS GREATER THAN 18" (46cm) IN DIAMETER.


DIME	NSIONS	cm	
\bigcirc	1/2"	1.5	MIN.
$^{\otimes}$	1"	2.5	MIN.
0	3"	7.5	MIN.





- 1. REMOVE ALL LEAD AND OTHER FLASHING BEFORE INSTALLING FIELD—FABRICATED PIPE SEAL.
- 2. TEMPERATURE OF PENETRATION MUST NOT EXCEED 180'F (82'C).
- 3. IN COLDER
 TEMPERATURES, A HEAT
 GUN MUST BE USED
 WHEN FORMING
 PRESSURE—SENSITIVE
 ELASTOFORM FLASHING.


DIMENSIONS		cm	
(A)	1/2"	1.5	MIN.
B	1"	2.5	MIN.
(C)	3"	7.5	MIN.



EVALUATION 30-YEAR WARRANTY




U-8C



- 1. REMOVE ALL LEAD AND OTHER FLASHING BEFORE INSTALLING FIELD FABRICATED PIPE SEAL.
- 2. TEMPERATURE OF METAL COLLAR MUST NOT EXCEED 180°F (82°C).
- 3. IN COLDER TEMPERATURES, A HEAT GUN MUST BE USED WHEN FORMING PRESSURE-SENSITIVE ELASTOFORM FLASHING.

DIME	NSIONS	cm	
\bigcirc	1/2"	1.5	MIN.
$^{\otimes}$	1"	2.5	MIN.
0	3"	7.5	MIN.

			DETAIL NO.
CARLISLE	FIELD FABRICATED HOT STACK		U-8D
SYNTEC SYSTEMS	MAXIMUM WARRANTY: 20 YEARS	U (UNIV	ERSAL DETAIL)




- 1. REMOVE ALL LEAD AND OTHER FLASHING BEFORE INSTALLING FIELD FABRICATED PIPE SEAL.
- 2. TEMPERATURE OF METAL COLLAR MUST NOT EXCEED 180°F (82°C).
- 3. IN COLDER TEMPERATURES, A HEAT GUN MUST BE USED WHEN FORMING PRESSURE—SENSITIVE ELASTOFORM FLASHING.

DIMENSIONS		cm	
A	1/2"	1.5	MIN.
B	1"	2.5	MIN.
(0)	3"	7.5	MIN.



9A MECHANICAL TERMINATION WITH COUNTER FLASHING



CARLISLE UNIVERSAL SINGLE-PLY SEALANT OR SEALANT (BY OTHERS)


METAL COUNTER-FLASHING WITH LEAD WEDGES, AS REQUIRED (BY OTHERS).

THREADED FASTENERS OR CARLISLE HP TERM BAR NAIL—IN. 6"(15cm) O.C. FASTENING RECOMMENDED.

CARLISLE TERMINATION BAR

WARRANTY UP TO 30 YEARS SEE INSET

9B MECHANICAL TERMINATION




CARLISLE UNIVERSAL SINGLE-PLY SEALANT OR SEALANT (BY OTHERS)

CARLISLE HP TERM BAR NAIL—IN. 6"(15cm) O.C. FASTENING RECOMMENDED.

CARLISLE TERMINATION BAR

WARRANTY UP TO 20 YEARS SEE INSET


INSET A



NOTES:

- 1. APPLY ON HARD SMOOTH SURFACE ONLY; NOT FOR USE ON EXPOSED WOOD.
- 2. DO NOT WRAP TERMINATION BAR AROUND CORNERS.
- 3. DETAIL <u>9D</u> MUST BE USED AT VERTICAL JOINTS IN PANEL WALLS.

9C COUNTER FLASHING TERMINATION



CARLISLE UNIVERSAL SINGLE-PLY SEALANT OR SEALANT (BY OTHERS)

METAL COUNTER-FLASHING WITH LEAD WEDGES, AS REQUIRED (BY OTHERS).

FASTEN MEMBRANE @ 12" (30cm) O.C. MAX. USE GALVANIZED WASHERS, MIN. 1", (2.54cm) DIAMETER

NOTE:

1. WHEN MECHANICAL FASTENERS ARE USED TO PENETRATE THE METAL COUNTER-FLASHING, USE EPDM WASHERS, APPLY WATER CUT-OFF MASTIC UNDER THE COUNTER-FLASHING OR CAULK THE FASTENER HEADS.

WARRANTY UP TO 10 YEARS

APPLICABLE BONDING ADHESIVE

WATER CUT-OFF MASTIC- MUST BE HELD UNDER CONSTANT COMPRESSION.



MEMBRANE TERMINATIONS (PAGE 1 OF 3)


WARRANTY AS NOTES FOR EACH DETAIL



DETAIL NO.

9D

MECHANICAL TERMINATION AT VERTICAL JOINTS




4. APPLY ON HARD SMOOTH SURFACE ONLY.

SEALED TO PREVENT AIR INFILTRATION.

9E SecurEdge & SecurEdge 300 COPINGS

NOTES:

- I. MEMBRANE MUST BE
 EXTENDED AT CORNERS TO
 PROVIDE COMPLETE
 COVERAGE OF THE TOP
 WALL SURFACE, REFER TO
 3D DETAIL
 U-9F.
- 2. REFER TO SecurEdge
 COPING INSTALLATION
 INSTRUCTION MANUAL FOR
 STEP-BY-STEP
 INSTRUCTION PROCEDURES.



APPLICABLE BONDING ADHESIVE

WATER CUT-OFF MASTIC- MUST BE HELD UNDER CONSTANT COMPRESSION.




MEMBRANE TERMINATIONS (PAGE 2 OF 3)

WARRANTY AS NOTES FOR EACH DETAIL




DETAIL NO.

U-9



- MEMBRANE MUST BE EXTENDED TO CORNERS TO PROVIDE COMPLETE COVERAGE OF THE TOP WALL SURFACE.
- 2. WARRANTY AS PROVIDED (BY OTHERS).

9G MASONRY COPINGS (BY OTHERS)



MAXIMUM WARRANTY: 30 YEARS

APPLICABLE BONDING ADHESIVE

WATER CUT-OFF MASTIC- MUST BE HELD UNDER CONSTANT COMPRESSION.




MEMBRANE TERMINATIONS (PAGE 3 OF 3)


MAXIMUM WARRANTY: 30 YEARS



DETAIL NO.

U-9






OPTIONAL: SEAM
PLATE/FASTENER MAY BE
INSTALLED INTO THE
STRUCTURAL DECK UP TO 6"
(15cm) FROM ANGLE CHANGE.

NOTES:

- 1. FASTENERS AND PLATES ARE REQUIRED AT 6" (15cm) O.C. FOR ADHERED SYSTEMS WITH WARRANTY WIND SPEED COVERAGE GREATER THAN 90 MPH AND FOR ALL PROJECTS WITH WARRANTIES GREATER THAN 20 YEARS. HP FASTENERS AND POLYMER SEAM PLATES ARE REQUIRED OVER STEEL DECKS ON MECHANICALLY FASTENED SYSTEMS.
- 2. PROJECTS WITH 30-YEAR WARRANTY OR WHEN USING 90-MIL MEMBRANE. REFER TO DETAIL U-2C.
- 3. FOR CORNERS AND RUSS APPLICATION REFER TO DETAILS U-15A OR U-15B.



DIMENSION


1/8"-1"

cm


0.5 - 2.5




C 2025 Carlisle SynTec a division of Carlisle Construction Materials Incorporated




OPTIONAL: SEAM
PLATE/FASTENER MAY BE
INSTALLED INTO THE
STRUCTURAL DECK UP TO 6"
(15cm) FROM ANGLE CHANGE.



- FASTENERS AND PLATES ARE REQUIRED AT 6"(15cm) O.C. FOR ADHERED SYSTEMS WITH WARRANTY WIND SPEED COVERAGE GREATER THAN 90 MPH AND FOR ALL PROJECTS WITH WARRANTIES GREATER THAN 20 YEARS. HP FASTENERS AND POLYMER SEAM PLATES ARE REQUIRED OVER STEEL DECKS ON MECHANICALLY FASTENED SYSTEMS.
- 2. USE 6" (15cm) WIDE SecurTAPE FOR 30-YEAR WARRANTY. LAP SEALANT IS REQUIRED ON CUT EDGES OF REINFORCED MEMBRANE.
- 3. PROJECTS WITH 30-YEAR WARRANTY OR WHEN USING 90-MIL MEMBRANE, REFER TO DETAIL U-2C.








PARAPET / CURB WITH SEPARATE MEMBRANE FLASHING

MAXIMUM WARRANTY: 30 YEARS




DETAIL NO.

U-12B



STRUCTURAL DECK UP TO 6" (15cm) FROM ANGLE CHANGE.



1	DIMENSION		cm	
	A	1/8"-1"	0.5-2.5	

CAV-GRIP III OR EPDM BONDING ADHESIVE

PRESSÚRE-SENSITIVE T-JOINT COVER OR PS ELASTOFORM LAP SEALANT

NOTES:


- 1. FOR CORNERS AND RUSS APPLICATION, REFER TO DETAILS <u>U-15A</u> OR <u>U-15B</u>.
- 2. FASTENERS AND PLATES REQUIRED AT 6" (7.5cm) O.C. FOR WARRANTY WIND SPEEDS **EXCEEDING 90 MPH.**



PARAPET / CURB WITH CONTINUOUS MEMBRANÉ - RUSS

MAXIMUM WARRANTY: 20 YEARS






DIME	NSION	cm
A	1/8"-1"	0.5-2.5
lacksquare	3"	7.5

SURE-SEAL BONDING ADHESIVE OR CAV-GRIP III

NOTES:

- SEAM FASTENING PLATE/FASTENER MAY BE INSTALLED INTO THE STRUCTURAL DECK ALSO.
- 2. FASTENRES AND PLATES REQUIRED AT 6" (7.5cm) O.C. FOR WARRANTY WIND SPEEDS EXCEEDING 90 MPH.
- APPLY PRESSURE SENSITIVE ELASTOFORM FLASHING COVERING VERTICAL SPLICE INTERSECTIONS.







PARAPET/CURB WITH SEPARATE REGULAR EPDM FLASHING


MAXIMUM WARRANTY: 20 YEARS





- SEAM FASTENING PLATE/FASTENER MAY BE INSTALLED INTO THE STRUCTURAL DECK ALSO.
- 2. FASTENERS AND PLATES REQUIRED AT 6" (7.5cm) O.C. FOR WARRANTY WIND SPEEDS **EXCEEDING 90 MPH.**
- 3. APPLY PRESSURE SENSITIVE ELASTOFORM FLASHING COVERING VERTICAL SPLICE INTERSECTIONS.








PARAPET/CURB WITH SEPARATE SAT EPDM

MAXIMUM WARRANTY: 20 YEARS




DIMENSIONS

cm



- T-JOINTS CAN BE ELIMINATED WHEN PRESSURE-SENSITIVE OVERLAYMENT STRIP IS USED.
- 2. FASTENERS AND PLATES REQUIRED AT 6" (7.5cm) O.C. FOR WARRANTY WIND SPEEDS EXCEEDING 90 MPH.






LAP SEALANT


COVER

UNDER T-JOINT





- 2. SPLICE TWO PIECES OR MORE OF ELASTOFORM OR PRESSURE—SENSITIVE ELASTOFORM TOGETHER TO ACHIEVE DESIRED WIDTH.
- 3. IF FLUTES ARE PERPENDICULAR TO THE TIE-IN DRILL A 3/8" (1cm) DIAMETER WEEP HOLE ON THE BOTTOM FLUTES OF THE STEEL DECK ALONG THE PERIMETER TO THE TIE-IN 6" (15cm) FROM THE SEAM FASTENING PLATE.
- 4. ON MECHANICALLY FASTENED SYSTEMS, HP FASTENERS AND POLYMER SEAM PLATES ARE REQUIRED OVER STEEL DECKS.
- 5. IF WATER PONDS OR FLOWS OVER TIE-IN FROM BUR SURFACE, USE DETAIL U-13B.
- 6. ON BALLASTED SYSTEMS, USE CONCRETE PAVERS TO PREVENT BALLAST MIGRATION.

DIMENSIONS cm A 5" 13 MIN. B 2" 5 ± 1/2" (1.5cm) C 6" 15	REMOVE & SEALER REPLACE UN	AL TWO NT POURABLE CURED EPDM ASTOFORM FLASHING		
BUILT-UP ROOFING TIE-IN OVER STEEL ROOF DECK DETAIL NO. DETAIL NO. U-134				
SYNTEC SYSTEMS	MAXIMUM WARRANTY: 30 YEARS	U (UNIVERSAL DETAIL)		




- 1. REMOVE ALL GRAVEL AT TIE-IN.
- 2. SPLICE TWO PIECES OF ELASTOFORM OR PRESSURE—SENSITIVE ELASTOFORM TOGETHER TO ACHIEVE DESIRED WIDTH.
- 3. WATER CUT-OFF MUST BE UNDER CONSTANT COMPRESSION.
- 4. CARLISLE IS NOT RESPONSIBLE FOR DAMAGE TO THE BUILT-UP ROOF OR STRUCTURAL DECK RESULTING FROM PONDED WATER; THIS DETAIL APPLIES TO RE-ROOFING WHEN A TEAR-OFF IS NOT SPECIFIED AND WAS DESIGNED TO PREVENT MIGRATION OF WATER INTO THE NEW ROOFING SYSTEM.
- 5. ON BALLASTED SYSTEMS, USE CONCRETE PAVERS TO PREVENT BALLAST MIGRATION.






- 1. CONTACT MANUFACTURER OF EXISTING EPDM MEMBRANE ROOFING SYSTEM TO VERIFY ACCEPTANCE OF TIE-IN AND TO NOT VOID EXISTING WARRANTY.
- 2. PRIOR TO SPLICING, CLEAN EXISTING EPDM MEMBRANE BY SCRUBBING THE SPLICE AREA WITH WEATHERED MEMBRANE CLEANER AND ALLOW TO DRY.
- 3. ON MECHANICALLY FASTENED SYSTEMS, HP FASTENERS AND POLYMER SEAM PLATES ARE REQUIRED OVER STEEL DECKS.
- 4. IF FLUTES ARE PERPENDICULAR TO THE TIE-IN DRILL A 3/8" (1cm) DIAMETER WEEP HOLE INTO THE BOTTOM FLUTES OF THE STEEL DECK ALONG THE PERIMETER OF THE TIE-IN 6" (15cm) MINIMUM TO 12" (30cm) MAXIMUM FROM THE SEAM FASTENING PLATE.






- 1. CONTACT MANUFACTURER OF EXISTING EPDM MEMBRANE ROOFING SYSTEM TO VERIFY ACCEPTANCE OF TIE-IN AND TO NOT VOID EXISTING WARRANTY.
- 2. PRIOR TO SPLICING, CLEAN EXISTING EPDM MEMBRANE BY SCRUBBING THE SPLICE AREA WITH WEATHERED MEMBRANE CLEANER; ALLOW TO DRY.
- 3. WATER CUT-OFF MASTIC MUST BE HELD UNDER CONSTANT COMPRESSION. WHEN RE-ROOFING OVER PRE-CAST CONCRETE, APPLY LIBERAL BEAD OF WATER CUT-OFF MASTIC IN THE JOINTS TO PREVENT MOISTURE MIGRATION.








U (UNIVERSAL DETAIL)



BALLASTED TO ADHERED TIE-IN




ADHERED OR MECHANICALLY

MAXIMUM WARRANTY: 30 YEARS

FASTENED ROOF


0




6" (15cm) WIDE PRESSURE— SENSITIVE RUSS (MAY BE FASTENED INTO VERTICAL SUBSTRATE)


CARLISLE SEAM PLATE & FASTENER.


EPDM PRIMER -






ĺ	DIMENSIONS		cm	
	\triangle	6"	15	то
9		9"	23	







NOTES:

- 1. MINIMUM SPLICE WIDTH:
- 1.1. 3" (7.5cm) UP TO 20 YEAR WARRANTIES
- 1.2. 6" (15cm) FOR 25/30 YEAR WARRANTIES
- 2. REFER TO DETAIL <u>U-15C</u>
 (20 YEAR) OR <u>U-15D.1</u>
 (25/30 YEAR) FOR INSIDE
 CORNER INSTALLATION
 REQUIREMENTS.





PIG EAR ON OPPOSITE WALL-






INSIDE CORNER WALL FLASHING WITH RUSS (OPTION 1)


MAXIMUM WARRANTY: 30 YEARS





DETAIL NO.


U-15A














- 1. PRE-CUT 7" X 9" CORNER OR 9" X 9" PRESSURE SENSITIVE ELASTOFORM.
- 2. FOR PROJECTS WITH 25 AND 30-YEAR WARRANTIES OR WHEN USING 90-MIL MEMBRANE, INSTALL A 6" T-JOINT COVER PRIOR TO INSTALLING A 12" T-JOINT COVER. SEAL TOP LAYER WITH CONTINUOUS LAP SEALANT. PER DETAIL U-15D.1
- 3. A HEAT GUN MUST BE USED WHEN FORMING PRESSURE—SENSITIVE ELASTOFORM FLASHING IN COLDER TEMPERATURES.





INSIDE CORNER WITH CONTINUOUS EPDM WALL FLASHING


MAXIMUM WARRANTY: 20 YEARS, SEE NOTE 2

DETAIL NO.

|U-15C|









DIMENSIONS		cm				
\bigcirc	6"	15	ТО			
	9"	23				
\bigcirc	3"	7.5				

- 1. A HEAT GUN MUST BE USED WHEN FORMING PRESSURE—SENSITIVE ELASTOFORM FLASHING IN COLDER TEMPERATURES.
- 2. FOR PROJECTS WITH 25 & 30-YEAR WARRANTIES OR WHEN USING 90-MIL MEMBRANE, REFER TO DETAIL U-15D.1 FOR REQUIRED FLASHING ENHANCEMENTS.







- 1. A 7"X9" (17.5cm X 23cm) PRESSURE-SENSITIVE PRE-CUT INSIDE/OUTSIDE CORNER MAY BE CUT DOWN TO 6" X 6" (7.5cm X 7.5cm).
- 2. A HEAT GUN MUST BE USED WHEN FORMING PRESSURE—SENSITIVE ELASTOFORM FLASHING IN COLDER TEMPERATURES.
- 3. APPLY PRIMER AND SecurTAPE TO ADHERE PIG EAR TO THE WALL.





INSIDE CORNER FLASHING FOR PROJECTS WITH 90-MIL MEMBRANE OR 30 YEAR WARRANTIES


MAXIMUM WARRANTY: 30 YEARS





DETAIL NO.
U-15D.1











1. FOR PROJECTS WITH 25 & 30-YEAR WARRANTIES OR WHEN USING 90-MIL MEMBRANE, REFER TO DETAIL U-15G.1 FOR REQUIRED FLASHING ENHANCEMENTS.




OUTSIDE CORNER WITH PRE-CUT PRESSURE-SENSITIVE CORNER


MAXIMUM WARRANTY: 20 YEARS. SEE NOTE 1




DETAIL NO.

U - 15E







DIME	NSIONS	cm	
A	6"	15	ТО
	9"	23	
B	2"	5	MIN.
\bigcirc	3"	7.5	MAX.

- 1. A HEAT GUN MUST BE USED WHEN FORMING PRESSURE—SENSITIVE ELASTOFORM FLASHING IN COLDER TEMPERATURES.
- 2. FOR PROJECTS WITH 30-YEAR WARRANTY OR WHEN USING 90-MIL MEMBRANE, REFER TO DETAIL U-156.1 FOR REQUIRED FLASHING ENHANCEMENTS.




OUTSIDE CORNER WITH
PRESSURE-SENSITIVE ELASTOFORM
FLASHING (2 PIECE)

MAXIMUM WARRANTY: 25 YEARS





DETAIL NO.

U - 15F





FASTEN MEMBRANE AND FLASH CURB OR WALL WITH CURED EPDM MEMBRANE FOLLOWING STANDARD PROCEDURES USING BONDING ADHESIVE and SecurTAPE.





AFTER APPLYING EPDM PRIMER, REMOVE AND REPLACE POLY BACKING. FOLD FLASHING IN HALF WITH ROUNDED PORTION TURNED UP. CENTER FLASHING ON CORNER AND FIRMLY PRESS AGAINST VERTICAL SURFACE.





AFTER ADHERING, ROLL WITH A TWO INCH WIDE STEEL HAND ROLLER. PAY PARTICULAR ATTENTION TO THE STEP OFFS AND ANGLE CHANGES.

DIMENSIONS		cm	
A	6"	15	ТО
	9"	23	

ANGLE CHANGE AND FIRMLY ROLL FLASHING

ONTO THE DECK MEMBRANE.

NOTES:

- 1. FOR PROJECTS WITH 25 & 30-YEAR WARRANTIES OR WHEN USING 90-MIL MEMBRANE, REFER TO DETAIL U-15G.1 FOR REQUIRED FLASHING ENHANCEMENTS.
- 2. A HEAT GUN MUST BE USED WHEN FORMING PRESSURE-SENSITIVE ELASTOFORM FLASHING IN COLDER TEMPERATURES.




OUTSIDE CORNER WITH
PRESSURE-SENSITIVE ELASTOFORM
FLASHING (1 PIECE)

MAXIMUM WARRANTY: 20 YEARS. SEE NOTE 1




DETAIL NO.


U - 15G




FASTEN MEMBRANE AND FLASH CURB OR WALL WITH CURED EPDM MEMBRANE FOLLOWING STANDARD PROCEDURES.




USE PRE-CUT T-JOINT COVERS OR CUT A 6"x6" (15X15cm) & 12"x12" (30X30cm) SECTION OF PRESSURE- SENSITIVE ELASTOFORM FLASHING AND ROUND CORNERS



CLEAN EPDM SPLICE AREA WITH WEATHERED MEMBRANE CLEANER PRIOR TO APPLYING EPDM PRIMER




REMOVE & REPLACE POLY BACKING ON FLASHING. FOLD FLASHING IN HALF WITH ROUNDED PORTION TURNED UP. CENTER ON CORNER & FIRMLY PRESS AGAINST VERTICAL **SURFACE**





ROLL & CREASE FLASHING TIGHTLY INTO ANGLE CHANGE & FIRMLY ROLL FLASHING ONTO THE DECK MEMBRANE

USE HEAT GUN TO WARM THE FLASHING IN COLD WEATHER




ROLL WITH A TWO INCH WIDE STEEL HAND ROLLER. PAY PARTICULAR ATTENTION TO THE STEP OFFS AND ANGLE **CHANGES**





APPLY EPDM PRIMER TO SPLICE AREA. INSTALL THE 12"X12" (30cmX30cm) SECTION OF PRESSURE - SENSITIVE ELASTOFORM FLASHING CENTERED OVER PREVIOUSLY APPLIED FLASHING.






OUTSIDE CORNER FLASHING FOR PROJECTS WITH 90-MIL MEMBRANE OR 30 YEAR WARRANTIES

MAXIMUM WARRANTY: 30 YEARS



DETAIL NO.


U - 15G.1



- 1. THE MAXIMUM ALLOWABLE SURFACE TEMPERATURE OF THE PENETRATION SHALL NOT EXCEED 180° F (82° C).
- 2. ALL DEBRIS (PAINT, RUST, LEAD, OTHER FLASHINGS, ETC.) MUST BE REMOVED FROM THE PENETRATION.
- 3. <u>ALL SURFACES MUST BE PRIMED WITH EPDM PRIMER PRIOR TO APPLYING POURABLE SEALER. DO NOT PRIME THE BLUE PLASTIC SUPPORT STRIP.</u>
- 4. POURABLE SEALER MUST COMPLETELY FILL POURABLE SEALER POCKET TO PREVENT PONDING OF WATER.
- 5. POURABLE SEALER MUST CONTACT PRIMED PRESSURE—SENSITIVE ELASTOFORM FLASHING AND DECK MEMBRANE.
- 6. SECUREMENT IS REQUIRED FOR POURABLE SEALER POCKETS WHICH ARE GREATER THAN 18" (46cm) IN DIAMETER. REFER TO SPECIFICATIONS.
- 7. ON MECHANICALLY—FASTENED ROOFING SYSTEMS, ADDITIONAL MEMBRANE SECUREMENT IS REQUIRED (SIMILAR TO DETAIL MF—8A) REGARDLESS OF SIZE OR DIAMETER.
- 8. MINIMUM 1" (2.5cm) CLEARANCE REQUIRED BETWEEN PENETRATIONS.

DIMENSIONS		cm	
\bigcirc	1"	2.5	MIN.
\bigcirc	2"	5	MIN.







- 1. THE MAXIMUM ALLOWABLE SURFACE TEMPERATURE OF THE PENETRATION SHALL NOT EXCEED 180° F (82° C).
- 2. ALL DEBRIS (PAINT, RUST, LEAD, OTHER FLASHINGS, ETC.) MUST BE REMOVED FROM THE PENETRATION.
- 3. <u>ALL SURFACES MUST BE PRIMED WITH EPDM PRIMER PRIOR TO APPLYING POURABLE SEALER.</u> DO NOT PRIME THE BLUE PLASTIC SUPPORT STRIP.
- 4. POURABLE SEALER MUST COMPLETELY FILL POURABLE SEALER POCKET TO PREVENT PONDING OF WATER.
- 5. POURABLE SEALER MUST CONTACT PRIMED PRESSURE—SENSITIVE ELASTOFORM FLASHING AND DECK MEMBRANE.
- 6. SECUREMENT IS REQUIRED FOR POURABLE SEALER POCKETS WHICH ARE GREATER THAN 18" (46cm) IN DIAMETER. REFER TO SPECIFICATIONS.
- 7. ON MECHANICALLY—FASTENED ROOFING SYSTEMS, ADDITIONAL MEMBRANE SECUREMENT IS REQUIRED (SIMILAR TO <u>DETAIL MF-8A</u>) REGARDLESS OF SIZE OR DIAMETER.
- 8. MINIMUM 1" (2.5cm) CLEARANCE REQUIRED BETWEEN PENETRATIONS.

DIMENSIONS		cm	
\bigcirc	1"	2.5	MIN.
\bigcirc	2"	5	MIN.





- 1. THE MAXIMUM ALLOWABLE SURFACE TEMPERATURE OF THE PENETRATION SHALL NOT EXCEED 180° F (82° C).
- 2. ALL DEBRIS (PAINT, RUST, LEAD, OTHER FLASHINGS, ETC.) MUST BE REMOVED FROM THE PENETRATION.
- 3. ALL SURFACES MUST BE PRIMED WITH EPDM PRIMER PRIOR TO APPLYING POURABLE SEALER.
- 4. POURABLE SEALER MUST COMPLETELY FILL POURABLE SEALER POCKET TO PREVENT PONDING OF WATER.
- 5. POURABLE SEALER MUST CONTACT PRIMED PRESSURE—SENSITIVE ELASTOFORM FLASHING AND DECK MEMBRANE.
- 6. SECUREMENT IS REQUIRED FOR POURABLE SEALER POCKETS WHICH ARE GREATER THAN 18" (46cm) IN DIAMETER. REFER TO SPECIFICATIONS.
- 7. ON MECHANICALLY—FASTENED ROOFING SYSTEMS, ADDITIONAL MEMBRANE SECUREMENT IS REQUIRED (SIMILAR TO DETAIL MF—8A) REGARDLESS OF SIZE AND DIAMETER, UNLESS WOOD NAILERS ARE PRESENT.
- 8. DECK FLANGE MUST BE CONTINUOUS WITH ROUNDED CORNERS.
- 9. WHEN ANY ONE SIDE OF THE FIELD FABRICATED POURABLE SEALER POCKET EXCEEDS 12" (30cm), USE WOOD BLOCKING TO ANCHOR SHEET METAL.
- 10. MINIMUM 1" (2.5cm) CLEARANCE REQUIRED BETWEEN PENETRATIONS.



MANDATORY EPDM
PRIMER AT ALL
INTERFACES OF
POURABLE SEALER
VS. ANY OTHER
COMPONENT & AS
SHOWN UNDER
--- FLASHING

ĺ	DIMENSIONS		cm	
	\bigcirc	1"	2.5	MIN.
	$^{\otimes}$	2"	5	MIN.
	0	3"	7.5	




FIELD FABRICATED POURABLE SEALER POCKET

MAXIMUM WARRANTY: 20 YEARS




DETAIL NO.

U-16B



- 1. THE MAXIMUM ALLOWABLE SURFACE TEMPERATURE OF THE PENETRATION SHALL NOT EXCEED 180° F (82° C).
- 2. ALL DEBRIS (PAINT, RUST, LEAD, OTHER FLASHINGS, ETC.) MUST BE REMOVED FROM THE PENETRATION.
- 3. ALL SURFACES MUST BE PRIMED WITH EPDM PRIMER PRIOR TO APPLYING POURABLE SEALER.
- 4. POURABLE SEALER MUST COMPLETELY FILL POURABLE SEALER POCKET TO PREVENT PONDING OF WATER.
- 5. POURABLE SEALER MUST CONTACT PRIMED PRESSURE—SENSITIVE ELASTOFORM FLASHING AND DECK MEMBRANE.
- 6. SECUREMENT IS REQUIRED FOR POURABLE SEALER POCKETS WHICH ARE GREATER THAN 18" (46cm) IN DIAMETER. REFER TO SPECIFICATIONS.
- 7. ON MECHANICALLY—FASTENED ROOFING SYSTEMS, ADDITIONAL MEMBRANE SECUREMENT IS REQUIRED (SIMILAR TO DETAIL MF—8A) REGARDLESS OF SIZE AND DIAMETER, UNLESS WOOD NAILERS ARE PRESENT.
- 8. DECK FLANGE MUST BE CONTINUOUS WITH ROUNDED CORNERS.
- 9. WHEN ANY ONE SIDE OF THE FIELD FABRICATED POURABLE SEALER POCKET EXCEEDS 12" (30cm), USE WOOD BLOCKING TO ANCHOR SHEET METAL.
- 10. MINIMUM 1" (2.5cm) CLEARANCE REQUIRED BETWEEN PENETRATIONS.



MANDATORY EPDM
PRIMER AT ALL
INTERFACES OF
POURABLE SEALER
VS. ANY OTHER
COMPONENT & AS
SHOWN UNDER
--- FLASHING

DIMENSIONS		cm	
A	1"	2.5	MIN.
B	2"	5	MIN.
0	3"	7.5	




FIELD FABRICATED POURABLE SEALER POCKET

MAXIMUM WARRANTY: 30 YEARS




DETAIL NO.

U-16B.1



- THE MAXIMUM ALLOWABLE SURFACE TEMPERATURE OF THE PENETRATION SHALL NOT EXCEED 180° F (82° C).
- 2. ALL DEBRIS (PAINT, RUST, LEAD, OTHER FLASHINGS, ETC.) MUST BE REMOVED FROM THE PENETRATION.
- 3. <u>ALL SURFACES MUST BE PRIMED WITH EPDM PRIMER PRIOR TO APPLYING POURABLE SEALER.</u>
- 4. POURABLE SEALER MUST COMPLETELY FILL POURABLE SEALER POCKET TO PREVENT PONDING OF WATER.
- 5. POURABLE SEALER MUST CONTACT PRIMED PRESSURE-SENSITIVE ELASTOFORM FLASHING.
- 6. SHAPE METAL DAM TO FIT EXISTING PITCH POCKET.
- 7. SECUREMENT IS REQUIRED FOR POURABLE SEALER POCKETS WHICH ARE GREATER THAN 18" (46cm) IN DIAMETER. REFER TO SPECIFICATIONS.
- 8. ON MECHANICALLY—FASTENED ROOFING SYSTEMS, ADDITIONAL MEMBRANE SECUREMENT IS REQUIRED (SIMILAR TO DETAIL MF—8A) REGARDLESS OF SIZE OR DIAMETER.
- 9. MINIMUM 1" (2.5cm) CLEARANCE REQUIRED BETWEEN PENETRATIONS.



MANDATORY EPDM PRIMER AT ALL INTERFACES OF POURABLE SEALER

DIME	NSIONS	cm	
A	1"	2.5	MIN.
B	2"	5	MIN.
(C)	3"	7.5	

U (UNIVERSAL DETAIL




EXTENDED POURABLE SEALER POCKET

T BOW


DETAIL NO.

|U-16C

MAXIMUM WARRANTY: 20 YEARS



- THE MAXIMUM ALLOWABLE SURFACE TEMPERATURE OF THE PENETRATION SHALL NOT EXCEED 180° F (82° C).
- ALL DEBRIS (PAINT, RUST, LEAD, OTHER FLASHINGS, ETC.) MUST BE REMOVED FROM THE PENETRATION.
- 3. ALL SURFACES MUST BE PRIMED WITH EPDM PRIMER PRIOR TO APPLYING POURABLE SEALER.
- 4. POURABLE SEALER MUST COMPLETELY FILL POURABLE SEALER POCKET TO PREVENT PONDING OF WATER.
- 5. POURABLE SEALER MUST CONTACT PRIMED PRESSURE-SENSITIVE ELASTOFORM FLASHING.
- SHAPE METAL DAM TO FIT EXISTING PITCH POCKET.
- 7. SECUREMENT IS REQUIRED FOR POURABLE SEALER POCKETS WHICH ARE GREATER THAN 18" (46cm) IN DIAMETER. REFER TO SPECIFICATIONS.
- 8. ON MECHANICALLY-FASTENED ROOFING SYSTEMS, ADDITIONAL MEMBRANE SECUREMENT IS REQUIRED (SIMILAR TO DETAIL MF-8A) REGARDLESS OF SIZE OR DIAMETER.
- 9. MINIMUM 1" (2.5cm) CLEARANCE REQUIRED BETWEEN PENETRATIONS.



MANDATORY EPDM PRIMER AT ALL INTERFACES OF POURABLE SEALER

DIME	NSIONS	cm	
\bigcirc	1"	2.5	MIN.
$^{\otimes}$	2"	5	MIN.
(C)	3"	7.5	

U (UNIVERSAL DETAIL)




EXTENDED POURABLE SEALER POCKET

DETAIL NO.

U-16C.1

MAXIMUM WARRANTY: 30 YEARS



OUTSIDE CORNER.

SCUPPERS WITHOUT A CONTINUOUS WATERTIGHT DESIGN MUST BE FLASHED IN PER DETAIL U-15

AND ALLOW TO DRY.


SCUPPER: SINGLE LAYER FLASHING

:5

MAXIMUM WARRANTY: 25 YEARS

DETAIL NO.


FIRST





- 1. METAL SCUPPER BOX MUST HAVE CONTINUOUS FLANGES WITH ROUNDED CORNERS, SOLDER ALL SCUPPER SEAMS AIR & WATER—TIGHT.
- 2. WATER CUT-OFF MASTIC UNDER SCUPPER FLANGES MUST BE UNDER CONSTANT COMPRESSION.
- 3. TAPERED EDGE STRIP BY HUNTER OR CANT STRIP, AS REQUIRED & SET IN ADHESIVE OR SHAVE THE EDGES OF TAPERED INSULATION.

DIMENSIONS		cm	
A	2"	5	MIN.
B	3"	7.6	MIN.

CARLISLE	SCUPPER: DOUBLE LAYERS FLASHING PAGE 1 OF 2	U-18A.1
SYNTEC SYSTEMS	MAXIMUM WARRANTY: 30 YEARS	U (UNIVERSAL DETAIL)










SCUPPER: DOUBLE LAYERS FLASHING

PAGE 2 OF 2

MAXIMUM WARRANTY: 30 YEARS




DETAIL NO. U-18A.1




- 1. DETAIL MAY BE USED FOR ANY FASTENER PENETRATION (E.G., ACCESS LADDER, ANCHOR SUPPORT TO PARAPET).
- 2. WATER CUT-OFF MASTIC MUST BE UNDER CONSTANT COMPRESSION.
- 3. COMPLY WITH ZONING ORDNANCE AND LOCAL CODES FOR MOUNTING A LIGHTNING SYSTEM.
- 4. DETAIL UNACCEPTABLE FOR HORIZONTAL APPLICATIONS ON ROOF DECK.






- SURE—SEAL TWO COMPONENT POURABLE SEALER IN CONJUNCTION WITH EPDM PRIMER, OR UNIVERSAL SINGLE—PLY SEALANT.
- 2. CLEAN EXPOSED MEMBRANE WITH WEATHERED MEMBRANE CLEANER AND ALLOW TO DRY.
- 3. PRIOR TO THE APPLICATION OF POURABLE SEALER, APPLY EPDM PRIMER TO THE MEMBRANE AND LIGHTNING ROD BASE ACHIEVING A VERY THIN EVEN COAT ON BOTH SURFACES. ALLOW PRIMER TO DRY UNTIL IT IS TACK FREE.
- 4. COMPLY WITH ZONING ORDNANCE AND LOCAL CODES FOR MOUNTING A LIGHTNING SYSTEM.






- 1. DETAIL FOR SURE—SEAL/SURE—WHITE ADHERED AND SURE—TOUGH MECHANICALLY—FASTENED ROOFING SYSTEMS WHEN SLOPE AT VALLEY EXCEEDS 2" (5cm) IN ONE HORIZONTAL FOOT.
- 2. ON MECHANICALLY—FASTENED ROOFING SYSTEMS, HP FASTENERS AND POLYMER SEAMS ARE REQUIRED OVER STEEL DECKS.
- 3. EPDM PRIMER MUST BE APPLIED TO BACK SIDE OF DECK MEMBRANE PRIOR TO COMPLETING SPLICE TO PRESSURE-SENSITIVE RUSS.









- 1. FOR PARAPET FLASHING, REFER TO DETAIL(S) U-12.
- 2. FOR CURB FLASHING, REFER TO DETAIL(S) U-5.
- 3. FOR CORNER APPLICATION, REFER TO DETAIL(S) U-15.

