

G U I D E - S P E C
AFX EPDM Hot Mopped Roofing System

January 2025

This **GUIDE-SPEC** is a brief outline of AFX EPDM Hot Mopped Roofing System requirements and is intended for use as a submittal with a bid package. Specifiers and Carlisle Authorized Roofing Applicators must comply with the specification and details contained in Carlisle's Technical Manual.

PART I GENERAL

1.01 DESCRIPTION

The **AFX EPDM Hot Mopped Roofing System** incorporates the use of hot mopped (Type III or IV Asphalt, Modified SBS or SEBS Asphalt) AFX Membrane to recover various existing roof systems. The membrane assembly can also be used for new construction or when existing roofing material is to be removed. The AFX membrane combines either Sure-Seal® or Sure-White® non-reinforced EPDM membrane with 7.5 ounce per square yard, non-woven polyester polypropylene blended fleece-backing.

Adjoining EPDM sheets are spliced together with Factory-Applied SecurTAPETM and Primer. Sheet end laps are butted and overlaid with Sure-Seal or Sure-White Cured Cover Strip, or overlapped and overlaid with Sure-Seal Pressure-Sensitive Overlayment Strip (black only).

1.02 QUALITY ASSURANCE

- A. The specified roofing system must be installed by a Carlisle Authorized Roofing Applicator in compliance with drawings and specifications as approved by Carlisle SynTec.
- B. Upon request, an inspection shall be conducted by a Field Service Representative of Carlisle to ascertain that the membrane roofing system has been installed according to Carlisle's published specifications and details applicable at the time of bid. This inspection is to determine whether a warranty shall be issued. It is not intended as a final inspection for the benefit of the owner.
- C. For specific code approvals achieved with this system, refer to Carlisle's AFX Code Approval Guide, DORA (Directory of Roof Assemblies), FM Approvals or UL Fire Resistance Directory for Roofing Materials and Systems.

1.03 SUBMITTALS

- A. To ensure compliance with Carlisle's minimum warranty requirements, the following projects should be forwarded to Carlisle for review prior to installation, preferably prior to bid.
 - 1. Air pressurized buildings, canopies, and buildings with large openings, cold storage buildings or freezer facilities, adhered roofing system projects over 50' in height or projects where the membrane is expected to come in direct contact with petroleum-based products, waste products (i.e., grease, oil animal fates, etc.) and other chemicals.
 - 2. Projects where 20 or 25-year System Warranties or wind speed coverage greater than 72 mph are specified.

1.04 GENERAL DESIGN CONSIDERATIONS

- A. It is the responsibility of the building owner or his/her designated representative to verify structural load limitation. In addition, a core cut may be taken to verify weight of existing components when the roofing system is to be specified on an existing facility.
- B. Interior moisture generated due to the construction process or from the operation of the building could adversely impact various components within the roofing assembly if not addressed. Refer to Carlisle Technical Manual for industry recommendations.

1.05 WARRANTY

Membrane System Warranty is available for roofing systems on commercial buildings within the United States and applies only to products manufactured or marketed by Carlisle SynTec. The membrane system is defined as membrane, flashings, adhesives, sealants and other Carlisle brand products utilized in the installation.

Table I Membrane System Warranty Options – 5 Year to 25 Year

General: When AFX membrane is adhered directly to an acceptable existing roofing material or to a concrete deck, the application will be limited to Maximum 25 Year Warranty with Peak Gust Wind Speed of 80 MPH. When greater warranty coverage is specified, Carlisle must be contacted to determine any added enhancements.

Years	Membrane Attachment (3)			Minimum Membrane Thickness	Additional Coverage (1)		
	55 or 72 mph	80 mph	90 mph		Accidental Puncture (4)	1" Dia. Hail	2" Dia. Hail
5, 10, 15 or 20 year	Type III / IV or Cold Applied	SEBS	SEBS & Modified Base Sheet	AFX EPDM 90-mil	Up to 8 man-hours per year	Type III / IV or Cold Applied	NA (2)
25 year	Type III / IV & Modified Base Sheet	SEBS & Modified Base Sheet	NA (2)	AFX EPDM 105-mil	Up to 16 man-hours per year	SEBS	SEBS

- (1) Hail coverage option is available and requires underlayment of HP Recovery Board, or Securock
 (2) NA = Not Available
 (3) Projects specifying an Underlayment/Insulation refer to Carlisle Technical Manual.
 (4) Carlisle's Accidental Puncture Warranty covers labor hours and material used during the repair. Maximum labor and material hours are dependent upon system design. Refer to the Warranty Availability Quick Reference Guide for coverage.

Table II Underlayment/Insulation & Required Attachment

Warranty Wind Speed	Minimum Membrane Underlayment	Insulation/Underlayment Attachment	
		Asphalt Fully Mopped 4' x 4' size bd	# of Fasteners for 4' x 8' size bd (1)
55mph or 72mph	1/2" HP Recovery Bd	Type III or IV	16
	1/2" Securock	Type III or IV	12
	1/2" Securshield HD	Type III or IV	16

Notes:

- (1) For steel, concrete, and wood plank decks.

Table IV Direct Application to Existing Roofing Materials - Up to 15 YR

Warranty Wind Speed	Existing Roofing Material (1)	Membrane Adhesion with Asphalt
55mph or 72mph	Smooth Surface BUR / Mineral Surface Cap Sheet	Direct with Type III or IV Asphalt
	Modified Bitumen	Direct with Type III or IV Asphalt

Notes:

- (1) Refer to paragraph 3.02 for existing material preparation.

Additional Design Considerations

- Refer to Table I for minimum membrane thickness.
- All wet roofing materials must be totally removed and fill all voids with appropriate material relatively flush with the existing surface.
- Insulation/cover board is required for reroofing of Gravel Surface BUR, Coal Tar Pitch, or existing single-ply membrane. Refer to Table II.
- For 20 year warranty or additional wind coverage, please contact Carlisle for design considerations.

1.06 PRODUCT DELIVERY, STORAGE AND HANDLING

- Deliver materials to the job site in the original, unopened containers labeled with the manufacturer's name, brand name and installation instructions.
- Job site storage temperatures in excess of 90° F may affect shelf life of curable materials (i.e., Sealant, cleaners, primers, SecurTAPE, Pourable Sealer, and Pressure-Sensitive Flashing).
- Membrane should be stored in its original plastic wrap or be covered to protect from moisture. Any moisture absorbed by the fleece-backing must be removed by using a wet-vac system, prior to membrane mopping.

1.07 JOB CONDITIONS

- Refer to Carlisle Technical Manual for applicable project specific Job Conditions.

PART II PRODUCTS

2.01 GENERAL

The components of this roofing system are to be products of Carlisle or accepted by Carlisle as compatible. The installation, performance or integrity of products by others, **when selected by the specifier and accepted as compatible by Carlisle**, is not the responsibility of Carlisle and is expressly disclaimed by the Carlisle Warranty. Other components (asphalt and pressure relief vents) which are not supplied by Carlisle, when required for the installation of this roofing system, may be included as part of the Carlisle Warranty.

2.02 MEMBRANE

The membrane incorporates 45-mil or 60-mil thick non-reinforced Sure-Seal EPDM (black) or 60-mil thick non-reinforced, Sure-White EPDM (white-on-black) membrane laminated to 7.5 ounce per square yard, non-woven polyester polypropylene blended fleece resulting in a total finished sheet thickness of 90-mil or 105-mil. Black membrane is available in 4.5' or 10' wide and lengths 50' or 100'. White membrane is available 4.5' wide and length 50'.

2.03 RELATED CARLISLE MATERIALS

- A. Carlisle Base Sheets, Fasteners/Plates, CCW-550 Primer, SecurTAPE, Primer, Lap Sealant, Pressure Sensitive Cover Strips, Weathered Membrane Cleaner, Termination Bars, Water Cut-Off Mastic, and other Carlisle products such as cover boards, insulations, and edgings are also required when a System Warranty is specified.
- B. Other Carlisle Products – Walkway Pads, Pre-Molded Pipe Seals, LIQUISEAL Liquid Flashing and Pressure-Sensitive Inside/Outside Corners.

2.04 RELATED MATERIALS

- A. **Hot Asphalt** - Type III or IV, SBS or SEBS Hot Asphalt shall conform to the physical properties listed in the Carlisle Technical Manual.
- B. **One-Way Relief Vents** - Vents are required when the membrane is adhered over lightweight insulating concrete and installed at the rate listed in the Carlisle Technical Manual.

PART III EXECUTION

3.01 GENERAL

When feasible, begin the application at the highest point of the highest roof level and work to the lowest point to prevent moisture infiltration and minimize construction traffic on completed sections. This will include completion of all flashings and terminations.

3.02 ROOF DECK CRITERIA

- A. A proper substrate shall be provided by the building owner. The structure shall be sufficient to withstand normal construction loads and live loads.
- B. Defects in the roof deck must be reported and documented to the specifier, general contractor and building owner for assessment. The Carlisle Authorized Roofing Applicator shall not proceed unless the defects are corrected.
- C. Refer to Carlisle Technical Manual for acceptable decks and the applicable Carlisle Fasteners (when mechanical attachment of insulation or base sheets is specified).

3.03 SUBSTRATE REQUIREMENTS

Construction Type	Acceptable Roof Deck/Substrate	Asphalt Applied
Retrofit/No Tearoff	Existing Smooth Surface BUR or Mineral Surface Cap Sheet	Direct Application (3)
	Gravel Surfaced BUR (2)	Cover Board / Insulation (1)
	Coal Tar Pitch	Cover Board / Insulation (1)
	Modified Bitumen	Direct Application (3)
	Existing Single-Ply	Cover Board / Insulation (1)

- (1) Refer to the Warranty Table II of this specification, for the minimum underlayment requirements.
- (2) When installing this roofing system over existing gravel surfaced built-up roof, loose gravel must be removed. Any uneven areas of the substrate must be leveled to prevent insulation from bridging.
- (3) Prepare existing Smooth Surface BUR (Type III or IV), Mineral Surface Cap Sheet, and Modified Bitumen with CCW-550 Cut Back Asphalt Primer prior to adhering AFX membrane with asphalt.

A. General

The substrate must be dry, relatively smooth, free of protrusions, debris, sharp edges or foreign materials and must be free of accumulated water, ice and snow. Cracks or voids in the substrate greater than 1/4" must be filled with suitable material.

B. Structural concrete deck

The membrane can be mopped directly to structural concrete, in addition to paragraph 3.03.A, concrete must be smooth with a steel trowel finish and then primed with CCW-550 Cut Back Asphalt primer prior to membrane mopping.

C. Lightweight insulating concrete

Projects with new or existing lightweight insulating concrete substrates will require the use of a Carlisle Base Sheet and One-Way Relief Vent, refer to Carlisle Technical Manual for fastening patterns for base sheets and layout of vents.

3.04 INSTALLATION

Refer to the applicable Safety Data Sheets and Technical/Product Data Sheets for cautions and warnings.

A. Base Sheet Attachment

1. When base sheets are to be mopped to a structural concrete deck, the deck must be primed with CCW-550 Cut Back Asphalt Primer (ASTM D 41) prior to mopping base sheets.
2. Prior to installing either the AFX membrane or insulation in asphalt, Carlisle Base Sheets shall be fastened into the gypsum, lightweight insulated concrete or fibrous cement with Carlisle Dual Prong fasteners.
3. When no insulation is specified and AFX Membrane is to be directly mopped to a Carlisle Modified Base Sheet, a base sheet must be fastened with Carlisle HP or HP-X Fasteners with 3" diameter insulation plates.

B. Insulation Attachment

1. When specified, the cover board or insulation may be adhered with asphalt to a Carlisle Base Sheet or a concrete deck primed (CCW-550 Cut Back Asphalt) with Type III or IV Asphalt, SBS or SEBS as outlined in the Carlisle Technical Manual.
2. When roof insulation is specified to be mechanically securement is specified, use appropriate Carlisle fasteners for deck type and ensure minimum deck penetration.

C. AFX Membrane Installation

1. AFX Membrane shall be fully adhered to an acceptable substrate with hand mopping Type III or IV, SBS or SEBS asphalt. Apply asphalt to the substrate the full width of the membrane extending a maximum of 3 to 6 feet while rolling the membrane into the asphalt immediately.
2. After membrane mopping, immediately after adhesion, brush down the sheet with a stiff bristled broom using light to medium pressure. Do not use weighted rollers or heavy pressure when brooming the membrane to avoid asphalt saturation of the fleece.
3. When overlapping adjoining AFX Membranes, extend fleece backing approximately 1/2 inch above previously installed membrane. This will avoid direct contact between membrane in the seam area and hot asphalt adhesive.
4. Refer to Carlisle Technical Manual for alternate attachment methods, asphalt temperature, cover rates, and steps to avoid saturation of fleece backing with asphalt

D. AFX Membrane Splicing with Factory-Applied SecurTAPE

1. AFX EPDM membrane has a selva edge (fleece backing is discontinued) with Factory-Applied SecurTAPE (3" or 6" wide) along the length of the sheet for membrane splicing in accordance with the following procedures and within the Carlisle Technical Manual.
2. Selva edges are not provided along the width of the membrane. Adjoining membrane sheets (end-to-end) shall be butted together and overlaid with 6" wide Pressure-Sensitive Cured Cover Strip in accordance with applicable details.

E. Flashing Considerations

Refer to Carlisle Technical Manual for other requirements.

Attach copies of the applicable Carlisle Details that pertain to the individual project to complete a bid package submittal.

Copyright 2025 Carlisle Construction Materials Incorporated
Carlisle, Sure-Seal, FleeceBACK, LIQUISEAL, and SecurTAPE are Trademarks of Carlisle Construction Materials Incorporated

Carlisle SynTec P. O. Box 7000 Carlisle, PA 17013-0925 (800-479-6832)
<http://www.carlisle-syntec.com>