

VersiWeld TPO Reinforced Overlayment Strip



Overview

Versico's VersiWeld TPO Reinforced Overlayment Strip is made from heat-weldable, reinforced thermoplastic polyolefin membrane. It is available in 45-mil 6" x 100' and 60-mil 6" x 100' and 9" x 50' rolls. It can be used to cover end laps on VersiFleece and QA TPO systems and to strip in flat metal flanges on details such as TPO coated drip edges, gravel stops, and scuppers.

Features and Benefits

- Made from reinforced VersiWeld TPO enhanced with the OctaGuard XT™ weathering package for exceptional resistance to heat, solar UV, ozone and oxidation
- 6" and 9" widths save labor by eliminating the need to slit large rolls of membrane
- Available in white, gray, and tan

Installation

1. Ensure the existing TPO membrane, or Coated Metal surface is clean prior to welding the Overlayment Strip in place. If dirt is present, use Versico's Weathered Membrane Cleaner to properly prepare the surface.
2. Weld Overlayment Strip in place using an auto-welder or hand welder with a silicone roller.
3. Install T-joint covers as necessary. Install cut-edge sealant along all exposed edges of Overlayment Strip.

REVIEW CURRENT VERSICO SPECIFICATIONS AND DETAILS FOR SPECIFIC INSTALLATION REQUIREMENTS.

Precautions

- UV filtering sunglasses are strongly recommended when working on VersiWeld TPO roofing systems.
- Store VersiWeld TPO Overlayment Strip in a cool, shaded area and cover with light-colored, breathable, waterproof tarpaulins.

Typical Properties and Characteristics

Properties	Test Method	45-mil	60-mil
Tolerance on nominal thickness, %	ASTM D751	+/- 10%	+/- 10%
Thickness Over Scrim, in. (mm)	D7635 optical method avg. of 3 areas	.018 typical (0.457)	0.024 typical (0.610)
Breaking Strength, lbf (kN)	ASTM D751 grab method	225 (1.0) min 320 (1.4) typical	250 (1.1) min 360 (1.6) typical
Elongation Break of Reinforcement, %	ASTM D751 grab method	15 min 25 typical	15 min 25 typical
Tearing Strength, lbf (N)	ASTM D751 proc. B 8 in. x 8 in.	55 (245) min 130 (578) typical	55 (245) min 130 (578) typical
Brittleness Point, °F (°C)	ASTM D2137	-40 (-40) max -50 (-46) typical	-40 (-40) max -50 (-46) typical
Linear Dimensional Change, %	ASTM D1204, 6 hours at 158°F	± 1 max -0.2 typical	± 1 max -0.2 typical
Typical Weights lb/ft ² (kg/m ²)		0.23 (1.1)	0.29 (1.4)

Refer to VersiWeld TPO Reinforced Membrane Typical Properties and Characteristics for more information.

Typical properties and characteristics are based on samples tested and are not guaranteed for all samples of this product. This data and information is intended as a guide and does not reflect the specification range for any particular property of this product.

LEED® Information

Pre-consumer Recycled Content	10%
Post-consumer Recycled Content	0%
Manufacturing Location	Senatobia, MS
Solar Reflectance Index	99 (white), 86 (tan)



A SINGLE SOURCE FOR SINGLE-PLY ROOFING

800.992.7663 • www.versico.com