

# VersiFlex™ PVC Membrane (Minimum Thickness)



## Overview

Versico's VersiFlex PVC is an advanced-formula, heat-weldable PVC membrane that is designed for long-term weatherability and performance. The physical properties of the membrane are enhanced by a tenacious, anti-wicking, weft-inserted polyester fabric that is encapsulated by thick PVC-based top and bottom plies. The membrane's smooth surfaces facilitate a permanent weld for a consistent, watertight, monolithic roof assembly.

## Features and Benefits

- Exceptional fire and chemical resistance
- Fully formulated monolithic top-ply for long-term weatherability
- Enhanced physical characteristics meeting ASTM D4434 Type IV requirements
- Antimicrobials throughout the polymer for increased resistance to mold, mildew, and algae growth
- Highly flexible with a wide window of weldability for ease of installation
- Available colors:



White

Gray

Tan



## Sustainable Attributes

Versico Roofing Systems' focus has always been innovation - Innovation to solve problems, improve performance, reduce labor, and above all, improve sustainability. Versico is committed to driving sustainable and efficient processes in the design and manufacturing of our products.

- PVC polymer derived from less than 50% fossil fuels
- Up to 10% pre-consumer recycled content
- Fully recyclable when used in mechanically-attached systems
- 3<sup>rd</sup>-party verified Environmental Product Declaration available
- California Title 24 compliant\*
- See Radiative Properties and LEED® Information tables below for additional attributes

\*White only.

## Installation

Installation requires minimal labor and few components, making it quick and easy to install. Sheet seams are heat-welded together using hot-air welding equipment to create a monolithic, water-tight roof system.

VersiFlex PVC is suitable for the following roof systems:

**Fully-Adhered** – membrane is adhered to a suitable substrate utilizing an appropriate bonding adhesive

**Mechanically Attached** – membrane is attached to a suitable substrate utilizing plates and fasteners which are overlapped with membrane

**Induction-Welded** – membrane is attached to a suitable substrate via an induction welding tool being placed over the membrane where a fastened PVC induction welding plate is located to weld the two components together

REVIEW CURRENT VERSICO SPECIFICATIONS AND DETAILS FOR SPECIFIC INSTALLATION REQUIREMENTS.

# VersiFlex PVC Membrane (Minimum Thickness)

## Precautions

- Sunglasses that filter out ultraviolet light are strongly recommended when working on reflective membranes. Roofing technicians should dress appropriately and wear sunscreen.
- Exercise caution when walking on wet membranes; membranes may be slippery when wet or due to frost and ice buildup.
- Care must be exercised while working close to a roof edge when the surrounding area is snow-covered, as the roof edge may not be clearly visible.
- Use proper stacking procedures to ensure sufficient stability of the materials.
- Store membrane in its original, undisturbed plastic wrap in a cool, shaded area and cover with light-colored, breathable, waterproof tarpaulins.
- Membrane that has been exposed to the weather or contaminated with dirt must be prepared with VersiFlex PVC/KEE HP Membrane Cleaner prior to hot-air welding.

## Supplemental Approvals, Statements and Characteristics

- VersiFlex PVC meets or exceeds the requirements of ASTM D4434 Standard Specification for Poly (Vinyl Chloride) Sheet Roofing. VersiFlex PVC is classified as Type III and/or Type IV as defined by ASTM D4434.
- VersiFlex reinforced PVC was tested for dynamic puncture resistance per ASTM D5635-04 using the most recently modified impact head. 50-mil thick membrane was watertight after an impact energy of 22.5 J (16.6 ft-lbf), which passes the ASTM D4434 requirement.
- VersiFlex reinforced PVC was tested for static puncture resistance per ASTM D5602-98 and exceeded 33 lbf (145 N), which passes the ASTM D4434 requirement.

## Radiative Properties for Cool Roof Rating Council (CRRC) and LEED

Physical Property	Test Method	White PVC	Tan PVC	Gray PVC
CRRC - Initial Solar Reflectance	ASTM C1549	0.87	0.72	0.59
CRRC - Solar Reflectance after 3 years	ASTM C1549 (uncleaned)	0.70	0.56	0.49
CRRC - Initial Thermal Emittance	ASTM C1371	0.89	0.87	0.89
CRRC - Thermal Emittance after 3 years	ASTM C1371 (uncleaned)	0.88	0.87	0.89
Solar Reflective Index (SRI)	ASTM E1980	110	89	70
Solar Reflective Index (SRI) SRI after 3 years	ASTM E1980	86	65	57

## LEED Information

Pre-consumer Recycled Content	Up to 10%
Post-consumer Recycled Content	0%
Manufacturing Location	Greenville, IL
Solar Reflective Index (SRI), Initial	White: 110, Tan: 89, Gray: 70



# VersiFlex PVC Membrane (Minimum Thickness)

## Typical Properties and Characteristics

Physical Property	ASTM D4434 Requirement	60-mil Min	80-mil Min
<b>Thickness over scrim</b> , in. (mm) ASTM D4434 optical method average of 3 areas	0.016 min (0.40)	0.028 (0.711)	0.038 (0.965)
<b>Weight</b> , lbs/ft <sup>2</sup> (kg/m <sup>2</sup> )	No requirement	0.40 (1.95)	0.55 (2.68)
<b>Breaking strength</b> (MD x CD), lbf/in (kN/m) ASTM D751 grab method	275 min (48)	330 x 300 (58 x 55)	360 x 330 (63 x 58)
<b>Elongation</b> break of reinforcement (MD x CD), % ASTM D751 grab method	25 min	30 x 30	30 x 30
<b>Tearing strength</b> (MD x CD), lbf (N) ASTM D751 proc. B, 8 in. x 8 in.	90 min (400)	100 x 130 (445 x 578)	100 x 132 (445 x 587)
<b>Low temperature bend</b> , ASTM D2136, no cracks 5x at -40°C	PASS	PASS (-40°C)	PASS (-40°C)
<b>Linear dimensional change</b> , % ASTM D1204, 6 hours at 176°F	±0.5 max	0.4	0.4
<b>Ozone resistance</b> , no cracks 7x ASTM D1149, 100pphm, 168 hrs	PASS	PASS	PASS
<b>Water absorption resistance</b> , mass % ASTM D570, 166 hours at 158°F water	±3.0 max	2.0	2.0
<b>Field seam strength</b> , lbf/in. (kN/m) ASTM D1876 tested in peel	No requirement	25 (4.4) min 60 (10.5) typ.	25 (4.4) min 60 (10.5) typ.
<b>Water vapor permeance</b> , Perms, ASTM E96 proc. B	No requirement	0.10 max 0.05 typ	0.10 max 0.05 typ
<b>Puncture resistance</b> - Federal, lbf (kN) FTM 101C, method 2031	No requirement	320	380
<b>Puncture resistance</b> - Dynamic, J (ft-lbf) ASTM D5635	20 (14.7)	PASS	PASS
<b>Puncture resistance</b> - Static, lbf (N) ASTM D5602	33 (145)	PASS	PASS
<b>Xenon-Arc resistance</b> , no cracks/ crazing 10x, ASTM G155 0.35 W/m <sup>2</sup> at 340-nm, 63°C B.P.T. 12,600 kJ/m <sup>2</sup> total radiant exposure 10,000 hours	PASS	PASS	PASS
<b>Properties after heat aging</b> ASTM D3045, 56 days at 176°F Breaking strength, % retained Elongation reinf., % retained	90 min	90 min 90 min	90 min 90 min
<b>Air Permeance</b> , ASTM E2178	No Requirement	PASS	PASS

Typical properties and characteristics are based on samples tested and are not guaranteed for all samples of this product. This data and information is intended as a guide and does not reflect the specification range for any particular property of this product.



A SINGLE SOURCE FOR SINGLE-PLY ROOFING

800.992.7663 • [www.versico.com](http://www.versico.com)