

# VersiGard® White EPDM Peel & Stick Inside/Outside Corners



## Overview

Versico's VersiGard White EPDM Peel & Stick (P&S) Inside/Outside Corners are a 60-mil-thick, uncured EPDM Flashing laminated to 30-mil-thick fully cured, pressure-sensitive adhesive provides 90 mils of total thickness.

P&S Inside/Outside Corners are ideal for installing both inside and outside corners on all VersiGard EPDM and VersiWeld® TPO Roofing Systems.

They can also be used as T-Joint Covers at field splice intersections or at horizontal to vertical transitions of field splices.

## Features and Benefits

- Available in 7" x 9" and packaged 20 per carton
- Pre-cut flashing increases the installation speed by eliminating cutting time and reducing adhesive application requirements
- Combine with P&S Curb Flashing for maximum productivity
- Cleaner appearance as all Corners and T-Joint Covers are pre-cut to the same size
- Approved for use on EPDM and TPO membranes

## Installation

1. The entire surface where the P&S Corner/T-Joint Cover will be applied must be clean. The adhesive on the back of the P&S Corner/T-Joint Cover will not adhere to dusted/dirty surfaces. Any residual contamination will be detrimental to the bond strength of the adhesive.
2. Remove dirt and excess dust from the splice area by wiping with a clean rag. If necessary, clean the splice area thoroughly with Weathered Membrane Cleaner.
3. Application of V-150 Primer, TPO Primer, or Low-VOC Primer:
  - a. Standard (Dusted) EPDM Membrane: Apply the appropriate primer with a clean HP Splice Wipe (or equivalent). Scrub the membrane area where the P&S Corner/T-Joint Cover is to be applied in a circular motion to achieve a thin, even coating on the membrane. The properly cleaned/primed area will be uniform in color and free of streaks, globs or puddles.
  - b. Pre-Cleaned (No Dust) EPDM or TPO Membrane: Roller-apply the appropriate primer to the membrane with a short nap length paint roller. The coated area will be free of streaks, globs or puddles.
 

Note: Using excessive amounts of primer will not enhance adhesion of the P&S Corner/T-Joint Cover to the membrane. Use only the necessary amount to obtain 100% coverage of the area where the P&S Corner/T-Joint Cover will be applied.
  - c. Membrane type determines which primer to use. V-150 Primer is used with EPDM membranes. TPO Primer is used with TPO membranes. Low-VOC Primer can be used with either TPO or EPDM membrane.

REVIEW CURRENT VERSICO SPECIFICATIONS AND DETAILS FOR SPECIFIC INSTALLATION REQUIREMENTS

# VersiGard White EPDM Peel & Stick Inside/Outside Corners

## Precautions

- Avoid prolonged contact with skin. In case of contact with skin, thoroughly wash affected area with soap and water.
- Prolonged jobsite storage temperatures in excess of 90°F (32°C) may affect product shelf life.
- In warm, sunny weather, keep P&S Corners/T-Joint Covers in the box or in a shaded area until ready to use.
- P&S Corners/T-Joint Covers must be stored in a dry area.
- Storage and use of P&S Corners/T-Joint Covers at temperatures below 40°F (4°C) will result in a loss of adhesive tack and, in extreme cases, will result in no bond to the substrate. Overnight storage must be available to keep the temperature of the P&S Corners/T-Joint Covers at a minimum of 60°F (15°C). Hot boxes for jobsite storage must be provided to maintain a minimum product temperature of 40°F (4°C).
- Due to solvent flash-off, condensation may form on applied Primer when the ambient temperature is near the dew point. If condensation develops, the application of primer and P&S Corners/T-Joint Covers must be discontinued as proper adhesion will not be achieved. Allow the surface to dry before applying a thin coat of primer and P&S Corners/T-Joint Covers to the previously coated surface.
- Do not allow waste products (petroleum, grease, oil, solvents, vegetable or mineral oil, animal fats, etc.) or direct steam venting to come in contact with the P&S Corners/T-Joint Covers.
- A heat gun is required for forming outside corners in colder temperatures as outlined in the current specifications.
- **KEEP OUT OF THE REACH OF CHILDREN.**

## Typical Properties and Characteristics

| Property   | Value   |
|------------|---|
| Sizes      | 7" x 9" (180 mm x 230 mm)                               |
| Color      | White   |
| Packaging  | 20/carton   |
| Weight     | 6 lbs/carton (2.72 Kg)                                  |
| Shelf Life | 9 months when stored between 60° and 80°F (15° to 26°C) |

Typical properties and characteristics are based on samples tested and are not guaranteed for all samples of this product. This data and information is intended as a guide and does not reflect the specification range for any particular property of this product.

VersiGard White Peel & Stick White Uncured EPDM Flashing meets or exceeds the minimum requirements set forth by ASTM D4811 for a Type 1 (EPDM) Class V (cures on the roof) flashing material.

## LEED® Information

|                                |                |
|--------------------------------|----------------|
| Pre-consumer Recycled Content  | 0%             |
| Post-consumer Recycled Content | 0%             |
| Manufacturing Location         | Greenville, IL |
| Solar Reflectance Index        | N/A            |



A SINGLE SOURCE FOR SINGLE-PLY ROOFING

800.992.7663 • www.versico.com